



(86) Date de dépôt PCT/PCT Filing Date: 2014/03/14
 (87) Date publication PCT/PCT Publication Date: 2014/09/18
 (45) Date de délivrance/Issue Date: 2021/07/27
 (85) Entrée phase nationale/National Entry: 2015/09/01
 (86) N° demande PCT/PCT Application No.: US 2014/029130
 (87) N° publication PCT/PCT Publication No.: 2014/144634
 (30) Priorité/Priority: 2013/03/15 (US61/800,563)

(51) Cl.Int./Int.Cl. *C08F 32/00* (2006.01),
B29C 41/02 (2006.01), *C08F 4/80* (2006.01),
C08L 45/00 (2006.01), *C09D 7/40* (2018.01)
 (72) Inventeurs/Inventors:
 STEPHEN, ANTHONY R., US;
 CRUCE, CHRISTOPHER J., US;
 TRIMMER, MARK S., US;
 GIARDELLO, MICHAEL A., US
 (73) Propriétaire/Owner:
 MATERIA, INC., US
 (74) Agent: GOWLING WLG (CANADA) LLP

(54) Titre : REVETEMENT DANS LE MOULE DE POLYMERES ROMP
 (54) Title: IN-MOLD COATING OF ROMP POLYMERS

(57) **Abrégé/Abstract:**

The present invention relates to in-mold coating of a cyclic olefin polymer. More particularly, the present invention relates to methods and compositions for in-mold coating cyclic olefin polymers prepared by ring opening metathesis polymerization (ROMP) reactions and the manufacture of polymer articles via ROMP. Polymer products produced via the metathesis reactions of the invention may be utilized for a wide range of materials and composite applications. The invention has utility in the fields of polymer and material chemistry and manufacture.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau(10) International Publication Number
WO 2014/144634 A1(43) International Publication Date
18 September 2014 (18.09.2014)

WIPO | PCT

(51) International Patent Classification:
C08F 4/80 (2006.01)(21) International Application Number:
PCT/US2014/029130(22) International Filing Date:
14 March 2014 (14.03.2014)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
61/800,563 15 March 2013 (15.03.2013) US(71) Applicant: **MATERIA, INC.** [US/US]; 60 North San Gabriel Boulevard, Pasadena, CA 91107 (US).(72) Inventors: **STEPHEN, Anthony, R.**; 1505 Fair Oaks #B, South Pasadena, CA 91030 (US). **CRUCE, Christopher, J.**; 13100 Kirkham Way #202, Poway, CA 92064 (US). **TRIMMER, Mark, S.**; 845 Ridgeside Drive, Monrovia, CA 91046 (US). **GIARDELLO, Michael, A.**; 894 S. Oakland Ave., Pasadena, CA 91106 (US).(74) Agent: **RAPHAEL, Aaron, M.**; J.A. Lindeman & Co., PLLC, 3190 Fairview Park Drive, Suite 480, Falls Church, VA 22042 (US).(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM,

AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).**Published:**

- with international search report (Art. 21(3))
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))

(54) Title: IN-MOLD COATING OF ROMP POLYMERS

(57) Abstract: The present invention relates to in-mold coating of a cyclic olefin polymer. More particularly, the present invention relates to methods and compositions for in-mold coating cyclic olefin polymers prepared by ring opening metathesis polymerization (ROMP) reactions and the manufacture of polymer articles via ROMP. Polymer products produced via the metathesis reactions of the invention may be utilized for a wide range of materials and composite applications. The invention has utility in the fields of polymer and material chemistry and manufacture.



WO 2014/144634 A1

IN-MOLD COATING OF ROMP POLYMERS

RELATED APPLICATIONS

This application claims the benefit of U.S. Provisional Patent Application No. 61/800,563, filed March 15, 2013.

TECHNICAL FIELD

[0001] The present invention relates to in-mold coating of a cyclic olefin polymer. More particularly, the present invention relates to methods and compositions for in-mold coating cyclic olefin polymers prepared by ring opening metathesis polymerization (ROMP) reactions and the manufacture of polymer articles via ROMP. Polymer products produced via the metathesis reactions of the invention may be utilized for a wide range of materials and composite applications. The invention has utility in the fields of polymer and material chemistry and manufacture.

BACKGROUND

[0002] The molding of thermoset polymers is a technologically and commercially important processing technique. In one known version of this technique, a liquid cyclic olefin monomer resin is combined with an olefin metathesis catalyst to form a ROMP composition, and the ROMP composition is added (e.g., poured, cast, infused, injected, etc.) into a mold. The ROMP composition is subjected to conditions effective to polymerize the ROMP composition and on completion the molded article is removed from the mold for any optional post cure processing that may be required. As is known in the art, the liquid cyclic olefin monomer resin may optionally contain added modifiers, fillers, reinforcements, flame retardants, pigments, etc. Examples of such prior art ROMP compositions are disclosed in U.S. Pat. Nos. 5,342,909; 6,310,121; 6,515,084; 6,525,125; 6,759,537; 7,329,758, etc.

[0003] ROMP derived polymers have been used to prepare a wide array of commercially important articles including without limitation any molded or shaped article for use as an aerospace component, a marine component, an automotive component, a sporting goods component, an electrical component, and industrial component, medical component, dental component, oil and gas component, or military component. However, priming and painting of ROMP polymer articles is often necessary, particularly when these molded articles are used outdoors, because of their insufficient weathering properties (e.g., oxidation and/or ozone degradation) due to the presence of ethylenic unsaturation throughout the body and surface of the ROMP polymer.

[0004] Typically, in order to improve the weathering properties of ROMP molded articles by painting, the surface of the article may have to be sanded and wiped with a solvent (e.g., 2-propanol, soapy water, etc.) to remove any residual mold release and/or dirt on the surface as a result of manufacturing and/or handling. The article is then treated with a primer treatment and/or a subsequent paint treatment. When the article is first treated with a primer treatment, the second or subsequent paint treatment is often referred to as a top-coat. Unfortunately the application of primer and/or paint (e.g., a paint top-coat) to a demolded ROMP polymer article is a difficult, expensive, and time consuming process. In order to prime and paint a molded ROMP polymer article, it is typically necessary to have a paint booth or clean room to avoid unwanted airborne contaminants such as dirt, dust, oils, etc. The presence of such unwanted airborne contaminants often results in the quality of the primed and/or painted surface (e.g., top-coat paint surface) being unacceptable due to the formation of pinholes and other surface defects present in the primed and/or painted surface. Moreover, the priming and/or painting of ROMP polymer articles typically requires skilled personnel who are experienced and knowledgeable in the art of applying primer and/or paint to polymer surfaces, resulting in additional cost being added to the final primed and/or painted ROMP polymer article.

[0005] Generally, it would be useful and commercially important to be able to provide a molded ROMP polymer article that does not need to be primed and/or painted after being demolded. Therefore, it would be useful and commercially important to be able to apply a primer and/or paint to the surface of a molded ROMP polymer article while the molded ROMP polymer article is still in the mold instead of after demolding. Such processes are common practice in the molding of fiber reinforced plastics, such as fiberglass reinforced composites comprising polyester resin or vinyl ester resins as well as in the molding of polyurethane polymers and are commonly known in the art as gel-coating, in-mold coating, and/or in-mold painting. In particular it would be useful and commercially important to be able to provide an in-mold coated ROMP polymer article where the primer and/or paint is urethane, acrylic, or epoxy based. More preferably, it would be useful and commercially important to be able to provide an in-mold coated ROMP polymer article where the primer and/or paint is urethane based. As is commonly known in the art, urethane based primers and/or paints are typically preferred over acrylic and epoxy based primers and/or paints. Epoxy paints, particularly when used as a top-coat, are known to develop a chalky film on the exterior when exposed to ultraviolet light; therefore, when epoxy paint is used as the top-coat it is often recommended for use in indoor applications or applications where high gloss and/or original color retention are not required. Moreover, epoxy based paints may be suitable for industrial applications and applications in corrosive environments. On the other hand, urethane based paints have superior performance and retention of gloss and color when exposed to ultraviolet light. Therefore, urethane based paints and/or primers are preferred over epoxy based paints and/or primers for outdoor applications.

Acrylic paints differ from urethane paints in that acrylic paints are water based, where urethane paints are solvent based. While the water based nature of acrylic paints makes them less toxic than urethane based paints, the drawback is that acrylic based paints being water based take significantly longer to dry (i.e., cure) than urethane paints. Therefore, the use of acrylic based paints is not particularly conducive to the molding of ROMP polymer articles, where it is advantageous to have short cycle times to reduce the cost of the finished ROMP polymer articles. Moreover, urethane paints are preferred for many applications and are the industry standard for automotive paint, where high gloss and color retention are a requirement. Therefore, it would be particularly useful and commercially important to be able to provide an in-mold coating system for use with molding ROMP polymer articles where the primer and/or paint is urethane based.

[0006] Previously, there have been few methods for in-mold coating of ROMP polymers. One method for in-mold coating of ROMP polymers is disclosed in International Application Nos. WO 2005/046958 A1; WO 2006/070813 A1; WO 2006/118206 A1; WO 2007/086444 A1; and WO 2007/125787 A1. According to these disclosures a ROMP composition is first added to a mold and subjected to conditions effective to polymerize the ROMP composition to form a ROMP polymer article. Once the ROMP polymer article is cured in the mold, the mold is opened some minimal amount to create a gap between the molded article surface(s) and the mold surface(s) and a coating material is injected or poured into the gap, where the coating material flows around the molded article thereby coating the surface(s) of the ROMP polymer article. This method of coating a molded ROMP polymer article suffers from a number of limitations. One major limitation of this method is the difficulty of obtaining a uniformly coated molded article, particularly where the shape of the molded article possesses a complex geometry. Moreover, this methodology also requires the use of a coating material having a composition containing an ethylenic unsaturated monomer, a polymerization component, a mold release agent and an organic-peroxide initiator, where the organic-peroxide initiator is required so as to effectuate adhesion between the coating material and the ROMP polymer.

[0007] Another method for in-mold coating of a ROMP polymer is disclosed in U.S. Pat. No. 5,098,750. According to this disclosure a polymer which is capable of forming a film on the mold surface is dissolved in a solvent, and the solvent/polymer mixture is applied to the mold surface, the mold is closed, a ROMP composition is added to the mold, and the ROMP composition is subjected to conditions effective to polymerize the ROMP composition. While this method may lead to reasonable bonding via interface blending or mechanical bonding between the polymer surface and the polymer film, the overall quality and degree of adhesion between the polymer film and the ROMP polymer over time is questionable. Moreover, this method requires the use of large amounts of volatile organic solvents to dissolve the polymers used to form the polymer film, where the use of these organic solvents creates

elevated workplace volatile organic content (VOC) levels, which in recent years has come under strict regulation by federal and state agencies. While this method is a pre-molded coating procedure there is no discussion related to the use of commercially available low VOC based primer(s) and/or paint(s).

[0008] Therefore, despite advances achieved in the art, particularly in properties of olefin metathesis polymers (e.g., ROMP polymers) and their associated applications, a continuing need therefore exists for further improvement in a number of areas, including methods and compositions for in-mold coating of ROMP polymer articles.

SUMMARY OF INVENTION

[0009] The present invention relates to methods and compositions for in-mold coating of ROMP polymer articles.

[0010] It is an object of the present invention to provide a composition and method for in-mold coating of ROMP polymers for use with commercially available low VOC based primers and/or paints and/or gel coats. In particular, it is an object of the present invention to provide in-mold coated ROMP polymer articles, which overcomes the disadvantages of in-mold coating compositions and methods disclosed in the prior art. Furthermore, it is an object of the present invention to provide compositions and methods for in-mold coating of ROMP polymer articles and/or ROMP polymer composite articles. These objects are solved by providing an in-mold coating adhesion compound, wherein the in-mold coating adhesion compound provides for compositions and methods for in-mold coating of ROMP polymers for use with commercially available low VOC based primers and/or paints and/or gel coats.

[0011] In one embodiment the present invention provides a composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound. In another embodiment the present invention provides a composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound, wherein the at least one in-mold coating adhesion compound is a compound comprising at least one heteroatom containing functional group and at least one metathesis active olefin.

[0012] In another embodiment method of in-mold coating a ROMP polymer comprising, providing a paint, applying the paint to a mold surface to form a painted mold surface, providing an optional primer, applying the optional primer to the painted mold surface, contacting the painted mold surface with a resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound, and subjecting the resin composition to conditions effective to polymerize the resin composition.

[0013] In another embodiment the present invention provides a method of in-mold coating a ROMP polymer comprising, providing a paint, wherein the paint is a urethane based paint, applying the paint to a

mold surface to form a painted mold surface, providing an optional primer, wherein the optional primer is a urethane based primer, applying the optional primer to the painted mold surface, contacting the painted mold surface with a resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and a least one in-mold coating adhesion compound.

[00014] In another embodiment the present invention provides a method of in-mold coating a ROMP polymer comprising, providing a primer, applying the primer to a mold surface to form a primered mold surface, contacting the primered mold surface with a resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound, and subjecting the resin composition to conditions effective to polymerize the resin composition.

[00015] In another embodiment the present invention provides a method of in-mold coating a ROMP polymer comprising, providing a primer, wherein the primer is a urethane based primer, applying the primer to a mold surface to form a primered mold surface, contacting the primered mold surface with a resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound, and subjecting the resin composition to conditions effective to polymerize the resin composition.

[00016] In another embodiment the present invention provides an article of manufacture comprising an in-mold coated ROMP polymer, wherein the in-mold coated ROMP polymer comprises a resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound.

[00017] In another embodiment the present invention provides a composition for adhering a ROMP polymer to a paint, the composition comprising a resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound.

[00018] In another embodiment the present invention provides a composition for adhering a ROMP polymer to a primer, the composition comprising a resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound.

[00019] In another embodiment the present invention provides a method of in-mold coating a ROMP polymer comprising, providing a paint, applying the paint to a mold surface to form a painted mold surface, optionally providing an optional primer, optionally applying the optional primer to the painted mold surface, contacting the painted mold surface with a resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound, and subjecting the resin composition to conditions effective to polymerize the resin composition.

[00020] In another embodiment the present invention provides a method of in-mold coating a ROMP polymer composite comprising, providing a paint, applying the paint to a mold surface to form a painted mold surface, optionally providing an optional primer, optionally applying the optional primer to the

painted mold surface, contacting the painted mold surface with a resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, at least one substrate material, and at least one in-mold coating adhesion compound, and subjecting the resin composition to conditions effective to polymerize the resin composition.

[00021] In another embodiment the present invention provides an article of manufacture comprising an in-mold coated ROMP polymer, wherein the in-mold coated ROMP polymer comprises a metathesis-polymerized resin composition and an adherent coating thereon.

[00022] In another embodiment the present invention provides an article of manufacture comprising an in-mold coated ROMP polymer composite, wherein the in-mold coated ROMP polymer composite comprises a metathesis-polymerized resin composition and an adherent coating thereon

[00023] In another embodiment the present invention provides an article of manufacture comprising an in-mold coated ROMP polymer, where the in-mold coated ROMP polymer comprises a metathesis-polymerized resin composition and an adherent coating thereon, where the metathesis-polymerized resin composition comprises at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound; and the adherent coating comprises a paint or a gel coat, a primer, or combination thereof.

[00024] In another embodiment the present invention provides an article of manufacture comprising an in-mold coated ROMP polymer composite, where the in-mold coated ROMP polymer composite comprises a metathesis-polymerized resin composition and an adherent coating thereon, where the metathesis-polymerized resin composition comprises at least one cyclic olefin, at least one olefin metathesis catalyst, at least one substrate material, and at least one in-mold coating adhesion compound; and the adherent coating comprises a paint or a gel coat, a primer, or combination thereof.

[00025] In another embodiment the present invention provides a use of at least one in-mold coating adhesion compound for making an in-mold coated ROMP polymer.

[00026] In another embodiment the present invention provides a use of at least one in-mold coating adhesion compound for making an in-mold coated ROMP polymer composite.

[00027] In another embodiment the present invention provides a use of at least one in-mold coating adhesion compound for adhering a ROMP polymer to a paint or a gel coat, a primer, or a combination thereof.

[00028] In another embodiment the present invention provides a use of at least one in-mold coating adhesion compound for adhering a ROMP polymer composite to a paint or a gel coat, a primer, or a combination thereof.

[00029] In another embodiment the present invention provides a use of at least one in-mold coating adhesion compound for adhering a metathesis-polymerized resin composition to a paint or a gel coat, a primer, or a combination thereof.

[00030] In another embodiment the present invention provides a use of at least one in-mold coating adhesion compound for adhering a metathesis-polymerized resin composition to a paint or a gel coat, a primer, or combination thereof, where the paint, the gel coat, the primer, or a combination thereof is first applied to a mold surface.

[00031] In another embodiment the present invention provides a use of at least one in-mold coating adhesion compound for adhering a metathesis-polymerized resin composition to a paint or a gel coat, a primer, or a combination thereof, where the metathesis-polymerized resin composition comprises at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound.

[00032] In another embodiment the present invention provides a composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, at least one in-mold coating adhesion compound, and at least one paint.

[00033] In another embodiment the present invention provides a composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, at least one in-mold coating adhesion compound, and at least one gel coat.

[00034] In another embodiment the present invention provides a composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, at least one in-mold coating adhesion compound, and at least one primer.

[00035] In another embodiment the present invention provides a composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, at least one in-mold coating adhesion compound, at least one paint, and optionally at least one primer.

[00036] In another embodiment the present invention provides a composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, at least one in-mold coating adhesion compound, at least one gel coat, and optionally at least one primer.

[00037] In another embodiment the present invention provides a composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, at least one in-mold coating adhesion compound, at least one substrate material, and at least one paint.

[00038] In another embodiment the present invention provides a composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, at least one in-mold coating adhesion compound, at least one substrate material, and at least one gel coat.

[00039] In another embodiment the present invention provides a composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, at least one in-mold coating adhesion compound, at least one substrate material, and at least one primer.

[00040] In another embodiment the present invention provides a composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, at least one in-mold coating adhesion compound, at least one substrate material, at least one paint, and optionally at least one primer.

[00041] In another embodiment the present invention provides a composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, at least one in-mold coating adhesion compound, at least one substrate material, at least one gel coat, and optionally at least one primer.

[00042] In another embodiment the present invention provides a method of in-mold coating a ROMP polymer composite comprising, providing a paint or a gel coat, applying the paint or the gel coat to a mold surface to form a painted or gel coated mold surface, contacting the painted or gel coated mold surface with a substrate material, and contacting the substrate material and the painted or gel coated mold surface with a resin composition, wherein the resin composition comprises at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound.

[00043] In another embodiment the present invention provides a method of in-mold coating a ROMP polymer composite comprising, providing a primer, applying the primer to a mold surface to form a primered mold surface, contacting the primered mold surface with a substrate material, and contacting the substrate material and the primered mold surface with a resin composition, wherein the resin composition comprises at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound.

[00044] In another embodiment the present invention provides a method of in-mold coating a ROMP polymer composite comprising, providing a paint or a gel coat, applying the paint or the gel coat to a mold surface to form a painted or gel coated mold surface, optionally providing an optional primer, optionally applying the optional primer to the painted or gel coated mold surface, contacting the painted or gel coated mold surface with a substrate material, and contacting the substrate material and the painted or gel coated mold surface with a resin composition, wherein the resin composition comprises at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound.

[00045] In another embodiment the present invention provides a method of in-mold coating a ROMP polymer composite comprising, providing a paint or a gel coat, applying the paint or the

gel coat to a mold surface to form a painted or gel coated mold surface, contacting the painted or gel coated mold surface with a tie coat, wherein the tie coat comprises a first resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound, contacting the tie coat with a substrate material, contacting the substrate material and the tie coat with a second resin composition, wherein the second resin composition comprises at least one cyclic olefin, at least one olefin metathesis catalyst, and optionally at least one in-mold coating adhesion compound.

[00046] In another embodiment the present invention provides a method of in-mold coating a ROMP polymer composite comprising, providing a primer, applying the primer to a mold surface to form a primered mold surface, contacting the primered mold surface with a tie coat, wherein the tie coat comprises a first resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound, contacting the tie coat with a substrate material, contacting the substrate material and the tie coat with a second resin composition, wherein the second resin composition comprises at least one cyclic olefin, at least one olefin metathesis catalyst, and optionally at least one in-mold coating adhesion compound.

[00047] In another embodiment the present invention provides a method of in-mold coating a ROMP polymer composite comprising, providing a paint or a gel coat, applying the paint or the gel coat to a mold surface to form a painted or gel coated mold surface, optionally providing an optional primer, optionally applying the optional primer to the painted or gel coated mold surface, contacting the painted or gel coated mold surface with a tie coat, wherein the tie coat comprises a first resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound, contacting the tie coat with a substrate material, contacting the substrate material and the tie coat with a second resin composition, wherein the second resin composition comprises at least one cyclic olefin, at least one olefin metathesis catalyst, and optionally at least one in-mold coating adhesion compound.

[00048] In another embodiment the present invention provides an article of manufacture comprising an in-mold coated ROMP polymer composite, wherein the in-mold coated ROMP polymer composite comprises a resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, at least one substrate material, and at least one in-mold coating adhesion compound.

[00049] In another embodiment the present invention provides a composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, at least one substrate material, and at least one in-mold coating adhesion compound.

[00050] These and other aspects of the present invention will be apparent to the skilled artisan in light of the following detailed description and examples.

[0050a] The invention provides a composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound, wherein the at least one in-mold coating adhesion compound is a compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin having the structure: $(O^M)-(Q^*)_n-(X^*)-H$ wherein: O^M is a metathesis active olefin fragment selected from cyclic olefins or acyclic olefins; Q^* is a linker group selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, substituted heteroatom-containing hydrocarbylene, or $-(CO)-$; n is zero or 1; and X^* is selected from oxygen, sulfur, or a heteroatom-containing fragment, wherein the heteroatom-containing fragment is selected from $N(R^X)$, $P(R^X)$, $OP(R^X)$, $OP(R^X)O$, $OP(OR^X)O$, $P(=O)(R^X)$, $OP(=O)(R^X)$, $OP(=O)(R^X)O$, $OP(=O)(OR^X)O$, $Si(R^X)_2$, $Si(R^X)_2O$, $Si(OR^X)_2O$, or $Si(R^X)(OR^X)O$, wherein each R^X is independently selected from hydrogen, hydrocarbyl, or substituted hydrocarbyl.

[0050b] The invention further provides a method of in-mold coating a ROMP polymer, comprising: providing a paint; applying the paint to a mold surface to form a painted mold surface; providing primer; applying the primer to the painted mold surface; contacting the painted and primed mold surface with a resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound; and subjecting the resin composition to conditions effective to polymerize the resin composition forming an in-mold coating ROMP polymer, wherein the at least one in-mold coating adhesion compound is a compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin having the structure: $(OM)-(Q^*)_n-(X^*)-H$ wherein: OM is a metathesis active olefin fragment selected from cyclic olefins or acyclic olefins; Q^* is a linker group selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, substituted heteroatom-containing hydrocarbylene, or $-(CO)-$; n is zero or 1; and X^* is selected from oxygen, sulfur, or a heteroatom-containing fragment, wherein the heteroatom-containing fragment is selected from $N(R^X)$, $P(R^X)$, $OP(R^X)$, $OP(R^X)O$, $OP(OR^X)O$, $P(=O)(R^X)$, $OP(=O)(R^X)$, $OP(=O)(R^X)O$, $OP(=O)(OR^X)O$, $Si(R^X)_2$, $Si(R^X)_2O$, $Si(OR^X)_2O$, or $Si(R^X)(OR^X)O$, wherein each R^X is independently selected from hydrogen, hydrocarbyl, or substituted hydrocarbyl.

[0050c] The invention further provides a method of in-mold coating a ROMP polymer, comprising: providing a primer; applying the primer to a mold surface to form a primed mold surface; contacting the primed mold surface with a resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound; and subjecting the resin composition

to conditions effective to polymerize the resin composition forming an in-mold coating ROMP polymer, wherein the at least one in-mold coating adhesion compound is a compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin having the structure: $(OM)-(Q^*)_n-(X^*)-H$ wherein: OM is a metathesis active olefin fragment selected from cyclic olefins or acyclic olefins; Q^* is a linker group selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, substituted heteroatom-containing hydrocarbylene, or $-(CO)-$; n is zero or 1; and X^* is selected from oxygen, sulfur, or a heteroatom-containing fragment, wherein the heteroatom-containing fragment is selected from $N(R^X)$, $P(R^X)$, $OP(R^X)$, $OP(R^X)O$, $OP(OR^X)O$, $P(=O)(R^X)$, $OP(=O)(R^X)$, $OP(=O)(R^X)O$, $OP(=O)(OR^X)O$, $Si(R^X)_2$, $Si(R^X)_2O$, $Si(OR^X)_2O$, or $Si(R^X)(OR^X)O$, wherein each R^X is independently selected from hydrogen, hydrocarbyl, or substituted hydrocarbyl.

[0050d] The invention further provides an article of manufacture comprising an in-mold coated ROMP polymer, where the in-mold coated ROMP polymer comprises a polymerized resin composition and an adherent coating thereon, where the polymerized resin composition comprises at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound; and the adherent coating comprises a paint, a primer, or combination thereof, wherein the at least one in-mold coating adhesion compound is a compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin having the structure: $(OM)-(Q^*)_n-(X^*)-H$, wherein: OM is a metathesis active olefin fragment selected from cyclic olefins or acyclic olefins; Q^* is a linker group selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, substituted heteroatom-containing hydrocarbylene, or $-(CO)-$; n is zero or 1; and X^* is selected from oxygen, sulfur, or a heteroatom-containing fragment, wherein the heteroatom-containing fragment is selected from $N(R^X)$, $P(R^X)$, $OP(R^X)$, $OP(R^X)O$, $OP(OR^X)O$, $P(=O)(R^X)$, $OP(=O)(R^X)$, $OP(=O)(R^X)O$, $OP(=O)(OR^X)O$, $Si(R^X)_2$, $Si(R^X)_2O$, $Si(OR^X)_2O$, or $Si(R^X)(OR^X)O$, wherein each R^X is independently selected from hydrogen, hydrocarbyl, or substituted hydrocarbyl.

[0050e] The invention further provides use of at least one in-mold coating adhesion compound for adhering a metathesis-polymerized resin composition to a paint, a primer, or a combination thereof, where the metathesis-polymerized resin composition comprises at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound, wherein the at least one in-mold coating adhesion compound is a compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin having the structure: $(OM)-(Q^*)_n-(X^*)-H$ wherein: OM is a metathesis active olefin fragment selected from cyclic olefins or acyclic olefins; Q^* is a linker group selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, substituted heteroatom-containing hydrocarbylene, or $-(CO)-$; n is zero or 1; and X^* is selected from oxygen, sulfur, or a heteroatom-containing fragment, wherein the heteroatom-containing fragment is selected from (R^X) , $P(R^X)$, $OP(R^X)$, $OP(R^X)O$, $OP(OR^X)O$, $P(=O)(R^X)$, $OP(=O)(R^X)$, $OP(=O)(R^X)O$, $OP(=O)(OR^X)O$, $Si(R^X)_2$, $Si(R^X)_2O$, $Si(OR^X)_2O$, or $Si(R^X)(OR^X)O$, wherein each R^X is independently selected from hydrogen, hydrocarbyl, or substituted hydrocarbyl.

DETAILED DESCRIPTION OF THE DISCLOSURE

Terminology and Definitions

[00051] Unless otherwise indicated, the invention is not limited to specific reactants, substituents, catalysts, catalyst compositions, resin compositions, reaction conditions, or the like, as such may vary. It is also to be understood that the terminology used herein is for the purpose of describing particular embodiments only and is not to be interpreted as being limiting.

[00052] As used in the specification and the appended claims, the singular forms “a,” “an,” and “the” include plural referents unless the context clearly dictates otherwise. Thus, for example, reference to “an α -olefin” includes a single α -olefin as well as a combination or mixture of two or more α -olefins, reference to “a substituent” encompasses a single substituent as well as two or more substituents, and the like.

[00053] As used in the specification and the appended claims, the terms “for example,” “for instance,” “such as,” or “including” are meant to introduce examples that further clarify more general subject matter. Unless otherwise specified, these examples are provided only as an aid for understanding the invention, and are not meant to be limiting in any fashion.

[00054] In this specification and in the claims that follow, reference will be made to a number of terms, which shall be defined to have the following meanings:

[00055] The term “alkyl” as used herein refers to a linear, branched, or cyclic saturated hydrocarbon group typically although not necessarily containing 1 to about 24 carbon atoms, preferably 1 to about 12 carbon atoms, such as methyl, ethyl, *n*-propyl, isopropyl, *n*-butyl, isobutyl, *t*-butyl, octyl, decyl, and the like, as well as cycloalkyl groups such as cyclopentyl, cyclohexyl, and the like. Generally, although again not necessarily, alkyl groups herein contain 1 to about 12 carbon atoms. The term “lower alkyl” refers to an alkyl group of 1 to 6 carbon atoms, and the specific term “cycloalkyl” refers to a cyclic alkyl group, typically having 4 to 8, preferably 5 to 7, carbon atoms. The term “substituted alkyl” refers to alkyl substituted with one or more substituent groups, and the terms “heteroatom-containing alkyl” and “heteroalkyl” refer to alkyl in which at least one carbon atom is replaced with a heteroatom. If not otherwise indicated, the terms “alkyl” and “lower alkyl” include linear, branched, cyclic, unsubstituted, substituted, and/or heteroatom-containing alkyl and lower alkyl, respectively.

[00056] The term “alkylene” as used herein refers to a difunctional linear, branched, or cyclic alkyl group, where “alkyl” is as defined above.

[00057] The term “alkenyl” as used herein refers to a linear, branched, or cyclic hydrocarbon group of 2 to about 24 carbon atoms containing at least one double bond, such as ethenyl, *n*-propenyl, isopropenyl, *n*-butenyl, isobutenyl, octenyl, decenyl, tetradecenyl, hexadecenyl, eicosenyl, tetracosenyl, and the like. Preferred alkenyl groups herein contain 2 to about 12 carbon atoms. The term “lower alkenyl” refers to an alkenyl group of 2 to 6 carbon atoms, and the specific term “cycloalkenyl” refers to a cyclic alkenyl group, preferably having 5 to 8 carbon atoms. The term “substituted alkenyl” refers to alkenyl substituted with one or more substituent groups, and the terms “heteroatom-containing alkenyl” and “heteroalkenyl” refer to alkenyl in which at least one carbon atom is replaced with a heteroatom. If not otherwise indicated, the terms “alkenyl” and “lower alkenyl” include linear, branched, cyclic, unsubstituted, substituted, and/or heteroatom-containing alkenyl and lower alkenyl, respectively.

[00058] The term “alkenylene” as used herein refers to a difunctional linear, branched, or cyclic alkenyl group, where “alkenyl” is as defined above.

[00059] The term “alkynyl” as used herein refers to a linear or branched hydrocarbon group of 2 to about 24 carbon atoms containing at least one triple bond, such as ethynyl, *n*-propynyl, and the like. Preferred alkynyl groups herein contain 2 to about 12 carbon atoms. The term “lower alkynyl” refers to an alkynyl group of 2 to 6 carbon atoms. The term “substituted alkynyl” refers to alkynyl substituted with one or more substituent groups, and the terms “heteroatom-containing alkynyl” and “heteroalkynyl” refer to alkynyl in which at least one carbon atom is replaced with a heteroatom. If not otherwise indicated, the terms “alkynyl” and “lower alkynyl” include linear, branched, unsubstituted, substituted, and/or heteroatom-containing alkynyl and lower alkynyl, respectively.

[00060] The term “alkoxy” as used herein refers to an alkyl group bound through a single, terminal ether linkage; that is, an “alkoxy” group may be represented as -O-alkyl where alkyl is as defined above. A “lower alkoxy” group refers to an alkoxy group containing 1 to 6 carbon atoms. Analogously, “alkenyloxy” and “lower alkenyloxy” respectively refer to an alkenyl and lower alkenyl group bound through a single, terminal ether linkage, and “alkynyloxy” and “lower alkynyloxy” respectively refer to an alkynyl and lower alkynyl group bound through a single, terminal ether linkage.

[00061] The term “aryl” as used herein, and unless otherwise specified, refers to an aromatic substituent containing a single aromatic ring or multiple aromatic rings that are fused together, directly linked, or indirectly linked (such that the different aromatic rings are bound to a common group such as a methylene or ethylene moiety). Preferred aryl groups contain 5 to 24 carbon atoms, and particularly preferred aryl groups contain 5 to 14 carbon atoms. Exemplary aryl groups contain one aromatic ring or two fused or linked aromatic rings, e.g., phenyl, naphthyl, biphenyl, diphenylether, diphenylamine,

benzophenone, and the like. "Substituted aryl" refers to an aryl moiety substituted with one or more substituent groups, and the terms "heteroatom-containing aryl" and "heteroaryl" refer to aryl substituents in which at least one carbon atom is replaced with a heteroatom, as will be described in further detail *infra*.

[00062] The term "aryloxy" as used herein refers to an aryl group bound through a single, terminal ether linkage, wherein "aryl" is as defined above. An "aryloxy" group may be represented as -O-aryl where aryl is as defined above. Preferred aryloxy groups contain 5 to 24 carbon atoms, and particularly preferred aryloxy groups contain 5 to 14 carbon atoms. Examples of aryloxy groups include, without limitation, phenoxy, o-halo-phenoxy, m-halo-phenoxy, p-halo-phenoxy, o-methoxy-phenoxy, m-methoxy-phenoxy, p-methoxy-phenoxy, 2,4-dimethoxy-phenoxy, 3,4,5-trimethoxy-phenoxy, and the like.

[00063] The term "alkaryl" refers to an aryl group with an alkyl substituent, and the term "aralkyl" refers to an alkyl group with an aryl substituent, wherein "aryl" and "alkyl" are as defined above. Preferred alkaryl and aralkyl groups contain 6 to 24 carbon atoms, and particularly preferred alkaryl and aralkyl groups contain 6 to 16 carbon atoms. Alkaryl groups include, without limitation, p-methylphenyl, 2,4-dimethylphenyl, p-cyclohexylphenyl, 2,7-dimethylnaphthyl, 7-cyclooctylnaphthyl, 3-ethylcyclopenta-1,4-diene, and the like. Examples of aralkyl groups include, without limitation, benzyl, 2-phenyl-ethyl, 3-phenyl-propyl, 4-phenyl-butyl, 5-phenyl-pentyl, 4-phenylcyclohexyl, 4-benzylcyclohexyl, 4-phenylcyclohexylmethyl, 4-benzylcyclohexylmethyl, and the like. The terms "alkaryloxy" and "aralkyloxy" refer to substituents of the formula -OR wherein R is alkaryl or aralkyl, respectively, as just defined.

[00064] The term "acyl" refers to substituents having the formula -(CO)-alkyl, -(CO)-aryl, -(CO)-aralkyl, -(CO)-alkaryl, -(CO)-alkenyl, or -(CO)-alkynyl, and the term "acyloxy" refers to substituents having the formula -O(CO)-alkyl, -O(CO)-aryl, -O(CO)-aralkyl, -O(CO)-alkaryl, -O(CO)-alkenyl, -O(CO)-alkynyl wherein "alkyl," "aryl," "aralkyl", alkaryl, alkenyl, and alkynyl are as defined above.

[00065] The terms "cyclic" and "ring" refer to alicyclic or aromatic groups that may or may not be substituted and/or heteroatom containing, and that may be monocyclic, bicyclic, or polycyclic. The term "alicyclic" is used in the conventional sense to refer to an aliphatic cyclic moiety, as opposed to an aromatic cyclic moiety, and may be monocyclic, bicyclic, or polycyclic.

[00066] The terms "halo" and "halogen" are used in the conventional sense to refer to a chloro, bromo, fluoro, or iodo substituent.

[00067] "Hydrocarbyl" refers to univalent hydrocarbyl radicals containing 1 to about 30 carbon atoms, preferably 1 to about 24 carbon atoms, most preferably 1 to about 12 carbon atoms, including linear, branched, cyclic, saturated, and unsaturated species, such as alkyl groups, alkenyl groups, alkynyl groups, aryl groups, and the like. The term "lower hydrocarbyl" intends a hydrocarbyl group of 1 to 6

carbon atoms, preferably 1 to 4 carbon atoms, and the term “hydrocarbylene” refers to a divalent hydrocarbyl moiety containing 1 to about 30 carbon atoms, preferably 1 to about 24 carbon atoms, most preferably 1 to about 12 carbon atoms, including linear, branched, cyclic, saturated, and unsaturated species. The term “lower hydrocarbylene” refers to a hydrocarbylene group of 1 to 6 carbon atoms. “Substituted hydrocarbyl” refers to hydrocarbyl substituted with one or more substituent groups, and the terms “heteroatom-containing hydrocarbyl” and “heterohydrocarbyl” refer to hydrocarbyl in which at least one carbon atom is replaced with a heteroatom. Similarly, “substituted hydrocarbylene” refers to hydrocarbylene substituted with one or more substituent groups, and the terms “heteroatom-containing hydrocarbylene” and “heterohydrocarbylene” refer to hydrocarbylene in which at least one carbon atom is replaced with a heteroatom. Unless otherwise indicated, the term “hydrocarbyl” and “hydrocarbylene” are to be interpreted as including substituted and/or heteroatom-containing hydrocarbyl and heteroatom-containing hydrocarbylene moieties, respectively.

[00068] The term “heteroatom-containing” as in a “heteroatom-containing hydrocarbyl group” refers to a hydrocarbon molecule or a hydrocarbyl molecular fragment in which one or more carbon atoms is replaced with an atom other than carbon, e.g., nitrogen, oxygen, sulfur, phosphorus, or silicon, typically nitrogen, oxygen, or sulfur. Similarly, the term “heteroalkyl” refers to an alkyl substituent that is heteroatom-containing, the term “heterocyclic” refers to a cyclic substituent that is heteroatom-containing, the terms “heteroaryl” and “heteroaromatic” respectively refer to “aryl” and “aromatic” substituents that are heteroatom-containing, and the like. It should be noted that a “heterocyclic” group or compound may or may not be aromatic, and further that “heterocycles” may be monocyclic, bicyclic, or polycyclic as described above with respect to the term “aryl.” Examples of heteroalkyl groups include without limitation alkoxyaryl, alkylsulfanyl-substituted alkyl, N-alkylated amino alkyl, and the like. Examples of heteroaryl substituents include without limitation pyrrolyl, pyrrolidinyl, pyridinyl, quinolinyl, indolyl, pyrimidinyl, imidazolyl, 1,2,4-triazolyl, tetrazolyl, etc., and examples of heteroatom-containing alicyclic groups include without limitation pyrrolidino, morpholino, piperazino, piperidino, etc.

[00069] By “substituted” as in “substituted hydrocarbyl,” “substituted alkyl,” “substituted aryl,” and the like, as alluded to in some of the aforementioned definitions, is meant that in the hydrocarbyl, alkyl, aryl, or other moiety, at least one hydrogen atom bound to a carbon (or other) atom is replaced with one or more non-hydrogen substituents. Examples of such substituents include, without limitation: functional groups referred to herein as “Fn,” such as halo, hydroxyl, sulfhydryl, C₁-C₂₄ alkoxy, C₂-C₂₄ alkenyloxy, C₂-C₂₄ alkynyloxy, C₅-C₂₄ aryloxy, C₆-C₂₄ aralkyloxy, C₆-C₂₄ alkaryloxy, acyl (including C₂-C₂₄ alkylcarbonyl (-CO-alkyl) and C₆-C₂₄ arylcarbonyl (-CO-aryl)), acyloxy (-O-acyl, including C₂-C₂₄ alkylcarbonyloxy (-O-CO-alkyl) and C₆-C₂₄ arylcarbonyloxy (-O-CO-aryl)), C₂-C₂₄ alkoxy carbonyl (-CO-O-alkyl), C₆-C₂₄ aryloxy carbonyl (-CO-O-aryl), halocarbonyl (-CO)-X where X is halo), C₂-C₂₄

alkylcarbonato (-O-(CO)-O-alkyl), C₆-C₂₄ arylcarbonato (-O-(CO)-O-aryl), carboxy (-COOH), carboxylato (-COO⁻), carbamoyl (-CO-NH₂), mono-(C₁-C₂₄ alkyl)-substituted carbamoyl (-CO-NH(C₁-C₂₄ alkyl)), di-(C₁-C₂₄ alkyl)-substituted carbamoyl (-CO-N(C₁-C₂₄ alkyl)₂), mono-(C₁-C₂₄ haloalkyl)-substituted carbamoyl (-CO-NH(C₁-C₂₄ haloalkyl)), di-(C₁-C₂₄ haloalkyl)-substituted carbamoyl (-CO-N(C₁-C₂₄ haloalkyl)₂), mono-(C₅-C₂₄ aryl)-substituted carbamoyl (-CO-NH-aryl), di-(C₅-C₂₄ aryl)-substituted carbamoyl (-CO-N(C₅-C₂₄ aryl)₂), di-N-(C₁-C₂₄ alkyl),N-(C₅-C₂₄ aryl)-substituted carbamoyl (-CO-N(C₁-C₂₄ alkyl)(C₅-C₂₄ aryl)), thiocarbamoyl (-CS-NH₂), mono-(C₁-C₂₄ alkyl)-substituted thiocarbamoyl (-CS-NH(C₁-C₂₄ alkyl)), di-(C₁-C₂₄ alkyl)-substituted thiocarbamoyl (-CS-N(C₁-C₂₄ alkyl)₂), mono-(C₅-C₂₄ aryl)-substituted thiocarbamoyl (-CS-NH-aryl), di-(C₅-C₂₄ aryl)-substituted thiocarbamoyl (-CS-N(C₅-C₂₄ aryl)₂), di-N-(C₁-C₂₄ alkyl), N-(C₅-C₂₄ aryl)-substituted thiocarbamoyl (-CS-N(C₁-C₂₄ alkyl)(C₅-C₂₄ aryl)), carbamido (-NH-(CO)-NH₂), cyano (-C≡N), cyanato (-O-C≡N), thiocyanato (-S-C≡N), isocyanate (-N=C=O), thioisocyanate (-N=C=S), formyl (-CO-H), thioformyl (-CS-H), amino (-NH₂), mono-(C₁-C₂₄ alkyl)-substituted amino (-NH(C₁-C₂₄ alkyl)), di-(C₁-C₂₄ alkyl)-substituted amino (-N(C₁-C₂₄ alkyl)₂), mono-(C₅-C₂₄ aryl)-substituted amino (-NH(C₅-C₂₄ aryl)), di-(C₅-C₂₄ aryl)-substituted amino (-N(C₅-C₂₄ aryl)₂), C₂-C₂₄ alkylamido (-NH-(CO)-alkyl), C₆-C₂₄ arylamido (-NH-(CO)-aryl), imino (-CR=NH where R includes without limitation hydrogen, C₁-C₂₄ alkyl, C₅-C₂₄ aryl, C₆-C₂₄ alkaryl, C₆-C₂₄ aralkyl, etc.), C₂-C₂₀ alkylimino (-CR=N(alkyl), where R includes without limitation hydrogen, C₁-C₂₄ alkyl, C₅-C₂₄ aryl, C₆-C₂₄ alkaryl, C₆-C₂₄ aralkyl, etc.), arylimino (-CR=N(aryl), where R includes without limitation hydrogen, C₁-C₂₀ alkyl, C₅-C₂₄ aryl, C₆-C₂₄ alkaryl, C₆-C₂₄ aralkyl, etc.), nitro (-NO₂), nitroso (-NO), sulfo (-SO₂-OH), sulfonato (-SO₂-O⁻), C₁-C₂₄ alkylsulfanyl (-S-alkyl; also termed "alkylthio"), C₅-C₂₄ arylsulfanyl (-S-aryl; also termed "arylthio"), C₁-C₂₄ alkylsulfanyl (-SO-alkyl), C₅-C₂₄ arylsulfanyl (-SO-aryl), C₁-C₂₄ alkylsulfonyl (-SO₂-alkyl), C₁-C₂₄ monoalkylaminosulfonyl (-SO₂-N(H) alkyl), C₁-C₂₄ dialkylaminosulfonyl (-SO₂-N(alkyl)₂), C₅-C₂₄ arylsulfonyl (-SO₂-aryl), boryl (-BH₂), borono (-B(OH)₂), boronato (-B(OR)₂ where R includes without limitation alkyl or other hydrocarbyl), phosphono (-P(O)(OH)₂), phosphonato (-P(O)(O⁻)₂), phosphinato (-P(O)(O⁻)), phospho (-PO₂), and phosphino (-PH₂); and the hydrocarbyl moieties C₁-C₂₄ alkyl (preferably C₁-C₁₂ alkyl, more preferably C₁-C₆ alkyl), C₂-C₂₄ alkenyl (preferably C₂-C₁₂ alkenyl, more preferably C₂-C₆ alkenyl), C₂-C₂₄ alkynyl (preferably C₂-C₁₂ alkynyl, more preferably C₂-C₆ alkynyl), C₅-C₂₄ aryl (preferably C₅-C₁₄ aryl), C₆-C₂₄ alkaryl (preferably C₆-C₁₆ alkaryl), and C₆-C₂₄ aralkyl (preferably C₆-C₁₆ aralkyl).

[00070] By "functionalized" as in "functionalized hydrocarbyl," "functionalized alkyl," "functionalized olefin," "functionalized cyclic olefin," and the like, is meant that in the hydrocarbyl, alkyl, olefin, cyclic olefin, or other moiety, at least one hydrogen atom bound to a carbon (or other) atom is replaced with one or more functional groups such as those described hereinabove. The term

“functional group” is meant to include any functional species that is suitable for the uses described herein. In particular, as used herein, a functional group would necessarily possess the ability to react with or bond to corresponding functional groups on a substrate surface.

[00071] In addition, the aforementioned functional groups may, if a particular group permits, be further substituted with one or more additional functional groups or with one or more hydrocarbyl moieties such as those specifically mentioned above. Analogously, the above-mentioned hydrocarbyl moieties may be further substituted with one or more functional groups or additional hydrocarbyl moieties as noted above.

[00072] “Optional” or “optionally” means that the subsequently described circumstance may or may not occur, so that the description includes instances where the circumstance occurs and instances where it does not. For example, the phrase “optionally substituted” means that a non-hydrogen substituent may or may not be present on a given atom, and, thus, the description includes structures wherein a non-hydrogen substituent is present and structures wherein a non-hydrogen substituent is not present.

[00073] The term “substrate material” as used herein, is intended to generally mean any material that the resin compositions of the invention or ROMP compositions (e.g., polymerizable compositions) of the invention may be contacted with, applied to, or have the substrate material incorporated in to the resin. Without limitation, such materials include reinforcing materials, such as filaments, fibers, rovings, mats, weaves, fabrics, knitted material, cloth or other known structures, glass fibers and fabrics, carbon fibers and fabrics, aramid fibers and fabrics, and polyolefin or other polymer fibers or fabrics. Other suitable substrate materials include metallic density modulators, microparticulate density modulators, such as microspheres, and macroparticulate density modulators, such as glass or ceramic beads.

[00074] As used in the specification and the appended claims, the terms “reactive formulation,” “polymerizable composition,” and “ROMP composition” have the same meaning and are used interchangeably herein.

[00075] In reference to the ROMP reaction of a resin composition comprising at least one cyclic olefin catalyzed by an olefin metathesis catalyst, the term “onset of a ROMP reaction” generally refers to the increase in the viscosity of the resin composition that occurs during polymerization just prior to gelation. The progress of an olefin metathesis polymerization can be cheaply and conveniently monitored by measuring the increase in viscosity as the reaction proceeds from the liquid monomer state to the gelled state. The progress of an olefin metathesis polymerization may also be cheaply and conveniently monitored by measuring the temperature increase as the metathesis reaction proceeds from the monomer to the cured state.

Cyclic Olefin

[00076] Resin compositions that may be used with the present invention disclosed herein comprise one or more cyclic olefins. In general, any cyclic olefin suitable for the metathesis reactions disclosed herein may be used. Such cyclic olefins may be optionally substituted, optionally heteroatom-containing, mono-unsaturated, di-unsaturated, or poly-unsaturated C₅ to C₂₄ hydrocarbons that may be mono-, di-, or poly-cyclic. The cyclic olefin may generally be any strained or unstrained cyclic olefin, provided the cyclic olefin is able to participate in a ROMP reaction either individually or as part of a ROMP cyclic olefin composition. While certain unstrained cyclic olefins such as cyclohexene are generally understood to not undergo ROMP reactions by themselves, under appropriate circumstances, such unstrained cyclic olefins may nonetheless be ROMP active. For example, when present as a co-monomer in a ROMP composition, unstrained cyclic olefins may be ROMP active. Accordingly, as used herein and as would be appreciated by the skilled artisan, the term “unstrained cyclic olefin” is intended to refer to those unstrained cyclic olefins that may undergo a ROMP reaction under any conditions, or in any ROMP composition, provided the unstrained cyclic olefin is ROMP active.

[00077] In general, the cyclic olefin may be represented by the structure of formula (A)




wherein J, R^{A1}, and R^{A2} are as follows:

R^{A1} and R^{A2} is selected independently from the group consisting of hydrogen, hydrocarbyl (e.g., C₁-C₂₀ alkyl, C₅-C₂₀ aryl, C₅-C₃₀ aralkyl, or C₅-C₃₀ alkaryl), substituted hydrocarbyl (e.g., substituted C₁-C₂₀ alkyl, C₅-C₂₀ aryl, C₅-C₃₀ aralkyl, or C₅-C₃₀ alkaryl), heteroatom-containing hydrocarbyl (e.g., C₁-C₂₀ heteroalkyl, C₅-C₂₀ heteroaryl, heteroatom-containing C₅-C₃₀ aralkyl, or heteroatom-containing C₅-C₃₀ alkaryl), and substituted heteroatom-containing hydrocarbyl (e.g., substituted C₁-C₂₀ heteroalkyl, C₅-C₂₀ heteroaryl, heteroatom-containing C₅-C₃₀ aralkyl, or heteroatom-containing C₅-C₃₀ alkaryl) and, if substituted hydrocarbyl or substituted heteroatom-containing hydrocarbyl, wherein the substituents may be functional groups (“Fn”) such as phosphonato, phosphoryl, phosphanyl, phosphino, sulfonato, C₁-C₂₀ alkylsulfanyl, C₅-C₂₀ arylsulfanyl, C₁-C₂₀ alkylsulfonyl, C₅-C₂₀ arylsulfonyl, C₁-C₂₀ alkylsulfinyl, C₅-C₂₀ arylsulfinyl, sulfonamido, amino, amido, imino, nitro, nitroso, hydroxyl, C₁-C₂₀ alkoxy, C₅-C₂₀ aryloxy, C₂-C₂₀ alkoxy-carbonyl, C₅-C₂₀ aryloxy-carbonyl, carboxyl, carboxylato, mercapto, formyl, C₁-C₂₀ thioester, cyano, cyanato, thiocyanato, isocyanate, thioisocyanate, carbamoyl, epoxy, styrenyl, silyl,

silyloxy, silanyl, siloxazanyl, boronato, boryl, or halogen, or a metal-containing or metalloid-containing group (wherein the metal may be, for example, Sn or Ge). R^{A1} and R^{A2} may itself be one of the aforementioned groups, such that the Fn moiety is directly bound to the olefinic carbon atom indicated in the structure. In the latter case, however, the functional group will generally not be directly bound to the olefinic carbon through a heteroatom containing one or more lone pairs of electrons, e.g., an oxygen, sulfur, nitrogen, or phosphorus atom, or through an electron-rich metal or metalloid such as Ge, Sn, As, Sb, Se, Te, etc. With such functional groups, there will normally be an intervening linkage Z^* , such that R^{A1} and/or R^{A2} then has the structure $-(Z^*)_n$ -Fn wherein n is 1, Fn is the functional group, and Z^* is a hydrocarbylene linking group such as an alkylene, substituted alkylene, heteroalkylene, substituted heteroalkene, arylene, substituted arylene, heteroarylene, or substituted heteroarylene linkage.

J is a saturated or unsaturated hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, or substituted heteroatom-containing hydrocarbylene linkage, wherein when J is substituted hydrocarbylene or substituted heteroatom-containing hydrocarbylene, the substituents may include one or more $-(Z^*)_n$ -Fn groups, wherein n is zero or 1, and Fn and Z^* are as defined previously. Additionally, two or more substituents attached to ring carbon (or other) atoms within J may be linked to form a bicyclic or polycyclic olefin. J will generally contain in the range of approximately 5 to 14 ring atoms, typically 5 to 8 ring atoms, for a monocyclic olefin, and, for bicyclic and polycyclic olefins, each ring will generally contain 4 to 8, typically 5 to 7, ring atoms.

[00078] Mono-unsaturated cyclic olefins encompassed by structure (A) may be represented by the structure (B)




wherein b is an integer generally although not necessarily in the range of 1 to 10, typically 1 to 5, R^{A1} and R^{A2} are as defined above for structure (A), and R^{B1} , R^{B2} , R^{B3} , R^{B4} , R^{B5} , and R^{B6} are independently selected from the group consisting of hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, substituted heteroatom-containing hydrocarbyl and $-(Z^*)_n$ -Fn where n, Z^* and Fn are as defined previously, and wherein if any of the R^{B1} through R^{B6} moieties is substituted hydrocarbyl or substituted heteroatom-containing hydrocarbyl, the substituents may include one or more $-(Z^*)_n$ -Fn groups. Accordingly, R^{B1} , R^{B2} , R^{B3} , R^{B4} , R^{B5} , and R^{B6} may be, for example, hydrogen, hydroxyl, C_1 - C_{20}

alkyl, C₅-C₂₀ aryl, C₁-C₂₀ alkoxy, C₅-C₂₀ aryloxy, C₂-C₂₀ alkoxy carbonyl, C₅-C₂₀ aryloxy carbonyl, amino, amido, nitro, etc. Furthermore, any of the R^{B1}, R^{B2}, R^{B3}, R^{B4}, R^{B5}, and R^{B6} moieties can be linked to any of the other R^{B1}, R^{B2}, R^{B3}, R^{B4}, R^{B5}, and R^{B6} moieties to provide a substituted or unsubstituted alicyclic group containing 4 to 30 ring carbon atoms or a substituted or unsubstituted aryl group containing 6 to 18 ring carbon atoms or combinations thereof and the linkage may include heteroatoms or functional groups, e.g., the linkage may include without limitation an ether, ester, thioether, amino, alkylamino, imino, or anhydride moiety. The alicyclic group can be monocyclic, bicyclic, or polycyclic. When unsaturated the cyclic group can contain monounsaturations or multiunsaturations, with monounsaturated cyclic groups being preferred. When substituted, the rings contain monosubstitution or multisubstitution wherein the substituents are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, substituted heteroatom-containing hydrocarbyl, $-(Z^*)_n$ -Fn where n is zero or 1, Z* and Fn are as defined previously, and functional groups (Fn) provided above.

[00079] Examples of monounsaturated, monocyclic olefins encompassed by structure (B) include, without limitation, cyclopentene, cyclohexene, cycloheptene, cyclooctene, cyclononene, cyclodecene, cycloundecene, cyclododecene, tricyclodecene, tetracyclodecene, octacyclodecene, and cycloeicosene, and substituted versions thereof such as 1-methylcyclopentene, 1-ethylcyclopentene, 1-isopropylcyclohexene, 1-chloropentene, 1-fluorocyclopentene, 4-methylcyclopentene, 4-methoxycyclopentene, 4-ethoxycyclopentene, cyclopent-3-ene-thiol, cyclopent-3-ene, 4-methylsulfanyl-cyclopentene, 3-methylcyclohexene, 1-methylcyclooctene, 1,5-dimethylcyclooctene, etc.

[00080] Monocyclic diene reactants encompassed by structure (A) may be generally represented by the structure (C)



wherein c and d are independently integers in the range of 1 to about 8, typically 2 to 4, preferably 2 (such that the reactant is a cyclooctadiene), R^{A1} and R^{A2} are as defined above for structure (A), and R^{C1}, R^{C2}, R^{C3}, R^{C4}, R^{C5}, and R^{C6} are defined as for R^{B1} through R^{B6}. In this case, it is preferred that R^{C3} and R^{C4} be non-hydrogen substituents, in which case the second olefinic moiety is tetrasubstituted. Examples of monocyclic diene reactants include, without limitation, 1,3-cyclopentadiene, 1,3-cyclohexadiene, 1,4-cyclohexadiene, 5-ethyl-1,3-cyclohexadiene,

1,3-cycloheptadiene, cyclohexadiene, 1,5-cyclooctadiene, 1,3-cyclooctadiene, and substituted analogs thereof. Triene reactants are analogous to the diene structure (C), and will generally contain at least one methylene linkage between any two olefinic segments.


[00081] Bicyclic and polycyclic olefins encompassed by structure (A) may be generally represented by the structure (D)



wherein R^{A1} and R^{A2} are as defined above for structure (A), R^{D1} , R^{D2} , R^{D3} , and R^{D4} are as defined for R^{B1} through R^{B6} , e is an integer in the range of 1 to 8 (typically 2 to 4) f is generally 1 or 2; T is lower alkylene or alkenylene (generally substituted or unsubstituted methyl or ethyl), CHR^{G1} , $C(R^{G1})_2$, O , S , N , R^{G1} , P , R^{G1} , $O=P$, R^{G1} , $Si(R^{G1})_2$, B , R^{G1} , or As , R^{G1} where R^{G1} is alkyl, alkenyl, cycloalkyl, cycloalkenyl, aryl, alkaryl, aralkyl, or alkoxy. Furthermore, any of the R^{D1} , R^{D2} , R^{D3} , and R^{D4} moieties can be linked to any of the other R^{D1} , R^{D2} , R^{D3} , and R^{D4} moieties to provide a substituted or unsubstituted alicyclic group containing 4 to 30 ring carbon atoms or a substituted or unsubstituted aryl group containing 6 to 18 ring carbon atoms or combinations thereof and the linkage may include heteroatoms or functional groups, e.g., the linkage may include without limitation an ether, ester, thioether, amino, alkylamino, imino, or anhydride moiety. The cyclic group can be monocyclic, bicyclic, or polycyclic. When unsaturated the cyclic group can contain monounsaturations or multiunsaturations, with monounsaturated cyclic groups being preferred. When substituted, the rings contain monosubstitution or multisubstitution wherein the substituents are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, substituted heteroatom-containing hydrocarbyl, $-(Z^*)_n$ -Fn where n is zero or 1, Z^* and Fn are as defined previously, and functional groups (Fn) provided above.

[00082] Cyclic olefins encompassed by structure (D) are in the norbornene family. As used herein, norbornene means any compound that includes at least one norbornene or substituted norbornene moiety, including without limitation norbornene, substituted norbornene(s), norbornadiene, substituted norbornadiene(s), polycyclic norbornenes, and substituted polycyclic norbornene(s). Norbornenes within this group may be generally represented by the structure (E)

(E)




wherein R^{A1} and R^{A2} are as defined above for structure (A), T is as defined above for structure (D), R^{E1} , R^{E2} , R^{E3} , R^{E4} , R^{E5} , R^{E6} , R^{E7} , and R^{E8} are as defined for R^{B1} through R^{B6} , and “a” represents a single bond or a double bond, f is generally 1 or 2, “g” is an integer from 0 to 5, and when “a” is a double bond one of R^{E5} , R^{E6} and one of R^{E7} , R^{E8} is not present.

[00083] Furthermore, any of the R^{E5} , R^{E6} , R^{E7} , and R^{E8} moieties can be linked to any of the other R^{E5} , R^{E6} , R^{E7} , and R^{E8} moieties to provide a substituted or unsubstituted alicyclic group containing 4 to 30 ring carbon atoms or a substituted or unsubstituted aryl group containing 6 to 18 ring carbon atoms or combinations thereof and the linkage may include heteroatoms or functional groups, e.g., the linkage may include without limitation an ether, ester, thioether, amino, alkylamino, imino, or anhydride moiety. The cyclic group can be monocyclic, bicyclic, or polycyclic. When unsaturated the cyclic group can contain monounsaturations or multiunsaturations, with monounsaturated cyclic groups being preferred. When substituted, the rings contain monosubstitution or multisubstitution wherein the substituents are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, substituted heteroatom-containing hydrocarbyl, $-(Z^*)_n-Fn$ where n is zero or 1, Z^* and Fn are as defined previously, and functional groups (Fn) provided above.

[00084] More preferred cyclic olefins possessing at least one norbornene moiety have the structure (F):

(F)




wherein R^{F1} , R^{F2} , R^{F3} , and R^{F4} , are as defined for R^{B1} through R^{B6} , and “a” represents a single bond or a double bond, “g” is an integer from 0 to 5, and when “a” is a double bond one of R^{F1} , R^{F2} and one of R^{F3} , R^{F4} is not present.

[00085] Furthermore, any of the R^{F1} , R^{F2} , R^{F3} , and R^{F4} moieties can be linked to any of the other R^{F1} , R^{F2} , R^{F3} , and R^{F4} moieties to provide a substituted or unsubstituted alicyclic group containing 4 to 30 ring carbon atoms or a substituted or unsubstituted aryl group containing 6 to 18 ring carbon atoms or combinations thereof and the linkage may include heteroatoms or functional groups, e.g., the linkage may include without limitation an ether, ester, thioether, amino, alkylamino, imino, or anhydride moiety. The alicyclic group can be monocyclic, bicyclic, or polycyclic. When unsaturated the cyclic group can contain monounsaturations or multiunsaturations, with monounsaturated cyclic groups being preferred. When substituted, the rings contain monosubstitution or multisubstitution wherein the substituents are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, substituted heteroatom-containing hydrocarbyl, $-(Z^*)_n-F_n$ where n is zero or 1, Z^* and F_n are as defined previously, and functional groups (F_n) provided above.

[00086] One route for the preparation of hydrocarbyl substituted and functionally substituted norbornenes employs the Diels-Alder cycloaddition reaction in which cyclopentadiene or substituted cyclopentadiene is reacted with a suitable dienophile at elevated temperatures to form the substituted norbornene adduct generally shown by the following reaction Scheme 1:


SCHEME 1



wherein R^{F1} to R^{F4} are as previously defined for structure (F).

[00087] Other norbornene adducts can be prepared by the thermal pyrolysis of dicyclopentadiene in the presence of a suitable dienophile. The reaction proceeds by the initial pyrolysis of dicyclopentadiene to cyclopentadiene followed by the Diels-Alder cycloaddition of cyclopentadiene and the dienophile to give the adduct shown below in Scheme 2:


SCHEME 2



wherein "g" is an integer from 0 to 5, and R^{F1} to R^{F4} are as previously defined for structure (F).

[00088] Norbornadiene and higher Diels-Alder adducts thereof similarly can be prepared by the thermal reaction of cyclopentadiene and dicyclopentadiene in the presence of an acetylenic reactant as shown below in Scheme 3:

SCHEME 3



wherein "g" is an integer from 0 to 5, R^{F1} and R^{F4} are as previously defined for structure (F).

[00089] Examples of bicyclic and polycyclic olefins thus include, without limitation, dicyclopentadiene (DCPD); trimer and other higher order oligomers of cyclopentadiene including without limitation tricyclopentadiene (cyclopentadiene trimer), cyclopentadiene tetramer, and cyclopentadiene pentamer; ethylenenorbornene; dicyclohexadiene; norbornene; 5-methyl-2-norbornene; 5-ethyl-2-norbornene; 5-isobutyl-2-norbornene; 5,6-dimethyl-2-norbornene; 5-phenylnorbornene; 5-benzylnorbornene; 5-acetylnorbornene; 5-methoxycarbonylnorbornene; 5-ethoxycarbonyl-1-norbornene; 5-methyl-5-methoxy-carbonylnorbornene; 5-cyanonorbornene; 5,5,6-trimethyl-2-norbornene; cyclo-hexenylnorbornene; endo, exo-5,6-dimethoxynorbornene; endo, endo-5,6-

dimethoxynorbornene; endo, exo-5,6-dimethoxycarbonylnorbornene; endo,endo-5,6-dimethoxycarbonylnorbornene; 2,3-dimethoxynorbornene; norbornadiene; tricycloundecene; tetracyclododecene; 8-methyltetracyclododecene; 8-ethyltetracyclododecene; 8-methoxycarbonyltetracyclododecene; 8-methyl-8-tetracyclododecene; 8-cyanotetracyclododecene; pentacyclopentadecene; pentacyclohexadecene; and the like, and their structural isomers, stereoisomers, and mixtures thereof. Additional examples of bicyclic and polycyclic olefins include, without limitation, C₂-C₁₂ hydrocarbyl substituted norbornenes such as 5-butyl-2-norbornene, 5-hexyl-2-norbornene, 5-octyl-2-norbornene, 5-decyl-2-norbornene, 5-dodecyl-2-norbornene, 5-vinyl-2-norbornene, 5-ethylidene-2-norbornene, 5-isopropenyl-2-norbornene, 5-propenyl-2-norbornene, and 5-butenyl-2-norbornene, and the like.

[00090] Preferred cyclic olefins include C₅ to C₂₄ unsaturated hydrocarbons. Also preferred are C₅ to C₂₄ cyclic hydrocarbons that contain one or more (typically 2 to 12) heteroatoms such as O, N, S, or P. For example, crown ether cyclic olefins may include numerous O heteroatoms throughout the cycle, and these are within the scope of the invention. In addition, preferred cyclic olefins are C₅ to C₂₄ hydrocarbons that contain one or more (typically 2 or 3) olefins. For example, the cyclic olefin may be mono-, di-, or tri-unsaturated. Examples of cyclic olefins include without limitation cyclooctene, cyclododecene, and (c,t,t)-1,5,9-cyclododecatiene.

[00091] The cyclic olefins may also comprise multiple (typically 2 or 3) rings. For example, the cyclic olefin may be mono-, di-, or tri-cyclic. When the cyclic olefin comprises more than one ring, the rings may or may not be fused. Preferred examples of cyclic olefins that comprise multiple rings include norbornene, dicyclopentadiene, tricyclopentadiene, and 5-ethylidene-2-norbornene.

[00092] The cyclic olefin may also be substituted, for example, a C₅ to C₂₄ cyclic hydrocarbon wherein one or more (typically 2, 3, 4, or 5) of the hydrogens are replaced with non-hydrogen substituents. Suitable non-hydrogen substituents may be chosen from the substituents described hereinabove. For example, functionalized cyclic olefins, i.e., C₅ to C₂₄ cyclic hydrocarbons wherein one or more (typically 2, 3, 4, or 5) of the hydrogens are replaced with functional groups, are within the scope of the invention. Suitable functional groups may be chosen from the functional groups described hereinabove. For example, a cyclic olefin functionalized with an alcohol group may be used to prepare a telechelic polymer comprising pendent alcohol groups. Functional groups on the cyclic olefin may be protected in cases where the functional group interferes with the metathesis catalyst, and any of the protecting groups commonly used in the art may be employed. Acceptable protecting groups may be found, for example, in Greene et al., *Protective Groups in Organic Synthesis*, 3rd Ed. (New York: Wiley, 1999). Examples of functionalized cyclic olefins include without limitation 2-hydroxymethyl-5-

norbornene, 2-[(2-hydroxyethyl)carboxylate]-5-norbornene, cydecanol, 5-n-hexyl-2-norbornene, 5-n-butyl-2-norbornene.

[00093] Cyclic olefins incorporating any combination of the abovementioned features (i.e., heteroatoms, substituents, multiple olefins, multiple rings) are suitable for the methods disclosed herein. Additionally, cyclic olefins incorporating any combination of the abovementioned features (i.e., heteroatoms, substituents, multiple olefins, multiple rings) are suitable for the invention disclosed herein.

[00094] The cyclic olefins useful in the methods disclosed herein may be strained or unstrained. It will be appreciated that the amount of ring strain varies for each cyclic olefin compound, and depends upon a number of factors including the size of the ring, the presence and identity of substituents, and the presence of multiple rings. Ring strain is one factor in determining the reactivity of a molecule towards ring-opening olefin metathesis reactions. Highly strained cyclic olefins, such as certain bicyclic compounds, readily undergo ring opening reactions with olefin metathesis catalysts. Less strained cyclic olefins, such as certain unsubstituted hydrocarbon monocyclic olefins, are generally less reactive. In some cases, ring opening reactions of relatively unstrained (and therefore relatively unreactive) cyclic olefins may become possible when performed in the presence of the olefinic compounds disclosed herein. Additionally, cyclic olefins useful in the invention disclosed herein may be strained or unstrained.

[00095] The resin compositions of the present invention may comprise a plurality of cyclic olefins. A plurality of cyclic olefins may be used to prepare metathesis polymers from the olefinic compound. For example, two cyclic olefins selected from the cyclic olefins described hereinabove may be employed in order to form metathesis products that incorporate both cyclic olefins. Where two or more cyclic olefins are used, one example of a second cyclic olefin is a cyclic alkenol, i.e., a C₅-C₂₄ cyclic hydrocarbon wherein at least one of the hydrogen substituents is replaced with an alcohol or protected alcohol moiety to yield a functionalized cyclic olefin.


[00096] The use of a plurality of cyclic olefins, and in particular when at least one of the cyclic olefins is functionalized, allows for further control over the positioning of functional groups within the products. For example, the density of cross-linking points can be controlled in polymers and macromonomers prepared using the methods disclosed herein. Control over the quantity and density of substituents and functional groups also allows for control over the physical properties (e.g., melting point, tensile strength, glass transition temperature, etc.) of the products. Control over these and other properties is possible for reactions using only a single cyclic olefin, but it will be appreciated that the use of a plurality of cyclic olefins further enhances the range of possible metathesis products and polymers formed.

[00097] More preferred cyclic olefins include dicyclopentadiene; tricyclopentadiene; dicyclohexadiene; norbornene; 5-methyl-2-norbornene; 5-ethyl-2-norbornene; 5-isobutyl-2-norbornene; 5,6-dimethyl-2-norbornene; 5-phenylnorbornene; 5-benzylnorbornene; 5-acetylnorbornene;

5-methoxycarbonylnorbornene; 5-ethoxycarbonyl-1-norbornene; 5-methyl-5-methoxy-carbonylnorbornene; 5-cyanonorbornene; 5,5,6-trimethyl-2-norbornene; cyclo-hexenylnorbornene; endo, exo-5,6-dimethoxynorbornene; endo, endo-5,6-dimethoxynorbornene; endo, exo-5-6-dimethoxycarbonylnorbornene; endo, endo-5,6-dimethoxycarbonylnorbornene; 2,3-dimethoxynorbornene; norbornadiene; tricycloundecene; tetracyclododecene; 8-methyltetracyclododecene; 8-ethyl-tetracyclododecene; 8-methoxycarbonyltetracyclododecene; 8-methyl-8-tetracyclo-dodecene; 8-cyanotetracyclododecene; pentacyclopentadecene; pentacyclohexadecene; higher order oligomers of cyclopentadiene such as cyclopentadiene tetramer, cyclopentadiene pentamer, and the like; and C₂-C₁₂ hydrocarbyl substituted norbornenes such as 5-butyl-2-norbornene; 5-hexyl-2-norbornene; 5-octyl-2-norbornene; 5-decyl-2-norbornene; 5-dodecyl-2-norbornene; 5-vinyl-2-norbornene; 5-ethylidene-2-norbornene; 5-isopropenyl-2-norbornene; 5-propenyl-2-norbornene; and 5-butenyl-2-norbornene, and the like. Even more preferred cyclic olefins include dicyclopentadiene, tricyclopentadiene, and higher order oligomers of cyclopentadiene, such as cyclopentadiene tetramer, cyclopentadiene pentamer, and the like, tetracyclododecene, norbornene, and C₂-C₁₂ hydrocarbyl substituted norbornenes, such as 5-butyl-2-norbornene, 5-hexyl-2-norbornene, 5-octyl-2-norbornene, 5-decyl-2-norbornene, 5-dodecyl-2-norbornene, 5-vinyl-2-norbornene, 5-ethylidene-2-norbornene, 5-isopropenyl-2-norbornene, 5-propenyl-2-norbornene, 5-butenyl-2-norbornene, and the like.

Olefin Metathesis Catalysts

[00098] An olefin metathesis catalyst that may be used in the invention disclosed herein, is preferably a Group 8 transition metal complex having the structure of formula (I)



in which:

M is a Group 8 transition metal;

L¹, L², and L³ are neutral electron donor ligands;

n is 0 or 1, such that L³ may or may not be present;

m is 0, 1, or 2;

k is 0 or 1;

X^1 and X^2 are anionic ligands; and

R^1 and R^2 are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, substituted heteroatom-containing hydrocarbyl, and functional groups,

wherein any two or more of X^1 , X^2 , L^1 , L^2 , L^3 , R^1 , and R^2 can be taken together to form one or more cyclic groups, and further wherein any one or more of X^1 , X^2 , L^1 , L^2 , L^3 , R^1 , and R^2 may be attached to a support.

[00099] Additionally, in formula (I), one or both of R^1 and R^2 may have the structure $-(W)_n-U^+V^-$, in which W is selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, or substituted heteroatom-containing hydrocarbylene; U is a positively charged Group 15 or Group 16 element substituted with hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, or substituted heteroatom-containing hydrocarbyl; V is a negatively charged counterion; and n is zero or 1. Furthermore, R^1 and R^2 may be taken together to form an indenylidene moiety.

[000100] Preferred catalysts contain Ru or Os as the Group 8 transition metal, with Ru particularly preferred.

[000101] Numerous embodiments of the catalysts useful in the reactions disclosed herein are described in more detail *infra*. For the sake of convenience, the catalysts are described in groups, but it should be emphasized that these groups are not meant to be limiting in any way. That is, any of the catalysts useful in the invention may fit the description of more than one of the groups described herein.

[000102] A first group of catalysts, then, are commonly referred to as First Generation Grubbs-type catalysts, and have the structure of formula (I). For the first group of catalysts, M is a Group 8 transition metal, m is 0, 1, or 2, and n, X^1 , X^2 , L^1 , L^2 , L^3 , R^1 , and R^2 are described as follows.

[000103] For the first group of catalysts, n is 0, and L^1 and L^2 are independently selected from phosphine, sulfonated phosphine, phosphite, phosphinite, phosphonite, arsine, stibine, ether, (including cyclic ethers), amine, amide, imine, sulfoxide, carboxyl, nitrosyl, pyridine, substituted pyridine, imidazole, substituted imidazole, pyrazine, substituted pyrazine and thioether. Exemplary ligands are trisubstituted phosphines. Preferred trisubstituted phosphines are of the formula $PR^{H1}R^{H2}R^{H3}$, where R^{H1} , R^{H2} , and R^{H3} are each independently substituted or unsubstituted aryl or C_1 - C_{10} alkyl, particularly primary alkyl, secondary alkyl, or cycloalkyl. In the most preferred, L^1 and L^2 are independently selected from the group consisting of trimethylphosphine (PMc_3), triethylphosphine (PEt_3), tri-n-butylphosphine (PBu_3), tri(ortho-tolyl)phosphine (P -o-tolyl $_3$), tri-tert-butylphosphine (P -tert-Bu $_3$), tricyclopentylphosphine ($PCyclopentyl_3$), tricyclohexylphosphine (PCy_3), triisopropylphosphine (P -i-Pr $_3$), trioctylphosphine (P Oct $_3$), triisobutylphosphine, (P -i-Bu $_3$), triphenylphosphine (PPh_3), tri(pentafluorophenyl)phosphine

($P(C_6F_5)_3$), methyldiphenylphosphine ($PMePh_2$), dimethyldiphenylphosphine (PM_e_2Ph), and diethyldiphenylphosphine (PEt_2Ph). Alternatively, L^1 and L^2 may be independently selected from phosphabicycloalkane (e.g., monosubstituted 9-phosphabicyclo-[3.3.1]nonane, or monosubstituted 9-phosphabicyclo[4.2.1]nonane) such as cyclohexylphoban, isopropylphoban, ethylphoban, methylphoban, butylphoban, pentylphoban and the like).

[000104] X^1 and X^2 are anionic ligands, and may be the same or different, or are linked together to form a cyclic group, typically although not necessarily a five- to eight-membered ring. In preferred embodiments, X^1 and X^2 are each independently hydrogen, halide, or one of the following groups: C_1 - C_{20} alkyl, C_5 - C_{24} aryl, C_1 - C_{20} alkoxy, C_5 - C_{24} aryloxy, C_2 - C_{20} alkoxy carbonyl, C_6 - C_{24} aryloxy carbonyl, C_2 - C_{24} acyl, C_2 - C_{24} acyloxy, C_1 - C_{20} alkylsulfonate, C_5 - C_{24} arylsulfonate, C_1 - C_{20} alkylsulfanyl, C_5 - C_{24} arylsulfanyl, C_1 - C_{20} alkylsulfinyl, NO_3 , $-N=C=O$, $-N=C=S$, or C_5 - C_{24} arylsulfinyl. Optionally, X^1 and X^2 may be substituted with one or more moieties selected from C_1 - C_{12} alkyl, C_1 - C_{12} alkoxy, C_5 - C_{24} aryl, and halide, which may, in turn, with the exception of halide, be further substituted with one or more groups selected from halide, C_1 - C_6 alkyl, C_1 - C_6 alkoxy, and phenyl. In more preferred embodiments, X^1 and X^2 are halide, benzoate, C_2 - C_6 acyl, C_2 - C_6 alkoxy carbonyl, C_1 - C_6 alkyl, phenoxy, C_1 - C_6 alkoxy, C_1 - C_6 alkylsulfanyl, aryl, or C_1 - C_6 alkylsulfonyl. In even more preferred embodiments, X^1 and X^2 are each halide, CF_3CO_2 , CH_3CO_2 , CFH_2CO_2 , $(CH_3)_3CO$, $(CF_3)_2(CH_3)CO$, $(CF_3)(CH_3)_2CO$, PhO , MeO , EtO , tosylate, mesylate, or trifluoromethane-sulfonate. In the most preferred embodiments, X^1 and X^2 are each chloride.


[000105] R^1 and R^2 are independently selected from hydrogen, hydrocarbyl (e.g., C_1 - C_{20} alkyl, C_2 - C_{20} alkenyl, C_2 - C_{20} alkynyl, C_5 - C_{24} aryl, C_6 - C_{24} alkaryl, C_6 - C_{24} aralkyl, etc.), substituted hydrocarbyl (e.g., substituted C_1 - C_{20} alkyl, C_2 - C_{20} alkenyl, C_2 - C_{20} alkynyl, C_5 - C_{24} aryl, C_6 - C_{24} alkaryl, C_6 - C_{24} aralkyl, etc.), heteroatom-containing hydrocarbyl (e.g., heteroatom-containing C_1 - C_{20} alkyl, C_2 - C_{20} alkenyl, C_2 - C_{20} alkynyl, C_5 - C_{24} aryl, C_6 - C_{24} alkaryl, C_6 - C_{24} aralkyl, etc.), and substituted heteroatom-containing hydrocarbyl (e.g., substituted heteroatom-containing C_1 - C_{20} alkyl, C_2 - C_{20} alkenyl, C_2 - C_{20} alkynyl, C_5 - C_{24} aryl, C_6 - C_{24} alkaryl, C_6 - C_{24} aralkyl, etc.), and functional groups. R^1 and R^2 may also be linked to form a cyclic group, which may be aliphatic or aromatic, and may contain substituents and/or heteroatoms. Generally, such a cyclic group will contain 4 to 12, preferably 5, 6, 7, or 8 ring atoms.

[000106] In preferred catalysts, R^1 is hydrogen and R^2 is selected from C_1 - C_{20} alkyl, C_2 - C_{20} alkenyl, and C_5 - C_{24} aryl, more preferably C_1 - C_6 alkyl, C_2 - C_6 alkenyl, and C_5 - C_{14} aryl. Still more preferably, R^2 is phenyl, vinyl, methyl, isopropyl, or t-butyl, optionally substituted with one or more moieties selected from C_1 - C_6 alkyl, C_1 - C_6 alkoxy, phenyl, and a functional group F_n as defined earlier herein. Most preferably, R^2 is phenyl or vinyl substituted with one or more moieties selected from methyl, ethyl,


chloro, bromo, iodo, fluoro, nitro, dimethylamino, methyl, methoxy, and phenyl. Optimally, R² is phenyl or -CH=C(CH₃)₂.

[000107] Any two or more (typically two, three, or four) of X¹, X², L¹, L², L³, R¹, and R² can be taken together to form a cyclic group, including bidentate or multidentate ligands, as disclosed, for example, in U.S. Patent No. 5,312,940. When any of X¹, X², L¹, L², L³, R¹, and R² are linked to form cyclic groups, those cyclic groups may contain 4 to 12, preferably 4, 5, 6, 7, or 8 atoms, or may comprise two or three of such rings, which may be either fused or linked. The cyclic groups may be aliphatic or aromatic, and may be heteroatom-containing and/or substituted. The cyclic group may, in some cases, form a bidentate ligand or a tridentate ligand. Examples of bidentate ligands include, but are not limited to, bisphosphines, dialkoxides, alkyldiketonates, and aryldiketonates.

[000108] A second group of catalysts, commonly referred to as Second Generation Grubbs-type catalysts, have the structure of formula (I), wherein L¹ is a carbene ligand having the structure of formula (II)



such that the complex may have the structure of formula (III)



wherein M, m, n, X¹, X², L², L³, R¹, and R² are as defined for the first group of catalysts, and the remaining substituents are as follows;

X and Y are heteroatoms typically selected from N, O, S, and P. Since O and S are divalent, p is necessarily zero when X is O or S, q is necessarily zero when Y is O or S, and k is zero or 1. However,

when X is N or P, then p is 1, and when Y is N or P, then q is 1. In a preferred embodiment, both X and Y are N;

Q^1 , Q^2 , Q^3 , and Q^4 are linkers, e.g., hydrocarbylene (including substituted hydrocarbylene, heteroatom-containing hydrocarbylene, and substituted heteroatom-containing hydrocarbylene, such as substituted and/or heteroatom-containing alkylene) or $-(CO)-$, and w, x, y, and z are independently zero or 1, meaning that each linker is optional. Preferably, w, x, y, and z are all zero. Further, two or more substituents on adjacent atoms within Q^1 , Q^2 , Q^3 , and Q^4 may be linked to form an additional cyclic group; and


R^3 , R^{3A} , R^4 , and R^{4A} are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, and substituted heteroatom-containing hydrocarbyl. In addition, X and Y may be independently selected from carbon and one of the heteroatoms mentioned above, preferably no more than one of X or Y is carbon. Also, L^2 and L^3 may be taken together to form a single bidentate electron-donating heterocyclic ligand. Furthermore, R^1 and R^2 may be taken together to form an indenylidene moiety. Moreover, X^1 , X^2 , L^2 , L^3 , X, and Y may be further coordinated to boron or to a carboxylate.

[000109] In addition, any two or more of X^1 , X^2 , L^1 , L^2 , L^3 , R^1 , R^2 , R^3 , R^{3A} , R^4 , R^{4A} , Q^1 , Q^2 , Q^3 , and Q^4 can be taken together to form a cyclic group, and any one or more of X^1 , X^2 , L^2 , L^3 , Q^1 , Q^2 , Q^3 , Q^4 , R^1 , R^2 , R^3 , R^{3A} , R^4 , and R^{4A} may be attached to a support. Any two or more of X^1 , X^2 , L^1 , L^2 , L^3 , R^1 , R^2 , R^3 , R^{3A} , R^4 , and R^{4A} can also be taken to be $-A-Fn$, wherein "A" is a divalent hydrocarbon moiety selected from alkylene and arylalkylene, wherein the alkyl portion of the alkylene and arylalkylene groups can be linear or branched, saturated or unsaturated, cyclic or acyclic, and substituted or unsubstituted, wherein the aryl portion of the of arylalkylene can be substituted or unsubstituted, and wherein hetero atoms and/or functional groups may be present in either the aryl or the alkyl portions of the alkylene and arylalkylene groups, and Fn is a functional group, or together to form a cyclic group, and any one or more of X^1 , X^2 , L^2 , L^3 , Q^1 , Q^2 , Q^3 , Q^4 , R^1 , R^2 , R^3 , R^{3A} , R^4 , and R^{4A} may be attached to a support.

[000110] A particular class of carbene ligands having the structure of formula (II), where R^{3A} and R^{4A} are linked to form a cyclic group and at least one of X or Y is a nitrogen, or at least one of Q^3 or Q^4 is a heteroatom-containing hydrocarbylene or substituted heteroatom-containing hydrocarbylene, where at least one heteroatom is a nitrogen, are commonly referred to as N-heterocyclic carbene (NHC) ligands.


[000111] Preferably, R^{3A} and R^{4A} are linked to form a cyclic group so that the carbene ligand has the structure of formula (IV)


(IV)




wherein R^3 and R^4 are as defined for the second group of catalysts above, with preferably at least one of R^3 and R^4 , and more preferably both R^3 and R^4 , being alicyclic or aromatic of one to about five rings, and optionally containing one or more heteroatoms and/or substituents. Q is a linker, typically a hydrocarbylene linker, including substituted hydrocarbylene, heteroatom-containing hydrocarbylene, and substituted heteroatom-containing hydrocarbylene linkers, wherein two or more substituents on adjacent atoms within Q may also be linked to form an additional cyclic structure, which may be similarly substituted to provide a fused polycyclic structure of two to about five cyclic groups. Q is often, although not necessarily, a two-atom linkage or a three-atom linkage.

[000112] Examples of N-heterocyclic carbene (NHC) ligands and acyclic diaminocarbene ligands suitable as L^1 thus include, but are not limited to, the following where DIPP or DiPP is diisopropylphenyl and Mes is 2,4,6-trimethylphenyl:





[000113] Additional examples of N-heterocyclic carbene (NHC) ligands and acyclic diaminocarbene ligands suitable as L^1 thus include, but are not limited to the following:




wherein R^{W1} , R^{W2} , R^{W3} , R^{W4} are independently hydrogen, unsubstituted hydrocarbyl, substituted hydrocarbyl, or heteroatom containing hydrocarbyl, and where one or both of R^{W3} and R^{W4} may be independently selected from halogen, nitro, amido, carboxyl, alkoxy, aryloxy, sulfonyl, carbonyl, thio, or nitroso groups.

[000114] Additional examples of N-heterocyclic carbene (NHC) ligands suitable as L^1 are further described in U.S. Pat. Nos. 7,378,528; 7,652,145; 7,294,717; 6,787,620; 6,635,768; and 6,552,139.

[000115] Additionally, thermally activated N-Heterocyclic Carbene Precursors as disclosed in U.S. Pat. No. 6,838,489, may also be used with the present invention.

[000116] When M is ruthenium, then, the preferred complexes have the structure of formula (V)

(V)



[000117] In a more preferred embodiment, Q is a two-atom linkage having the structure $-CR^{11}R^{12}-$, $CR^{13}R^{14}-$ or $-CR^{11}=CR^{13}-$, preferably $-CR^{11}R^{12}-CR^{13}R^{14}-$, wherein R^{11} , R^{12} , R^{13} , and R^{14} are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, substituted heteroatom-containing hydrocarbyl, and functional groups. Examples of functional groups here include without limitation carboxyl, C_1 - C_{20} alkoxy, C_5 - C_{24} aryloxy, C_2 - C_{20} alkoxy carbonyl, C_5 - C_{24} alkoxy carbonyl, C_2 - C_{24} acyloxy, C_1 - C_{20} alkylthio, C_5 - C_{24} arylthio, C_1 - C_{20} alkylsulfonyl, and C_1 - C_{20} alkylsulfinyl, optionally substituted with one or more moieties selected from C_1 - C_{12} alkyl, C_1 - C_{12} alkoxy, C_5 - C_{14} aryl, hydroxyl, sulfhydryl, formyl, and halide. R^{11} , R^{12} , R^{13} , and R^{14} are preferably independently selected from hydrogen, C_1 - C_{12} alkyl, substituted C_1 - C_{12} alkyl, C_1 - C_{12} heteroalkyl, substituted C_1 - C_{12} heteroalkyl, phenyl, and substituted phenyl. Alternatively, any two of R^{11} , R^{12} , R^{13} , and R^{14} may be linked together to form a substituted or unsubstituted, saturated or unsaturated ring structure, e.g., a C_4 - C_{12} alicyclic group or a C_5 or C_6 aryl group, which may itself be substituted, e.g., with linked or fused alicyclic or aromatic groups, or with other substituents. In one further aspect, any one or more of R^{11} , R^{12} , R^{13} , and R^{14} comprises one or more of the linkers. Additionally, R^3 and R^4 may be unsubstituted phenyl or phenyl substituted with one or more substituents selected from C_1 - C_{20} alkyl, substituted C_1 - C_{20} alkyl, C_1 - C_{20} heteroalkyl, substituted C_1 - C_{20} heteroalkyl, C_5 - C_{24} aryl, substituted C_5 - C_{24} aryl, C_5 - C_{24} heteroaryl, C_6 - C_{24} aralkyl, C_6 - C_{24} alkaryl, or halide. Furthermore, X^1 and X^2 may be halogen.

[000118] When R^3 and R^4 are aromatic, they are typically although not necessarily composed of one or two aromatic rings, which may or may not be substituted, e.g., R^3 and R^4 may be phenyl, substituted phenyl, biphenyl, substituted biphenyl, or the like. In one preferred embodiment, R^3 and R^4 are the same and are each unsubstituted phenyl or phenyl substituted with up to three substituents selected from C_1 - C_{20} alkyl, substituted C_1 - C_{20} alkyl, C_1 - C_{20} heteroalkyl, substituted C_1 - C_{20} heteroalkyl, C_5 - C_{24} aryl, substituted C_5 - C_{24} aryl, C_5 - C_{24} heteroaryl, C_6 - C_{24} aralkyl, C_6 - C_{24} alkaryl, or halide. Preferably, any substituents

present are hydrogen, C₁-C₁₂ alkyl, C₁-C₁₂ alkoxy, C₅-C₁₄ aryl, substituted C₅-C₁₄ aryl, or halide. As an example, R³ and R⁴ are mesityl (i.e., Mes as defined herein).

[000119] In a third group of catalysts having the structure of formula (I), M, m, n, X¹, X², R¹, and R² are as defined for the first group of catalysts, L¹ is a strongly coordinating neutral electron donor ligand such as any of those described for the first and second group of catalysts, and L² and L³ are weakly coordinating neutral electron donor ligands in the form of optionally substituted heterocyclic groups. Again, n is zero or 1, such that L³ may or may not be present. Generally, in the third group of catalysts, L² and L³ are optionally substituted five- or six-membered monocyclic groups containing 1 to 4, preferably 1 to 3, most preferably 1 to 2 heteroatoms, or are optionally substituted bicyclic or polycyclic structures composed of 2 to 5 such five- or six-membered monocyclic groups. If the heterocyclic group is substituted, it should not be substituted on a coordinating heteroatom, and any one cyclic moiety within a heterocyclic group will generally not be substituted with more than 3 substituents.

[000120] For the third group of catalysts, examples of L² and L³ include, without limitation, heterocycles containing nitrogen, sulfur, oxygen, or a mixture thereof.

[000121] Examples of nitrogen-containing heterocycles appropriate for L² and L³ include pyridine, bipyridine, pyridazine, pyrimidine, bipyridamine, pyrazine, 1,3,5-triazine, 1,2,4-triazine, 1,2,3-triazine, pyrrole, 2H-pyrrole, 3H-pyrrole, pyrazole, 2H-imidazole, 1,2,3-triazole, 1,2,4-triazole, indole, 3H-indole, 1H-isoindole, cyclopenta(b)pyridine, indazole, quinoline, bisquinoline, isoquinoline, bisisoquinoline, cinnoline, quinazoline, naphthyridine, piperidine, piperazine, pyrrolidine, pyrazolidine, quinuclidine, imidazolidine, picolyimine, purine, benzimidazole, bisimidazole, phenazine, acridine, and carbazole. Additionally, the nitrogen-containing heterocycles may be optionally substituted on a non-coordinating heteroatom with a non-hydrogen substituent.

[000122] Examples of sulfur-containing heterocycles appropriate for L² and L³ include thiophene, 1,2-dithiole, 1,3-dithiole, thiepin, benzo(b)thiophene, benzo(c)thiophene, thionaphthene, dibenzothiophene, 2H-thiopyran, 4H-thiopyran, and thioanthrene.

[000123] Examples of oxygen-containing heterocycles appropriate for L² and L³ include 2H-pyran, 4H-pyran, 2-pyrone, 4-pyrone, 1,2-dioxin, 1,3-dioxin, oxepin, furan, 2H-1-benzopyran, coumarin, coumarone, chromene, chroman-4-one, isochromen-1-one, isochromen-3-one, xanthene, tetrahydrofuran, 1,4-dioxan, and dibenzofuran.

[000124] Examples of mixed heterocycles appropriate for L² and L³ include isoxazole, oxazole, thiazole, isothiazole, 1,2,3-oxadiazole, 1,2,4-oxadiazole, 1,3,4-oxadiazole, 1,2,3,4-oxatriazole, 1,2,3,5-oxatriazole, 3H-1,2,3-dioxazole, 3H-1,2-oxathiole, 1,3-oxathiole, 4H-1,2-oxazine, 2H-1,3-oxazine, 1,4-oxazine, 1,2,5-oxathiazine, o-isooxazine, phenoxazine, phenothiazine, pyrano[3,4-b]pyrrole, indoxazine, benzoxazole, anthranil, and morpholine.

[000125] Preferred L^2 and L^3 ligands are aromatic nitrogen-containing and oxygen-containing heterocycles, and particularly preferred L^2 and L^3 ligands are monocyclic N-heteroaryl ligands that are optionally substituted with 1 to 3, preferably 1 or 2, substituents. Specific examples of particularly preferred L^2 and L^3 ligands are pyridine and substituted pyridines, such as 3-bromopyridine, 4-bromopyridine, 3,5-dibromopyridine, 2,4,6-tribromopyridine, 2,6-dibromopyridine, 3-chloropyridine, 4-chloropyridine, 3,5-dichloropyridine, 2,4,6-trichloropyridine, 2,6-dichloropyridine, 4-iodopyridine, 3,5-diiodopyridine, 3,5-dibromo-4-methylpyridine, 3,5-dichloro-4-methylpyridine, 3,5-dimethyl-4-bromopyridine, 3,5-dimethylpyridine, 4-methylpyridine, 3,5-diisopropylpyridine, 2,4,6-trimethylpyridine, 2,4,6-triisopropylpyridine, 4-(*tert*-butyl)pyridine, 4-phenylpyridine, 3,5-diphenylpyridine, 3,5-dichloro-4-phenylpyridine, and the like.


[000126] In general, any substituents present on L^2 and/or L^3 are selected from halo, C_1 - C_{20} alkyl, substituted C_1 - C_{20} alkyl, C_1 - C_{20} heteroalkyl, substituted C_1 - C_{20} heteroalkyl, C_5 - C_{24} aryl, substituted C_5 - C_{24} aryl, C_5 - C_{24} heteroaryl, substituted C_5 - C_{24} heteroaryl, C_6 - C_{24} alkaryl, substituted C_6 - C_{24} alkaryl, C_6 - C_{24} heteroalkaryl, substituted C_6 - C_{24} heteroalkaryl, C_6 - C_{24} aralkyl, substituted C_6 - C_{24} aralkyl, C_6 - C_{24} heteroaralkyl, substituted C_6 - C_{24} heteroaralkyl, and functional groups, with suitable functional groups including, without limitation, C_1 - C_{20} alkoxy, C_5 - C_{24} aryloxy, C_2 - C_{20} alkylcarbonyl, C_6 - C_{24} arylcarbonyl, C_2 - C_{20} alkylcarbonyloxy, C_6 - C_{24} arylcarbonyloxy, C_2 - C_{20} alkoxycarbonyl, C_6 - C_{24} aryloxycarbonyl, halocarbonyl, C_2 - C_{20} alkylcarbonato, C_6 - C_{24} arylcarbonato, carboxy, carboxylato, carbamoyl, mono-(C_1 - C_{20} alkyl)-substituted carbamoyl, di-(C_1 - C_{20} alkyl)-substituted carbamoyl, di-N-(C_1 - C_{20} alkyl), N-(C_5 - C_{24} aryl)-substituted carbamoyl, mono-(C_5 - C_{24} aryl)-substituted carbamoyl, di-(C_6 - C_{24} aryl)-substituted carbamoyl, thiocarbamoyl, mono-(C_1 - C_{20} alkyl)-substituted thiocarbamoyl, di-(C_1 - C_{20} alkyl)-substituted thiocarbamoyl, di-N-(C_1 - C_{20} alkyl)-N-(C_6 - C_{24} aryl)-substituted thiocarbamoyl, mono-(C_6 - C_{24} aryl)-substituted thiocarbamoyl, di-(C_6 - C_{24} aryl)-substituted thiocarbamoyl, carbamido, formyl, thioformyl, amino, mono-(C_1 - C_{20} alkyl)-substituted amino, di-(C_1 - C_{20} alkyl)-substituted amino, mono-(C_5 - C_{24} aryl)-substituted amino, di-(C_5 - C_{24} aryl)-substituted amino, di-N-(C_1 - C_{20} alkyl), N-(C_5 - C_{24} aryl)-substituted amino, C_2 - C_{20} alkylamido, C_6 - C_{24} arylamido, imino, C_1 - C_{20} alkylimino, C_5 - C_{24} arylimino, nitro, and nitroso. In addition, two adjacent substituents may be taken together to form a ring, generally a five- or six-membered alicyclic or aryl ring, optionally containing 1 to 3 heteroatoms and 1 to 3 substituents as above.

[000127] Preferred substituents on L^2 and L^3 include, without limitation, halo, C_1 - C_{12} alkyl, substituted C_1 - C_{12} alkyl, C_1 - C_{12} heteroalkyl, substituted C_1 - C_{12} heteroalkyl, C_5 - C_{14} aryl, substituted C_5 - C_{14} aryl, C_5 - C_{14} heteroaryl, substituted C_5 - C_{14} heteroaryl, C_6 - C_{16} alkaryl, substituted C_6 - C_{16} alkaryl, C_6 - C_{16} heteroalkaryl, substituted C_6 - C_{16} heteroalkaryl, C_6 - C_{16} aralkyl, substituted C_6 - C_{16} aralkyl, C_6 - C_{16} heteroaralkyl, substituted C_6 - C_{16} heteroaralkyl, C_1 - C_{12} alkoxy, C_5 - C_{14} aryloxy, C_2 - C_{12} alkylcarbonyl, C_6 -

C₁₄ arylcarbonyl, C₂-C₁₂ alkylcarbonyloxy, C₆-C₁₄ arylcarbonyloxy, C₂-C₁₂ alkoxy carbonyl, C₆-C₁₄ aryloxy carbonyl, halocarbonyl, formyl, amino, mono-(C₁-C₁₂ alkyl)-substituted amino, di-(C₁-C₁₂ alkyl)-substituted amino, mono-(C₅-C₁₄ aryl)-substituted amino, di-(C₅-C₁₄ aryl)-substituted amino, and nitro.

[000128] Of the foregoing, the most preferred substituents are halo, C₁-C₆ alkyl, C₁-C₆ haloalkyl, C₁-C₆ alkoxy, phenyl, substituted phenyl, formyl, N,N-di(C₁-C₆ alkyl)amino, nitro, and nitrogen heterocycles as described above (including, for example, pyrrolidine, piperidine, piperazine, pyrazine, pyrimidine, pyridine, pyridazine, etc.).

[000129] In certain embodiments, L² and L³ may also be taken together to form a bidentate or multidentate ligand containing two or more, generally two, coordinating heteroatoms such as N, O, S, or P, with preferred such ligands being diimine ligands of the Brookhart type. One representative bidentate ligand has the structure of formula (VI)




wherein R¹⁵, R¹⁶, R¹⁷, and R¹⁸ hydrocarbyl (e.g., C₁-C₂₀ alkyl, C₂-C₂₀ alkenyl, C₂-C₂₀ alkynyl, C₅-C₂₄ aryl, C₆-C₂₄ alkaryl, or C₆-C₂₄ aralkyl), substituted hydrocarbyl (e.g., substituted C₁-C₂₀ alkyl, C₂-C₂₀ alkenyl, C₂-C₂₀ alkynyl, C₅-C₂₄ aryl, C₆-C₂₄ alkaryl, or C₆-C₂₄ aralkyl), heteroatom-containing hydrocarbyl (e.g., C₁-C₂₀ heteroalkyl, C₅-C₂₄ heteroaryl, heteroatom-containing C₆-C₂₄ aralkyl, or heteroatom-containing C₆-C₂₄ alkaryl), or substituted heteroatom-containing hydrocarbyl (e.g., substituted C₁-C₂₀ heteroalkyl, C₅-C₂₄ heteroaryl, heteroatom-containing C₆-C₂₄ aralkyl, or heteroatom-containing C₆-C₂₄ alkaryl), or (1) R¹⁵ and R¹⁶, (2) R¹⁷ and R¹⁸, (3) R¹⁶ and R¹⁷, or (4) both R¹⁵ and R¹⁶, and R¹⁷ and R¹⁸, may be taken together to form a ring, i.e., an N-heterocycle. Preferred cyclic groups in such a case are five- and six-membered rings, typically aromatic rings.

[000130] In a fourth group of catalysts that have the structure of formula (I), two of the substituents are taken together to form a bidentate ligand or a tridentate ligand. Examples of bidentate ligands include, but are not limited to, bisphosphines, dialkoxides, alkylidiketones, and arylidiketones. Specific examples include -P(Ph)₂CH₂CH₂P(Ph)₂-, -As(Ph)₂CH₂CH₂As(Ph)₂-, -P(Ph)₂CH₂CH₂C(CF₃)₂O-, binaphtholate dianions, pinacolate dianions, -P(CH₃)₂(CH₂)₂P(CH₃)₂-, and -OC(CH₃)₂(CH₃)₂CO-. Preferred bidentate ligands are -P(Ph)₂CH₂CH₂P(Ph)₂- and -P(CH₃)₂(CH₂)₂P(CH₃)₂-. Tridentate ligands include, but are not limited to, (CH₃)₂NCH₂CH₂P(Ph)CH₂CH₂N(CH₃)₂. Other preferred tridentate ligands are those in which any three of X¹, X², L¹, L², L³, R¹, and R² (e.g., X¹, L¹, and L²) are taken together to be cyclopentadienyl, indenyl, or fluorenyl, each optionally substituted with C₂-C₂₀ alkenyl, C₂-C₂₀ alkynyl,

C₁-C₂₀ alkyl, C₅-C₂₀ aryl, C₁-C₂₀ alkoxy, C₂-C₂₀ alkenyloxy, C₂-C₂₀ alkynyloxy, C₅-C₂₀ aryloxy, C₂-C₂₀ alkoxy carbonyl, C₁-C₂₀ alkylthio, C₁-C₂₀ alkylsulfonyl, or C₁-C₂₀ alkylsulfinyl, each of which may be further substituted with C₁-C₆ alkyl, halide, C₁-C₆ alkoxy or with a phenyl group optionally substituted with halide, C₁-C₆ alkyl, or C₁-C₆ alkoxy. More preferably, in compounds of this type, X, L¹, and L² are taken together to be cyclopentadienyl or indenyl, each optionally substituted with vinyl, C₁-C₁₀ alkyl, C₅-C₂₀ aryl, C₁-C₁₀ carboxylate, C₂-C₁₀ alkoxy carbonyl, C₁-C₁₀ alkoxy, or C₅-C₂₀ aryloxy, each optionally substituted with C₁-C₆ alkyl, halide, C₁-C₆ alkoxy or with a phenyl group optionally substituted with halide, C₁-C₆ alkyl or C₁-C₆ alkoxy. Most preferably, X, L¹, and L² may be taken together to be cyclopentadienyl, optionally substituted with vinyl, hydrogen, methyl, or phenyl. Tetradentate ligands include, but are not limited to O₂C(CH₂)₂P(Ph)(CH₂)₂P(Ph)(CH₂)₂CO₂, phthalocyanines, and porphyrins.

[000131] Complexes wherein Y is coordinated to the metal are examples of a fifth group of catalysts, and are commonly called “Grubbs-Hoveyda” catalysts. Grubbs-Hoveyda metathesis-active metal carbene complexes may be described by the formula (VII)



wherein,

M is a Group 8 transition metal, particularly Ru or Os, or, more particularly, Ru;

X¹, X², and L¹ are as previously defined herein for the first and second groups of catalysts;

Y is a heteroatom selected from N, O, S, and P; preferably Y is O or N;


R⁵, R⁶, R⁷, and R⁸ are each, independently, selected from the group consisting of hydrogen, halogen, alkyl, alkenyl, alkynyl, aryl, heteroalkyl, heteroatom containing alkenyl, heteroalkenyl, heteroaryl, alkoxy, alkenyloxy, aryloxy, alkoxy carbonyl, carbonyl, alkylamino, alkylthio, aminosulfonyl, monoalkylaminosulfonyl, dialkylaminosulfonyl, alkylsulfonyl, nitrile, nitro, alkylsulfinyl, trihaloalkyl, perfluoroalkyl, carboxylic acid, ketone, aldehyde, nitrate, cyano, isocyanate, hydroxyl, ester, ether, amine, imine, amide, halogen-substituted amide, trifluoroamide, sulfide, disulfide, sulfonate, carbamate, silane,

siloxane, phosphine, phosphate, borate, or $-A-Fn$, wherein "A" and Fn have been defined above; and any combination of Y, Z, R^5 , R^6 , R^7 , and R^8 can be linked to form one or more cyclic groups;

n is 0, 1, or 2, such that n is 1 for the divalent heteroatoms O or S, and n is 2 for the trivalent heteroatoms N or P; and


Z is a group selected from hydrogen, alkyl, aryl, functionalized alkyl, functionalized aryl where the functional group(s) may independently be one or more of the following: alkoxy, aryloxy, halogen, carboxylic acid, ketone, aldehyde, nitrate, cyano, isocyanate, hydroxyl, ester, ether, amine, imine, amide, trifluoroamide, sulfide, disulfide, carbamate, silane, siloxane, phosphine, phosphate, or borate; methyl, isopropyl, sec-butyl, t-butyl, neopentyl, benzyl, phenyl and trimethylsilyl; and wherein any combination or combinations of X^1 , X^2 , L^1 , Y, Z, R^5 , R^6 , R^7 , and R^8 may be linked to a support. Additionally, R^5 , R^6 , R^7 , R^8 , and Z may independently be thioisocyanate, cyanato, or thiocyanato.

[000132] Examples of complexes comprising Grubbs-Hoveyda ligands suitable in the invention include:




wherein, L^1 , X^1 , X^2 , and M are as described for any of the other groups of catalysts. Suitable chelating carbenes and carbene precursors are further described by Pederson et al. (U.S. Pat. Nos. 7,026,495 and 6,620,955) and Hoveyda et al. (U.S. Pat. No. 6,921,735 and WO 02/14376).

[000133] Other useful complexes include structures wherein L^2 and R^2 according to formulae (I), (III), or (V) are linked, such as styrenic compounds that also include a functional group for attachment to a support. Examples in which the functional group is a trialkoxysilyl functionalized moiety include, but are not limited to, the following:



[000134] Further examples of complexes having linked ligands include those having linkages between a neutral NHC ligand and an anionic ligand, a neutral NHC ligand and an alkylidene ligand, a neutral NHC ligand and an L^2 ligand, a neutral NHC ligand and an L^3 ligand, an anionic ligand and an alkylidene ligand, and any combination thereof. While the possible structures are too numerous to list herein, some suitable structures based on formula (III) include:







[000135] In addition to the catalysts that have the structure of formula (I), as described above, other transition metal carbene complexes include, but are not limited to:

neutral ruthenium or osmium metal carbene complexes containing metal centers that are formally in the +2 oxidation state, have an electron count of 16, are penta-coordinated, and are of the general formula (IX);

neutral ruthenium or osmium metal carbene complexes containing metal centers that are formally in the +2 oxidation state, have an electron count of 18, are hexa-coordinated, and are of the general formula (X);

cationic ruthenium or osmium metal carbene complexes containing metal centers that are formally in the +2 oxidation state, have an electron count of 14, are tetra-coordinated, and are of the general formula (XI); and

cationic ruthenium or osmium metal carbene complexes containing metal centers that are formally in the +2 oxidation state, have an electron count of 14 or 16, are tetra-coordinated or penta-coordinated, respectively, and are of the general formula (XII)



wherein:

M, X¹, X², L¹, L², L³, R¹, and R² are as defined for any of the previously defined four groups of catalysts;

r and s are independently zero or 1;

t is an integer in the range of zero to 5;

k is an integer in the range of zero to 1;

Y is any non-coordinating anion (e.g., a halide ion, BF₄⁻, etc.);


Z¹ and Z² are independently selected from -O-, -S-, -NR²⁻-, -PR²⁻-, -P(=O)R²⁻-, -P(OR²⁻)-, -P(=O)(OR²⁻)-, -C(=O)-, -C(=O)O-, -OC(=O)-, -OC(=O)O-, -S(=O)-, -S(=O)₂-, -, and an optionally substituted and/or optionally heteroatom-containing C₁-C₂₀ hydrocarbylene linkage;

Z³ is any cationic moiety such as -P(R²⁺)₃⁺ or -N(R²⁺)₃⁺; and

any two or more of X¹, X², L¹, L², L³, Z¹, Z², Z³, R¹, and R² may be taken together to form a cyclic group, e.g., a multidentate ligand, and wherein any one or more of X¹, X², L¹, L², L³, Z¹, Z², Z³, R¹, and R² may be attached to a support.

[000136] Additionally, another group of olefin metathesis catalysts that may be used in the invention disclosed herein, is a Group 8 transition metal complex having the structure of formula (XIII):

(XIII)




wherein M is a Group 8 transition metal, particularly ruthenium or osmium, or more particularly, ruthenium;

X¹, X², L¹, and L² are as defined for the first and second groups of catalysts defined above; and

R^{G1}, R^{G2}, R^{G3}, R^{G4}, R^{G5}, and R^{G6} are each independently selected from the group consisting of hydrogen, halogen, alkyl, alkenyl, alkynyl, aryl, heteroalkyl, heteroatom containing alkenyl, heteroalkenyl, heteroaryl, alkoxy, alkenyloxy, aryloxy, alkoxycarbonyl, carbonyl, alkylamino, alkylthio, aminosulfonyl, monoalkylaminosulfonyl, dialkylaminosulfonyl, alkylsulfonyl, nitrile, nitro, alkylsulfinyl, trihaloalkyl, perfluoroalkyl, carboxylic acid, ketone, aldehyde, nitrate, cyano, isocyanate, thioisocyanate, cyanato, thiocyanato, hydroxyl, ester, ether, thioether, amine, alkylamine, imine, amide, halogen-

substituted amide, trifluoroamide, sulfide, disulfide, sulfonate, carbamate, silane, siloxane, phosphine, phosphate, borate, or $-A-Fn$, wherein "A" is a divalent hydrocarbon moiety selected from alkylene and arylalkylene, wherein the alkyl portion of the alkylene and arylalkylene groups can be linear or branched, saturated or unsaturated, cyclic or acyclic, and substituted or unsubstituted, wherein the aryl portion of the arylalkylene can be substituted or unsubstituted, and wherein hetero atoms and/or functional groups may be present in either the aryl or the alkyl portions of the alkylene and arylalkylene groups, and F_n is a functional group, or any one or more of the R^{G1} , R^{G2} , R^{G3} , R^{G4} , R^{G5} , and R^{G6} may be linked together to form a cyclic group, or any one or more of the R^{G1} , R^{G2} , R^{G3} , R^{G4} , R^{G5} , and R^{G6} may be attached to a support.

[000137] Additionally, one preferred embodiment of the Group 8 transition metal complex of formula XIII is a Group 8 transition metal complex of formula (XIV):




wherein M, X¹, X², L¹, and L² are as defined above for Group 8 transition metal complex of formula XIII; and

R^{G7}, R^{G8}, R^{G9}, R^{G10}, R^{G11}, R^{G12}, R^{G13}, R^{G14}, R^{G15}, and R^{G16} are as defined above for R^{G1}, R^{G2}, R^{G3}, R^{G4}, R^{G5}, and R^{G6} for Group 8 transition metal complex of formula XIII or any one or more of the R^{G7}, R^{G8}, R^{G9}, R^{G10}, R^{G11}, R^{G12}, R^{G13}, R^{G14}, R^{G15}, and R^{G16} may be linked together to form a cyclic group, or any one or more of the R^{G7}, R^{G8}, R^{G9}, R^{G10}, R^{G11}, R^{G12}, R^{G13}, R^{G14}, R^{G15}, and R^{G16} may be attached to a support.

[000138] Additionally, another preferred embodiment of the Group 8 transition metal complex of formula XIII is a Group 8 transition metal complex of formula (XV):


(XV)



wherein M, X¹, X², L¹ and L² are as defined above for Group 8 transition metal complex of formula XIII.

[000139] Additionally, another group of olefin metathesis catalysts that may be used in the invention disclosed herein, is a Group 8 transition metal complex comprising a Schiff base ligand having the structure of formula (XVI):

(XVI)



wherein M is a Group 8 transition metal, particularly ruthenium or osmium, or more particularly, ruthenium;


X¹ and L¹ are as defined for the first and second groups of catalysts defined above;

Z is selected from the group consisting of oxygen, sulfur, selenium, NR^{J11}, PR^{J11}, AsR^{J11}, and SbR^{J11}; and

R^{J1}, R^{J2}, R^{J3}, R^{J4}, R^{J5}, R^{J6}, R^{J7}, R^{J8}, R^{J9}, R^{J10}, and R^{J11} are each independently selected from the group consisting of hydrogen, halogen, alkyl, alkenyl, alkynyl, aryl, heteroalkyl, heteroatom containing alkenyl, heteroalkenyl, heteroaryl, alkoxy, alkenyloxy, aryloxy, alkoxy carbonyl, carbonyl, alkylamino, alkylthio, aminosulfonyl, monoalkylaminosulfonyl, dialkylaminosulfonyl, alkylsulfonyl, nitrile, nitro,

alkylsulfinyl, trihaloalkyl, perfluoroalkyl, carboxylic acid, ketone, aldehyde, nitrate, cyano, isocyanate, thioisocyanate, cyanato, thiocyanato, hydroxyl, ester, ether, thioether, amine, alkylamine, imine, amide, halogen-substituted amide, trifluoroamide, sulfide, disulfide, sulfonate, carbamate, silane, siloxane, phosphine, phosphate, borate, or -A-Fn, wherein "A" is a divalent hydrocarbon moiety selected from alkylene and arylalkylene, wherein the alkyl portion of the alkylene and arylalkylene groups can be linear or branched, saturated or unsaturated, cyclic or acyclic, and substituted or unsubstituted, wherein the aryl portion of the arylalkylene can be substituted or unsubstituted, and wherein hetero atoms and/or functional groups may be present in either the aryl or the alkyl portions of the alkylene and arylalkylene groups, and Fn is a functional group, or any one or more of the R^{J1} , R^{J2} , R^{J3} , R^{J4} , R^{J5} , R^{J6} , R^{J7} , R^{J8} , R^{J9} , R^{J10} , and R^{J11} may be linked together to form a cyclic group, or any one or more of the R^{J1} , R^{J2} , R^{J3} , R^{J4} , R^{J5} , R^{J6} , R^{J7} , R^{J8} , R^{J9} , R^{J10} , and R^{J11} may be attached to a support.


[000140] Additionally, one preferred embodiment of the Group 8 transition metal complex of formula (XVI) is a Group 8 transition metal complex comprising a Schiff base ligand having the structure of formula (XVII):



wherein M, X^1 , L^1 , Z, R^{J7} , R^{J8} , R^{J9} , R^{J10} , and R^{J11} are as defined above for Group 8 transition metal complex of formula XVI; and


R^{J12} , R^{J13} , R^{J14} , R^{J15} , R^{J16} , R^{J17} , R^{J18} , R^{J19} , R^{J20} , and R^{J21} are as defined above for R^{J1} , R^{J2} , R^{J3} , R^{J4} , R^{J5} , and R^{J6} for Group 8 transition metal complex of formula XVI, or any one or more of the R^{J7} , R^{J8} , R^{J9} , R^{J10} , R^{J11} , R^{J12} , R^{J13} , R^{J14} , R^{J15} , R^{J16} , R^{J17} , R^{J18} , R^{J19} , R^{J20} , and R^{J21} may be linked together to form a cyclic group, or any one or more of the R^{J7} , R^{J8} , R^{J9} , R^{J10} , R^{J11} , R^{J12} , R^{J13} , R^{J14} , R^{J15} , R^{J16} , R^{J17} , R^{J18} , R^{J19} , R^{J20} , and R^{J21} may be attached to a support.

[000141] Additionally, another preferred embodiment of the Group 8 transition metal complex of formula (XVI) is a Group 8 transition metal complex comprising a Schiff base ligand having the structure of formula (XVIII):



wherein M, X¹, L¹, Z, R⁷, R⁸, R⁹, R¹⁰, and R¹¹ are as defined above for Group 8 transition metal complex of formula (XVI).

[000142] Additionally, another group of olefin metathesis catalysts that may be used in the invention disclosed herein, is a Group 8 transition metal complex comprising a Schiff base ligand having the structure of formula (XIX):



wherein M is a Group 8 transition metal, particularly ruthenium or osmium, or more particularly, ruthenium;

X¹, L¹, R¹, and R² are as defined for the first and second groups of catalysts defined above;

Z is selected from the group consisting of oxygen, sulfur, selenium, NR^{K5}, PR^{K5}, AsR^{K5}, and SbR^{K5};

m is 0, 1, or 2; and













R^{K1} , R^{K2} , R^{K3} , R^{K4} , and R^{K5} are each independently selected from the group consisting of hydrogen, halogen, alkyl, alkenyl, alkynyl, aryl, heteroalkyl, heteroatom containing alkenyl, heteroalkenyl, heteroaryl, alkoxy, alkenyloxy, aryloxy, alkoxy-carbonyl, carbonyl, alkylamino, alkylthio, aminosulfonyl, monoalkylaminosulfonyl, dialkylaminosulfonyl, alkylsulfonyl, nitrile, nitro, alkylsulfinyl, trihaloalkyl, perfluoroalkyl, carboxylic acid, ketone, aldehyde, nitrate, cyano, isocyanate, thioisocyanate, cyanato, thiocyanato, hydroxyl, ester, ether, thioether, amine, alkylamine, imine, amide, halogen-substituted amide, trifluoroamide, sulfide, disulfide, sulfonate, carbamate, silane, siloxane, phosphine, phosphate, borate, or $-A-Fn$, wherein "A" is a divalent hydrocarbon moiety selected from alkylene and arylalkylene, wherein the alkyl portion of the alkylene and arylalkylene groups can be linear or branched, saturated or unsaturated, cyclic or acyclic, and substituted or unsubstituted, wherein the aryl portion of the arylalkylene can be substituted or unsubstituted, and wherein hetero atoms and/or functional groups may be present in either the aryl or the alkyl portions of the alkylene and arylalkylene groups, and Fn is a functional group, or any one or more of the R^{K1} , R^{K2} , R^{K3} , R^{K4} , and R^{K5} may be linked together to form a cyclic group, or any one or more of the R^{K1} , R^{K2} , R^{K3} , R^{K4} , and R^{K5} may be attached to a support.

[000143] In addition, catalysts of formulas (XVI) to (XIX) may be optionally contacted with an activating compound, where at least partial cleavage of a bond between the Group 8 transition metal and at least one Schiff base ligand occurs, wherein the activating compound is either a metal or silicon compound selected from the group consisting of copper (I) halides; zinc compounds of the formula $Zn(R^{Y1})_2$, wherein R^{Y1} is halogen, C_1 - C_7 alkyl or aryl; tin compounds represented by the formula $SnR^{Y2}R^{Y3}R^{Y4}R^{Y5}$ wherein each of R^{Y2} , R^{Y3} , R^{Y4} , and R^{Y5} is independently selected from the group consisting of halogen, C_1 - C_{20} alkyl, C_3 - C_{10} cycloalkyl, aryl, benzyl and C_2 - C_7 alkenyl; and silicon compounds represented by the formula $SiR^{Y6}R^{Y7}R^{Y8}R^{Y9}$ wherein each of R^{Y6} , R^{Y7} , R^{Y8} , and R^{Y9} is independently selected from the group consisting of hydrogen, halogen, C_1 - C_{20} alkyl, halo, C_1 - C_7 alkyl, aryl, heteroaryl, and vinyl. In addition, catalysts of formulas (XVI) to (XIX) may be optionally contacted with an activating compound where at least partial cleavage of a bond between the Group 8 transition metal and at least one Schiff base ligand occurs, wherein the activating compound is an inorganic acid such as hydrogen iodide, hydrogen bromide, hydrogen chloride, hydrogen fluoride, sulfuric acid, nitric acid, iodic acid, periodic acid, perchloric acid, $HOCIO$, $HOCIO_2$, and $HOIO_3$. In addition, catalysts of formulas (XVI) to (XIX) may be optionally contacted with an activating compound where at least partial cleavage of a bond between the Group 8 transition metal and at least one Schiff base ligand occurs, wherein the activating compound is an organic acid such as sulfonic acids including but not limited to methanesulfonic acid, aminobenzenesulfonic acid, benzenesulfonic acid, naphthalenesulfonic acid, sulfanilic acid and trifluoromethanesulfonic acid; monocarboxylic acids including but not limited to acetoacetic acid, barbituric acid, bromoacetic acid, bromobenzoic acid, chloroacetic acid, chlorobenzoic

acid, chlorophenoxyacetic acid, chloropropionic acid, cis-cinnamic acid, cyanoacetic acid, cyanobutyric acid, cyanophenoxyacetic acid, cyanopropionic acid, dichloroacetic acid, dichloroacetylacetic acid, dihydroxybenzoic acid, dihydroxymalic acid, dihydroxytartaric acid, dinicotinic acid, diphenylacetic acid, fluorobenzoic acid, formic acid, furancarboxylic acid, furoic acid, glycolic acid, hippuric acid, iodoacetic acid, iodobenzoic acid, lactic acid, lutidinic acid, mandelic acid, α -naphthoic acid, nitrobenzoic acid, nitrophenylacetic acid, o-phenylbenzoic acid, thioacetic acid, thiophene-carboxylic acid, trichloroacetic acid, and trihydroxybenzoic acid; and other acidic substances such as but not limited to picric acid and uric acid.













[000144] In addition, other examples of catalysts that may be used with the present invention are located in the following disclosures: U.S. Pat. Nos. 7,687,635; 7,671,224; 6,284,852; 6,486,279; and 5,977,393; International Publication Number WO 2010/037550; and U.S. Pat. App. Nos. 12/303,615; 10/590,380; 11/465,651 (U.S. Pat. App. Pub. No. 2007/0043188); and 11/465,651 (U.S. Pat. App. Pub. No. 2008/0293905 Corrected Publication); and European Pat. Nos. EP 1757613B1 and EP 1577282B1.












[000145] Non-limiting examples of catalysts that may be used to prepare supported complexes and in the reactions disclosed herein include the following, some of which for convenience are identified throughout this disclosure by reference to their molecular weight:





C884

C727











[000146] In the foregoing molecular structures and formulae, Ph represents phenyl, Cy represents cyclohexyl, Cp represents cyclopentyl, Me represents methyl, Bu represents *n*-butyl, *t*-Bu represents *tert*-butyl, *i*-Pr represents isopropyl, py represents pyridine (coordinated through the N atom), Mes represents mesityl (i.e., 2,4,6-trimethylphenyl), DiPp and DIPP represents 2,6-diisopropylphenyl, and MiPP represents 2-isopropylphenyl.

[000147] Further examples of catalysts useful to prepare supported complexes and in the reactions disclosed herein include the following: ruthenium (II) dichloro (3-methyl-2-butenylidene) bis(tricyclopentylphosphine) (**C716**); ruthenium (II) dichloro (3-methyl-2-butenylidene)

bis(tricyclohexylphosphine) (C801); ruthenium (II) dichloro(phenylmethylene) bis(tricyclohexylphosphine) (C823); ruthenium (II) (1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene) dichloro (phenylmethylene) (triphenylphosphine) (C830); ruthenium (II) dichloro (phenylvinylidene) bis(tricyclohexylphosphine) (C835); ruthenium (II) dichloro (tricyclohexylphosphine) (o-isopropoxyphenylmethylene) (C601); ruthenium (II) (1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene) dichloro (phenylmethylene) bis(3-bromopyridine) (C884); [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene]dichloro(o-isopropoxyphenylmethylene)ruthenium(II) (C627); [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene] dichloro (benzylidene) (triphenylphosphine) ruthenium(II) (C831); [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene] dichloro (benzylidene)(methyldiphenylphosphine)ruthenium(II) (C769); [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene]dichloro(benzylidene)(tricyclohexylphosphine)ruthenium(II) (C848); [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene] dichloro(benzylidene) (diethylphenylphosphine) ruthenium(II) (C735); [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene]dichloro(benzylidene)(tri-n-butylphosphine)ruthenium(II) (C771);[1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene]dichloro(3-methyl-2-butenylidene)(triphenylphosphine)ruthenium(II) (C809); [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene]dichloro(3-methyl-2-butenylidene)(methyldiphenylphosphine)ruthenium(II) (C747); [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene]dichloro(3-methyl-2-butenylidene) (tricyclohexylphosphine) ruthenium(II) (C827); [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene] dichloro(3-methyl-2-butenylidene)(diethylphenylphosphine)ruthenium(II) (C713); [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene] dichloro (3-methyl-2-butenylidene) (tri-n-butylphosphine)ruthenium(II) (C749); [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene] dichloro(phenylindenylidene)(triphenylphosphine)ruthenium(II) (C931); [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene] dichloro (phenylindenylidene) (methyldiphenylphosphine) ruthenium(II) (C869); [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene] dichloro (phenylindenylidene) (tricyclohexylphosphine) ruthenium(II) (C949); [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene]dichloro(phenylindenylidene)(diethylphenylphosphine)ruthenium(II) (C835); and [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene]dichloro(phenylindenylidene)(tri-n-butylphosphine)ruthenium(II) (C871).

[000148] Still further catalysts useful in ROMP reactions, and/or in other metathesis reactions, such as ring-closing metathesis, cross metathesis, ring-opening cross metathesis, self-metathesis, ethenolysis, alkenolysis, acyclic diene metathesis polymerization, and combinations thereof, include the following structures:






[000149] In general, the transition metal complexes used as catalysts herein can be prepared by several different methods, such as those described by Schwab et al. (1996) *J. Am. Chem. Soc.* **118**:100-110, Scholl et al. (1999) *Org. Lett.* **6**:953-956, Sanford et al. (2001) *J. Am. Chem. Soc.* **123**:749-750, U.S. Pat. No. 5,312,940, and U.S. Pat. No. 5,342,909. Also see U.S. Pat. App. Pub. No. 2003/0055262 to Grubbs et al., WO 02/079208, and U.S. Pat. No. 6,613,910 to Grubbs et al. Preferred synthetic methods are described in WO 03/11455 A1 to Grubbs et al.

[000150] Preferred olefin metathesis catalysts are Group 8 transition metal complexes having the structure of formula (I) commonly called “First Generation Grubbs” catalysts, formula (III) commonly called “Second Generation Grubbs” catalysts, or formula (VII) commonly called “Grubbs-Hoveyda” catalysts.

[000151] More preferred olefin metathesis catalysts have the structure of formula (I)



in which:

M is a Group 8 transition metal;

L^1 , L^2 , and L^3 are neutral electron donor ligands;

n is 0 or 1;

m is 0, 1, or 2;


k is 0 or 1;

X^1 and X^2 are anionic ligands;

R^1 and R^2 are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, substituted heteroatom-containing hydrocarbyl, and functional groups,

wherein any two or more of X^1 , X^2 , L^1 , L^2 , L^3 , R^1 , and R^2 can be taken together to form one or more cyclic groups, and further wherein any one or more of X^1 , X^2 , L^1 , L^2 , L^3 , R^1 , and R^2 may be attached to a support;

and formula (VII)



wherein,

M is a Group 8 transition metal;

L^1 is a neutral electron donor ligand;

X^1 and X^2 are anionic ligands;

Y is a heteroatom selected from O or N;


R^5 , R^6 , R^7 , and R^8 are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, substituted heteroatom-containing hydrocarbyl, and functional groups;

n is 0, 1, or 2; and

Z is selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, substituted heteroatom-containing hydrocarbyl, and functional groups,

wherein any combination of Y, Z, R^5 , R^6 , R^7 , and R^8 can be linked to form one or more cyclic groups, and further wherein any combination of X^1 , X^2 , L^1 , Y, Z, R^5 , R^6 , R^7 , and R^8 may be attached to a support.

[000152] Most preferred olefin metathesis catalysts have the structure of formula (I)



in which:

M is ruthenium;

n is 0;

m is 0;

k is 1;


L^1 and L^2 are trisubstituted phosphines independently selected from the group consisting of tri-n-butylphosphine ($Pn-Bu_3$), tricyclopentylphosphine (PCp_3), tricyclohexylphosphine (PCy_3), triisopropylphosphine ($P-i-Pr_3$), triphenylphosphine (PPh_3), methyl diphenylphosphine ($PMePh_2$), dimethylphenylphosphine (PMe_2Ph), and diethylphenylphosphine (PEt_2Ph); or L^1 is an N-heterocyclic carbene selected from the group consisting of 1,3-bis(2,4,6-trimethylphenyl)-2-imidazolidinylidene, 1,3-bis(2,4,6-trimethylphenyl)imidazol-2-ylidene, 1,3-bis(2,6-di-isopropylphenyl)-2-imidazolidinylidene, and 1,3-bis(2,6-di-isopropylphenyl)imidazol-2-ylidene and L^2 is a trisubstituted phosphine selected from the group consisting of tri-n-butylphosphine ($Pn-Bu_3$), tricyclopentylphosphine (PCp_3), tricyclohexylphosphine (PCy_3), triisopropylphosphine ($P-i-Pr_3$), triphenylphosphine (PPh_3),

methyldiphenylphosphine (PMePh₂), dimethylphenylphosphine (PMe₂Ph), and diethylphenylphosphine (PEt₂Ph);

X¹ and X² are chloride;

R¹ is hydrogen and R² is phenyl or -CH=C(CH₃)₂ or thienyl; or R¹ and R² are taken together to form 3-phenyl-1H-indene;

and formula (VII)



wherein,

M is ruthenium;

L¹ is a trisubstituted phosphine selected from the group consisting of tri-n-butylphosphine (Pn-Bu₃), tricyclopentylphosphine (PCp₃), tricyclohexylphosphine (PCy₃), triisopropylphosphine (P-i-Pr₃), triphenylphosphine (PPh₃), methyldiphenylphosphine (PMePh₂), dimethylphenylphosphine (PMe₂Ph), and diethylphenylphosphine (PEt₂Ph); or L¹ is an N-heterocyclic carbene selected from the group consisting of 1,3-bis(2,4,6-trimethylphenyl)-2-imidazolidinylidene, 1,3-bis(2,4,6-trimethylphenyl)imidazol-2-ylidene, 1,3-bis(2,6-di-isopropylphenyl)-2-imidazolidinylidene, and 1,3-bis(2,6-di-isopropylphenyl)imidazol-2-ylidene;

X¹ and X² are chloride;

Y is oxygen;

R⁵, R⁶, R⁷, and R⁸ are each hydrogen;

n is 1; and

Z is isopropyl.

[000153] Suitable supports for any of the catalysts described herein may be of synthetic, semi-synthetic, or naturally occurring materials, which may be organic or inorganic, e.g., polymeric, ceramic, or metallic. Attachment to the support will generally, although not necessarily, be covalent, and the covalent linkage may be direct or indirect. Indirect covalent linkages are typically, though not

necessarily, through a functional group on a support surface. Ionic attachments are also suitable, including combinations of one or more anionic groups on the metal complexes coupled with supports containing cationic groups, or combinations of one or more cationic groups on the metal complexes coupled with supports containing anionic groups.

[000154] When utilized, suitable supports may be selected from silicas, silicates, aluminas, aluminum oxides, silica-aluminas, aluminosilicates, zeolites, titanias, titanium dioxide, magnetite, magnesium oxides, boron oxides, clays, zirconias, zirconium dioxide, carbon, polymers, cellulose, cellulosic polymers amylose, amylosic polymers, or a combination thereof. The support preferably comprises silica, a silicate, or a combination thereof.

[000155] In certain embodiments, it is also possible to use a support that has been treated to include functional groups, inert moieties, and/or excess ligands. Any of the functional groups described herein are suitable for incorporation on the support, and may be generally accomplished through techniques known in the art. Inert moieties may also be incorporated on the support to generally reduce the available attachment sites on the support, e.g., in order to control the placement, or amount, of a complex linked to the support.

[000156] The metathesis catalysts that are described *infra* may be utilized in olefin metathesis reactions according to techniques known in the art. The catalyst is typically added to the resin composition as a solid, a solution, or as a suspension. When the catalyst is added to the resin composition as a suspension, the catalyst is suspended in a dispersing carrier such as mineral oil, paraffin oil, soybean oil, tri-isopropylbenzene, or any hydrophobic liquid which has a sufficiently high viscosity so as to permit effective dispersion of the catalyst, and which is sufficiently inert and which has a sufficiently high boiling point so that it does not act as a low-boiling impurity in the olefin metathesis reaction. It will be appreciated that the amount of catalyst that is used (i.e., the "catalyst loading") in the reaction is dependent upon a variety of factors such as the identity of the reactants and the reaction conditions that are employed. It is therefore understood that catalyst loading may be optimally and independently chosen for each reaction.


Paints and Primers

[000157] Any epoxy or urethane based paint and/or primer may be used with the resin compositions and/or in-mold coating adhesion compounds of the invention. As an example of a suitable urethane based paint and/or primer, Polane® paints and/or primers available from Sherwin Williams may be used.

In-Mold Coating Adhesion Compound Comprising

A Heteroatom-Containing Functional Group and A Metathesis Active Olefin

[000158] The in-mold coating adhesion compound comprising a heteroatom-containing functional group and a metathesis active olefin typically contains between 2 and 20 carbons with hydroxyl, amine, thiol, phosphorus, or silane functional groups. In-mold coating adhesion compounds comprising a heteroatom-containing functional group and a metathesis active olefin that may be used in the present invention disclosed herein are generally compounds containing at least one heteroatom containing functional group and at least one metathesis active olefin and are of the following general structure:



wherein O^M , Q^* , and X^* are as follows:

O^M is a metathesis active olefin fragment selected from cyclic olefins and acyclic olefins, where the carbon-carbon double bond typically is not tetra-substituted (e.g., at least one substituent is a hydrogen);

Q^* is an optional linker group (e.g., $n = 0$ or 1) such as, for example, a hydrocarbylene (including, for example, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, and substituted heteroatom-containing hydrocarbylene, such as substituted and/or heteroatom-containing alkylene) or $-(CO)-$ group; and

X^* is oxygen, sulfur, or a heteroatom-containing fragment such as $N(R^X)$, $P(R^X)$, $OP(R^X)$, $OP(R^X)O$, $OP(OR^X)O$, $P(=O)(R^X)$, $OP(=O)(R^X)$, $OP(=O)(R^X)O$, $OP(=O)(OR^X)O$, $Si(R^X)_2$, $Si(R^X)_2O$, $Si(OR^X)_2O$, or $Si(R^X)(OR^X)O$,

wherein each R^X is, independent of one another, a hydrogen or a hydrocarbyl group optionally comprising further functional groups. Each R^X is, independent of one another, most commonly a hydrogen, aryl, or lower alkyl group.

[000159] Metathesis active olefins include cyclic olefins as described herein, where such cyclic olefins may be optionally substituted, optionally heteroatom-containing, mono-unsaturated, di-unsaturated, or poly-unsaturated C_5 to C_{24} hydrocarbons that may be mono-, di-, or poly-cyclic. The cyclic olefin may generally be any strained or unstrained cyclic olefin, provided the cyclic olefin is able to participate in a ROMP reaction either individually or as part of a ROMP cyclic olefin composition. Very low-strain cyclic olefin groups such as cyclopentenenes and cyclohexenes may not be sufficiently reactive to allow the in-mold coating adhesion compound to be used at practical loading levels and should typically be avoided. Metathesis active olefins also include acyclic olefins, where such acyclic olefins may be optionally substituted, optionally heteroatom-containing, mono-unsaturated, di-unsaturated, or poly-unsaturated C_2 to C_{30} hydrocarbons, typically C_2 to C_{20} hydrocarbons, or more typically C_2 to C_{12}

hydrocarbons. Acyclic olefins may contain one or more terminal olefins and/or one or more internal olefins, and/or any combination of terminal olefins and/or internal olefins.

[000160] In the heteroatom-containing functional group, X* is commonly oxygen, sulfur, or NR^x and is most commonly oxygen, i.e., a hydroxy-substituted olefin. Preferred compounds comprising a heteroatom-containing functional group and a metathesis active olefin include, but are not limited to, 5-norbornene-2-methanol (NB-MeOH); 2-hydroxyethyl bicyclo[2.2.1]hept-2-ene-carboxylate (HENB); 2-hydroxyethyl acrylate (HEA); allyl alcohol; oleyl alcohol; 9-decen-1-ol; allyl alcohol, cis-13-dodecenol, and trans-9-octadecenol, and other unsaturated alcohols, norbornyl alcohol, 2-cycloocten-1-ol, 2-cyclooctadiene-1-ol, and p-vinyl phenol, and other alcohols which have an alicyclic structure; 2-hydroxyethyl methacrylate; 2-hydroxy-3-acryloxypropyl methacrylate, ethoxylated hydroxyethyl acrylate, ethoxylated hydroxyethyl methacrylate, polypropyleneglycol monomethacrylate, polypropylene glycol monoacrylate, phenol acrylate, phenol methacrylate, bisphenol A type epoxy acrylate, novolac type epoxy acrylate, and brominated bisphenol A type epoxy acrylate, and other methacrylics or acrylics which have one or more methacryl or acryl groups and hydroxyl groups, allyl amine, diallyl amine, oleyl amine, and any of a number of related linear or branched enamines, norbornene amines such as bicyclo[2.2.1]hept-2-ene-5-methylamine or 5-norbornenyl-2-methylamine (NBMA), etc. and combinations thereof.

[000161] An additional preferred compound comprising a heteroatom-containing functional group and a metathesis active olefin is 9-octadecene-1,18-diol.

[000162] Additionally, more preferred compounds comprising a heteroatom-containing functional group and a metathesis active olefin are 5-norbornene-2-methanol (NB-MeOH), 2-hydroxyethyl bicyclo[2.2.1]hept-2-ene-carboxylate (HENB), 9-octadecene-1,18-diol, or combinations thereof.

[000163] Furthermore, compounds comprising a heteroatom-containing functional group and a metathesis active olefin may be added to a cyclic olefin resin composition. Any concentration of compounds comprising a heteroatom-containing functional group and a metathesis active olefin which improves the adhesion of the paint and/or primer to the ROMP polymer is sufficient for the invention. In general, suitable amounts of compounds comprising a heteroatom-containing functional group and a metathesis active olefin range from 0.001-50 phr, particularly 0.05-10 phr, more particularly 0.1-10 phr, or even more particularly 0.5-4.0 phr.

Resin Compositions and Articles

[000164] Resin compositions that may be used in the present invention disclosed herein generally comprise at least one cyclic olefin. The cyclic olefins described hereinabove are suitable for use and may be functionalized or unfunctionalized, and may be substituted or unsubstituted. Additionally, resin

compositions according to the invention may also comprise at least one cyclic olefin, where the resin composition is combined with an olefin metathesis catalyst. Resin compositions of the invention may be optionally formulated with an exogenous inhibitor (e.g., trialkylphosphines, triarylphosphines, hydroperoxides). Here, exogenous (meaning external additive or other reactives that can be added to the resin composition, or mixed or combined with the catalyst) is distinguished from indigenous (meaning native or established by the components attached to the transition metal of the carbene catalysts). Exogenous inhibitors or “gel modification additives,” for use in the present invention and methods for their use are disclosed in U.S. Pat. No. 5,939,504. U.S. Pat. No. 5,939,504 discloses the use of exogenous “gel modification additives” or exogenous inhibitors, such as a neutral electron donor or a neutral Lewis base, preferably trialkylphosphines and triarylphosphines. Trialkylphosphines and triarylphosphines for use as exogenous inhibitors include without limitation trimethylphosphine (PMe₃), triethylphosphine (PEt₃), tri-*n*-butylphosphine (PBu₃), tri(*ortho*-tolyl)phosphine (P-*o*-tolyl₃), tri-*tert*-butylphosphine (P-*tert*-Bu₃), tricyclopentylphosphine (PCyclopentyl₃), tricyclohexylphosphine (PCy₃), triisopropylphosphine (P-*i*-Pr₃), trioctylphosphine (POct₃), triisobutylphosphine, (P-*i*-Bu₃), triphenylphosphine (PPh₃), tri(pentafluorophenyl)phosphine (P(C₆F₅)₃), methyldiphenylphosphine (PMePh₂), dimethylphenylphosphine (PMe₂Ph), and diethylphenylphosphine (PEt₂Ph). Preferred trialkyl phosphines and triarylphosphines for use as exogenous inhibitors are tricyclohexylphosphine and triphenylphosphine. A single trialkylphosphine and/or triarylphosphine may be used or a combination of two or more different trialkylphosphines and/or triarylphosphines may be used. Resin compositions of the invention may be optionally formulated with adhesion promoters as described in International Pat. App. No. PCT/US2012/042850. Resin compositions of the invention may be optionally formulated with a hydroperoxide gel modifier (exogenous inhibitor). Hydroperoxide gel modifiers for use in the present invention and methods for their use are disclosed in International Pat. App. No. PCT/US2012/042850. International Pat. App. No. PCT/US2012/042850 discloses the use of exogenous hydroperoxide gel modifiers or exogenous inhibitors, such as cumene hydroperoxide. Although, in general, the hydroperoxide may be any organic hydroperoxide that is effective to delay the onset of the gel state, the hydroperoxide is typically an alkyl, for example, C₂-C₂₄ alkyl, aryl, for example, C₅-C₂₄ aryl, aralkyl, or alkaryl, for example, C₆-C₂₄ alkaryl, hydroperoxide, especially secondary or tertiary aliphatic or aromatic hydroperoxides. More specific hydroperoxides suitable for use include *tert*-butyl hydroperoxide, *tert*-amyl hydroperoxide, cumene hydroperoxide, diisopropyl benzene hydroperoxide, (2,5-dihydroperoxy)-2,5-dimethylhexane, cyclohexyl hydroperoxide, triphenylmethyl hydroperoxide, pinane hydroperoxide (e.g., Glidox[®] 500; LyondellBasell), and paramenthane hydroperoxide (e.g.,

Glidox[®] 300; LyondellBasell). More preferably, the hydroperoxides suitable for use include *tert*-butyl hydroperoxide and cumene hydroperoxide. Gel-modification additives may be added to the reaction mixture in the absence of solvent, or as organic or aqueous solutions. A single hydroperoxide compound may be used as the gel-modification additive, or a combination of two or more different hydroperoxide compounds may be used.

[000165] Resin compositions of the invention may be optionally formulated with additives. Suitable additives include, but are not limited to, gel modifiers, hardness modulators, antioxidants, antiozonants, stabilizers, fillers, binders, coupling agents, thixotropes, impact modifiers, elastomers, wetting agents, wetting agents, biocides, plasticizers, pigments, flame retardants, dyes, fibers and reinforcement materials, including sized reinforcements and substrates, such as those treated with finishes, coatings, coupling agents, film formers and/or lubricants. Furthermore, the amount of additives present in the resin compositions may vary depending on the particular type of additive used. The concentration of the additives in the resin compositions typically ranges from, for example, 0.001-85 percent by weight, particularly, from 0.1-75 percent by weight, or even more particularly, from 2-60 percent by weight.

[000166] Suitable impact modifiers or elastomers include without limitation natural rubber, butyl rubber, polyisoprene, polybutadiene, polyisobutylene, ethylene-propylene copolymer, styrene-butadiene-styrene triblock rubber, random styrene-butadiene rubber, styrene-isoprene-styrene triblock rubber, styrene-ethylene/butylene-styrene copolymer, styrene-ethylene/propylene-styrene copolymer, ethylene-propylene-diene terpolymers, ethylene-vinyl acetate and nitrile rubbers. Preferred impact modifiers or elastomers are polybutadiene Diene 55AC10 (Firestone), polybutadiene Diene 55AM5 (Firestone), EPDM Royalene 301T, EPDM Buna T9650 (Bayer), styrene-ethylene/butylene-styrene copolymer Kraton G1651H, Polysar Butyl 301 (Bayer), polybutadiene Taktene 710 (Bayer), styrene-ethylene/butylene-styrene Kraton G1726M, Ethylene-Octene Engage 8150 (DuPont-Dow), styrene-butadiene Kraton D1184, EPDM Nordel 1070 (DuPont-Dow), and polyisobutylene Vistanex MML-140 (Exxon). Such materials are normally employed in the resin composition at levels of about 0.10 phr to 10 phr, but more preferably at levels of about 0.1 phr to 5 phr. Various polar impact modifiers or elastomers can also be used.

[000167] Resin compositions of the invention may be optionally formulated with or without a crosslinker, for example, a crosslinker selected from dialkyl peroxides, diacyl peroxides, and peroxyacids.

[000168] Antioxidants and antiozonants include any antioxidant or antiozonant used in the rubber or plastics industry. An "Index of Commercial Antioxidants and Antiozonants, Fourth Edition" is available from Goodyear Chemicals, The Goodyear Tire and Rubber Company, Akron, Ohio 44316. Suitable stabilizers (i.e., antioxidants or antiozonants) include without limitation: 2,6-di-*tert*-butyl-4-methylphenol (BHT); styrenated phenol, such as Wingstay S (Goodyear); 2- and 3-*tert*-butyl-4-methoxyphenol;

alkylated hindered phenols, such as Wingstay C (Goodyear); 4-hydroxymethyl-2,6-di-tert-butylphenol; 2,6-di-tert-butyl-4-sec-butylphenol; 2,2'-methylenebis(4-methyl-6-tert-butylphenol); 2,2'-methylenebis(4-ethyl-6-tert-butylphenol); 4,4'-methylenebis(2,6-di-tert-butylphenol); miscellaneous bisphenols, such as Cyanox® 53 and Permanax WSO; 2,2'-ethylidenebis(4,6-di-tert-butylphenol); 2,2'-methylenebis(4-methyl-6-(1-methylcyclohexyl)phenol); 4,4'-butylidenebis(6-tert-butyl-3-methylphenol); polybutylated Bisphenol A; 4,4'-thiobis(6-tert-butyl-3-methylphenol); 4,4'-methylenebis(2,6-dimethylphenol); 1,1'-thiobis(2-naphthol); methylene bridged polyaklylphenol, such as Ethyl antioxidant 738; 2,2'-thiobis(4-methyl-6-tert-butylphenol); 2,2'-isobutylidenebis(4,6-dimethylphenol); 2,2'-methylenebis(4-methyl-6-cyclohexylphenol); butylated reaction product of p-cresol and dicyclopentadiene, such as Wingstay L; tetrakis(methylene-3,5-di-tert-butyl-4-hydroxyhydrocinnamate) methane, i.e., Irganox 1010; 1,3,5-trimethyl-2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)benzene, e.g., Ethanox 330; 4,4'-methylenebis(2,6-di-tertiary-butylphenol), e.g., Ethanox 4702 or Ethanox 4710; 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)isocyanurate, i.e., Good-rite 3114, 2,5-di-tert-amylhydroquinone, tert-butylhydroquinone, tris(nonylphenylphosphite), bis(2,4-di-tert-butyl)pentaerythritol)diphosphite, distearyl pentaerythritol diphosphite, phosphited phenols and bisphenols, such as Naugard 492, phosphite/phenolic antioxidant blends, such as Irganox B215; di-n-octadecyl(3,5-di-tert-butyl-4-hydroxybenzyl)phosphonate, such as Irganox 1093; 1,6-hexamethylene bis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate), such as Irganox 259, and octadecyl-3,5-di-tert-butyl-4-hydroxyhydrocinnamate, i.e., Irganox 1076, tetrakis(2,4-di-tert-butylphenyl)4,4'-biphenylenediphosphonite, diphenylamine, and 4,4'-diemthoxydiphenylamine. Such materials are normally employed in the resin composition at levels of about 0.10 phr to 10 phr, but more preferably at levels of about 0.1 phr to 5 phr.

[000169] Suitable reinforcing materials include those that add to the strength or stiffness of a polymer composite when incorporated with the polymer. Reinforcing materials can be in the form of filaments, fibers, rovings, mats, weaves, fabrics, knitted material, cloth, or other known structures. Suitable reinforcement materials include glass fibers and fabrics, carbon fibers and fabrics, aramid fibers and fabrics, polyolefin fibers or fabrics (including ultrahigh molecular weight polyethylene fabrics such as those produced by Honeywell under the Spectra trade name), and polyoxazole fibers or fabrics (such as those produced by the Toyobo Corporation under the Zylon trade name). Reinforcing materials containing surface finishes, sizings, or coatings are particularly suitable for the described invention including Ahlstrom glass roving (R338-2400), Johns Manville glass roving (Star ROV®-086), Owens Corning rovings (OCV 366-AG-207, R25H-X14-2400, SE1200-207, SE1500-2400, SE2350-250), PPG glass rovings (Hybon® 2002, Hybon® 2026), Toho Tenax® carbon fiber tow (HTR-40), and Zoltek carbon fiber tow (Panex® 35). Furthermore, any fabrics prepared using reinforcing materials containing surface finishes, sizings or coatings are suitable for the invention. Advantageously, the invention does not

require the expensive process of removing of surface finishes, sizings, or coatings from the reinforcing materials. Additionally, glass fibers or fabrics may include without limitation A-glass, E-glass or S-glass, S-2 glass, C-glass, R-glass, ECR-glass, M-glass, D-glass, and quartz, and silica/quartz. Preferred glass fiber reinforcements are those with finishes formulated for use with epoxy, vinyl ester, and/or polyurethane resins. When formulated for use with a combination of these resin types, the reinforcements are sometimes described as “multi-compatible.” Such reinforcements are generally treated during their manufacture with organosilane coupling agents comprising vinyl, amino, glycidoxy, or methacryloxy functional groups (or various combinations thereof) and are coated with a finish to protect the fiber surface and facilitate handling and processing (e.g., spooling and weaving). Finishes typically comprise a mixture of chemical and polymeric compounds such as film formers, surfactants, and lubricants. Especially preferred glass reinforcements are those containing some amount of amino-functionalized silane coupling agent. Especially preferred finishes are those comprising and epoxy-based and/or polyurethane-based film formers. Examples of preferred glass-fiber reinforcements are those based on Hybon® 2026, 2002, and 2001 (PPG) multi-compatible rovings; Ahlstrom R338 epoxysilane-sized rovings; StarRov® 086 (Johns Manville) soft silane sized multi-compatible rovings; OCV™ 366, SE 1200, and R25H (Owens Corning) multi-compatible rovings; OCV™ SE 1500 and 2350 (Owens Corning) epoxy-compatible rovings; and Jushi Group multi-compatible glass rovings (752 type, 396 type, 312 type, 386 type). Additional suitable polymer fibers and fabrics may include without limitation one or more of polyester, polyamide (for example, NYLON polamide available from E.I. DuPont, aromatic polyamide (such as KEVLAR aromatic polyamide available from E.I. DuPont, or P84 aromatic polyamide available from Lenzing Aktiengesellschaft), polyimide (for example KAPTON polyimide available from E.I. DuPont, polyethylene (for example, DYNEEMA polyethylene from Toyobo Co., Ltd.). Additional suitable carbon fibers may include without limitation AS2C, AS4, AS4C, AS4D, AS7, IM6, IM7, IM9, and PV42/850 from Hexcel Corporation; TORAYCA T300, T300J, T400H, T600S, T700S, T700G, T800H, T800S, T1000G, M35J, M40J, M46J, M50J, M55J, M60J, M30S, M30G and M40 from Toray Industries, Inc.; HTS12K/24K, G30-500 3k/6K/12K, G30-500 12K, G30-700 12K, G30-7000 24K F402, G40-800 24K, STS 24K, HTR 40 F22 24K 1550tex from Toho Tenax, Inc.; 34-700, 34-700WD, 34-600, 34-600WD, and 34-600 unsized from Grafil Inc.; T-300, T-650/35, T-300C, and T-650/35C from Cytec Industries. Additionally suitable carbon fibers may include without limitation AKSACA (A42/D011), AKSACA (A42/D012), Blue Star Starafil (10253512-90), Blue Star Starafil (10254061-130), SGL Carbon (C30 T050 1.80), SGL Carbon (C50 T024 1.82), Grafil (347R1200U), Grafil (THR 6014A), Grafil (THR 6014K), Hexcel Carbon (AS4C/EXP 12K), Mitsubishi (Pyrofil TR 50S 12L AF), Mitsubishi (Pyrofil TR 50S 12L AF), Toho Tenax (T700SC 12000-50C), Toray (T700SC 12000-90C), Zoltek (Panex 35 50K, sizing 11), Zoltek (Panex 35 50K, sizing 13). Additional suitable

carbon fabrics may include without limitation Carbon fabrics by Vectorply (C-L 1800) and Zoltek (Panex 35 D Fabric-PX35UD0500-1220). Additionally suitable glass fabrics may include without limitation glass fabrics as supplied by Vectorply (E-LT 3500-10) based on PPG Hybon® 2026; Saertex (U14EU970-01190-T2525-125000) based on PPG Hybon® 2002; Chongqing Polycomp Internation Corp. (CPIC® Fiberglass) (EKU 1150(0)/50-600); and Owens Corning (L1020/07A06 Xweft 200tex), and SGL Kumpers (HPT970) based on PPG Hybon® 2002.

[000170] Other suitable fillers include, for example, metallic density modulators, microparticulate density modulators, such as, for example, microspheres, and macroparticulate density modulators, such as, for example, glass or ceramic beads. Metallic density modulators include, but are not limited to, powdered, sintered, shaved, flaked, filed, particulated, or granulated metals, metal oxides, metal nitrides, and/or metal carbides, and the like. Preferred metallic density modulators include, among others, tungsten, tungsten carbide, aluminum, titanium, iron, lead, silicon oxide, aluminum oxide, boron carbide, and silicon carbide. Microparticulate density modulators include, but are not limited to, glass, metal, thermoplastic (either expandable or pre-expanded) or thermoset, and/or ceramic/silicate microspheres. Macroparticulate density modulators include, but are not limited to, glass, plastic, or ceramic beads; metal rods, chunks, pieces, or shot; hollow glass, ceramic, plastic, or metallic spheres, balls, or tubes; and the like.

[000171] Articles may include, but are not limited to, those formed by standard manufacturing techniques including casting, centrifugal casting, pultrusion, molding, rotational molding, open molding, reaction injection molding (RIM), resin transfer molding (RTM), pouring, vacuum impregnation, surface coating, filament winding and other methods known to be useful for production of polymer articles. Molded parts include but are not limited to reaction injection molding, resin transfer molding, and vacuum assisted resin transfer molding. Furthermore, the compositions and articles of manufacture of the invention are not limited to a single polymer-surface interface but include also multilayers and laminates containing multiple polymer-surface interfaces. The invention is also suitable for manufacture of articles by the infusion of the resin into a porous material. Such porous materials include but are not limited to wood, cement, concrete, open-cell and reticulated foams and sponges, papers, cardboards, felts, ropes or braids of natural or synthetic fibers, and various sintered materials. Additionally, other manufacturing techniques include without limitation cell casting, dip casting, continuous casting, embedding, potting, encapsulation, film casting or solvent casting, gated casting, mold casting, slush casting, extrusion, mechanical foaming, chemical foaming, physical foaming, compression molding or matched die molding, spray up, Vacuum Assisted Resin Transfer Molding (VARTM), Seeman's Composite Resin Infusion Molding Process (SCRIMP), blow molding, in-mold coating, in-mold painting or injection, vacuum forming, Reinforced Reaction Injection Molding (RRIM), Structural Reaction Injection Molding (SRIM),

thermal expansion transfer molding (TERM), resin injection recirculation molding (RICM), controlled atmospheric pressure resin infusion (CAPRI), hand-layup. For manufacturing techniques requiring the use of a RIM or impingement style mixhead, including without limitation RIM, SRIM, and RRIM, articles of manufacture may be molded using a single mixhead or a plurality of mixheads as well as a plurality of material injection streams (e.g., two resin streams and one catalyst stream).

[000172] The present invention is also directed to articles manufactured from a resin composition comprising at least one cyclic olefin, where the resin composition is combined with an olefin metathesis catalyst, and the resulting resin composition is optionally applied to a substrate, which may be, for example, a functionalized substrate.

[000173] Furthermore, the present invention also allows for the making of articles of manufacture of any configuration, weight, size, thickness, or geometric shape. Examples of articles of manufacture include without limitation any molded or shaped article for use as an aerospace component, a marine component, an automotive component, a sporting goods component, an electrical component, and industrial component, medical component, dental component, oil and gas component, or military component. In one embodiment an article may be a turbine component used on aircraft or general power generation. In one embodiment, turbine components may include without limitation one or more of an inlet, pylon, pylon fairing, an acoustic panel, a thrust reverser panel, a fan blade, a fan containment case, a bypass duct, an aerodynamic cowl, or an airfoil component. In one embodiment, an article may be a turbine blade component or may be a turbine blade. In one embodiment, an article may be a wind rotor blade, tower, spar cap, or nacelle for wind turbines. In one embodiment, an article may be an airframe component. Examples of aerospace components may include without limitation one or more of fuselage skin, wing, fairing, doors, access panel, aerodynamic control surface, or stiffener. In one embodiment an article may be an automotive component. Examples of automotive components may include without limitation one or more of body panel, fender, spoiler, truck bad, protective plate, hood, longitudinal rail, pillar, or door. Examples of industrial components may include without limitation one or more of risers platforms, impact protection structures for oil and gas; bridges, pipes, pressure vessels, power poles, coils, containers, tanks, liners, electrolytic cell covers, containment vessels, articles for application in corrosive environments (e.g., chlor-alkali, caustic, acidic, brine, etc.), reinforcement structures for concrete architectures and roads, or radiators. Examples of electrical components may include without limitation one or more wound articles, such as coils or electric motors, or insulating devices. In one embodiment, an article may be an eddy-current shielding component of a magnetic resonance imaging system or shielding component for any electromagnetic radiation. In one embodiment, an article may be a military component including without limitation ballistics resistant armor for personnel or vehicles, or ballistics resistant structures for protecting personnel or equipment. In one embodiment, an article may be a

sporting goods component including without limitation an arrow shaft, a tennis racket frame, a hockey stick, compound bow limbs, or a golf club shaft. Examples of oil and gas components include casing centralizers and drill string centralizers.

[000174] In a preferred embodiment, the metathesis reactions disclosed herein are carried out under a dry, inert atmosphere. Such an atmosphere may be created using any inert gas, including such gases as nitrogen and argon. The use of an inert atmosphere is optimal in terms of promoting catalyst activity, and reactions performed under an inert atmosphere typically are performed with relatively low catalyst loading. The reactions disclosed herein may also be carried out in an oxygen-containing and/or a water-containing atmosphere, and in one embodiment, the reactions are carried out under ambient conditions. The presence of oxygen or water in the reaction may, however, necessitate the use of higher catalyst loadings as compared with reactions performed under an inert atmosphere. Where the vapor pressure of the reactants allows, the reactions disclosed herein may also be carried out under reduced pressure.

[000175] The reactions disclosed herein may be carried out in a solvent, and any solvent that is inert towards cross-metathesis may be employed. Generally, solvents that may be used in the metathesis reactions include organic, protic, or aqueous solvents, such as aromatic hydrocarbons, chlorinated hydrocarbons, ethers, aliphatic hydrocarbons, alcohols, water, or mixtures thereof. Example solvents include benzene, toluene, p-xylene, methylene chloride, 1,2-dichloroethane, dichlorobenzene, chlorobenzene, tetrahydrofuran, diethylether, pentane, methanol, ethanol, water, or mixtures thereof. In a preferred embodiment, the reactions disclosed herein are carried out neat, i.e., without the use of a solvent.

[000176] It will be appreciated that the temperature at which a metathesis reaction according to methods disclosed herein is conducted can be adjusted as needed, and may be at least about -78°C, -40°C, -10°C, 0°C, 10°C, 20°C, 25°C, 35°C, 50°C, 70°C, 100°C, or 150°C, or the temperature may be in a range that has any of these values as the upper or lower bounds. In a preferred embodiment, the reactions are carried out at a temperature of at least about 35°C, and in another preferred embodiment, the reactions are carried out at a temperature of at least about 50°C.

[000177] It is to be understood that while the invention has been described in conjunction with specific embodiments thereof, the description above as well as the examples that follow are intended to illustrate and not limit the scope of the invention. Other aspects, advantages, and modifications within the scope of the invention will be apparent to those skilled in the art to which the invention pertains.

EXPERIMENTAL

[000178] In the following examples, efforts have been made to ensure accuracy with respect to numbers used (e.g., amounts, temperature, etc.) but some experimental error and deviation should be

accounted for. Unless indicated otherwise, temperature is in degrees C, pressure is at or near atmospheric, viscosity is in centipoise (cP).

[000179] The following examples are to be considered as not being limiting of the invention as described herein, and are instead provided as representative examples of the in-mold coating compositions of the invention and the methods for their use.

EXAMPLES

Materials and Methods

[000180] All glassware was oven dried and reactions were performed under ambient conditions unless otherwise noted. All solvents and reagents were purchased from commercial suppliers and used as received unless otherwise noted.

[000181] Dicyclopentadiene (Ultrene[®] 99) (DCPD) was obtained from Cymetech Corporation. A modified DCPD base resin containing 20-25% tricyclopentadiene (and small amounts of higher cyclopentadiene homologs) was prepared by heat treatment of Ultrene[®] 99 generally as described in U.S. Pat. No. 4,899,005. 5-Norbornene-2-methanol was used as received from Sigma Aldrich. 2-Hydroxyethyl bicyclo [2.2.1]hept-2-ene-5-carboxylate (HENB) was prepared as described in WO 2012/174502. 4,7-Methano-3a,4,5,6,7,7a-hexahydro-1H-inden-5-ol (Cydecanol) was used as received from Texmark.

[000182] Paint adhesion was determined by cross hatch testing (ASTM-D-3359). A cutter was used to cut a 7x7 grid of 3/32-inch squared on the painted surface. An adhesive tape was applied and removed and removal or damage to fewer than 3 squares was required to achieve a passing grade.

[000183] K25 glass microspheres are available from 3M Company.

Example 1

DCPD Resin Formulation (3.5% Trimer)

[000184] A DCPD resin formulation was prepared by blending the modified DCPD (containing 20-25% tricyclopentadiene) with Ultrene[®] 99 DCPD to achieve a tricyclopentadiene level of 3.5% and then adding 2 phr Ethanox[®] 702 antioxidant and 0.06 phr of triphenylphosphine (TPP) inhibitor. ROMP catalyst [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene] dichloro(benzylidene) (tricyclohexylphosphine) ruthenium(II) (**C848**) was mixed into the resin formulation immediately prior to molding at a monomer to catalyst ratio of 30,000:1.

Example 2

Paint Formulation

[000185] A urethane paint formulation was prepared by mixing 15 grams of Polane[®] IMC paint (Sherwin Williams F63GC51), 1 gram Polane[®] B Exterior Catalyst (V66V29), 1 gram Polane[®] HS Plus Warm Weather Reducer (R7K75), and 0.26 grams V70VC130 Mold Release Agent.

Examples 3-5

In-Mold Paint Adhesion Results

[000186] A 6-inch by 6-inch or 13-inch by 13-inch aluminum mold was spray coated with the paint formulation of Example 2. The mold was heated to 40°C and filled with the catalyzed DCPD resin formulation of Example 1 further comprising the additives indicated in Table 1 below. After the resin had cured, paint adhesion was determined by cross hatch testing as described above.

Table 1

Example	Additive	Additive Amt.	Paint Adhesion
3	None	---	Fail
4	5-Norbornene-2-methanol	1.5 phr	Pass
5	9-Octadecene-1,18-diol	0.5 phr	Pass

Example 6

DCPD Resin Formulation (8% Trimer) with Cydecanol Additive

[000187] A DCPD resin formulation was prepared by blending the modified DCPD (containing 20-25% tricyclopentadiene) with Ultrene[®] 99 DCPD to achieve a tricyclopentadiene level of 8% and then adding 2 phr Ethanox[®] 702 antioxidant, 4 phr Kraton G1651 impact modifier, 0.06 phr TPP inhibitor, and 0.05 phr carbon black pigment. This resin was further formulated with 1, 2 and 5 phr of cydecanol. ROMP catalyst [1,3-bis-(2,4,6-trimethylphenyl)-2-imidazolidinylidene]dichloro(3-methyl-2-butenylidene) (tricyclohexylphosphine) ruthenium(II) (C827) was mixed into the resin formulation immediately prior to molding at a monomer to catalyst ratio of 30,000:1. Aluminum molds were spray coated with the paint formulation of Example 2. The molds were heated to 80°C for 10 minutes and then filled with the catalyzed DCPD resin formulations containing 1, 2 and 5 phr of cydecanol. After the resin had cured, paint adhesion was determined by cross hatch testing as described above. All of these samples failed.

Example 7

DCPD Resin Formulation (8% Trimer) with HENB Additive

[000188] A DCPD resin formulation was prepared by blending the modified DCPD (containing 20-25% tricyclopentadiene) with Ultrene[®] 99 DCPD to achieve a tricyclopentadiene level of 8% and then adding 2 phr Ethanox[®] 702 antioxidant, and 4 phr Kraton G1651 impact modifier. This resin was further formulated with 0.75, 1.5 and 3 phr of HENB. ROMP catalyst C827, as a suspension in Renoil 51-W (Whitaker Oil Company), was mixed into the resin formulation immediately prior to molding at a monomer to catalyst ratio of 30,000:1. Aluminum molds were spray coated with the paint formulation of Example 2. The molds were heated to 80°C for 10 minutes and then filled with the catalyzed DCPD resin formulations containing 0.75, 1.5 and 3 phr of HENB. After the resin had cured, paint adhesion was determined by cross hatch testing as described above. All of these samples passed.

Example 8

DCPD Resin Formulation (8% Trimer) with Modified Paint

[000189] A DCPD resin formulation was prepared by blending the modified DCPD (containing 20-25% tricyclopentadiene) with Ultrene[®] 99 DCPD to achieve a tricyclopentadiene level of 8% and then adding 2 phr Ethanox[®] 702 antioxidant, 4 phr Kraton G1651 impact modifier, 0.06 phr TPP inhibitor, and 0.05 phr carbon black pigment. ROMP catalyst C827, as a suspension in soybean oil, was mixed into the resin formulation immediately prior to molding at a monomer to catalyst ratio of 30,000:1. The paint formulation of Example 2 was further modified by the addition of 1 and 5 phr of 5-Norbornene-2-methanol and spray coated onto aluminum molds. The molds were held at 30°C overnight and then heated to 70°C and filled with the catalyzed DCPD resin formulation. After the resin had cured, paint adhesion was determined by cross hatch testing as described above. Both of these samples passed.

Example 9

Syntactic Foam

[000190] A DCPD resin formulation is prepared by blending the modified DCPD (containing 20-25% tricyclopentadiene) with Ultrene[®] 99 DCPD to achieve a tricyclopentadiene level of 8% and then adding 2 phr Ethanox[®] 702 antioxidant, 0.6 phr TPP inhibitor, 1.5 phr of HENB, and K25 glass microspheres (56% by volume). ROMP catalyst C827, as a suspension in Renoil 51-W (Whitaker Oil Company), is mixed into the resin formulation immediately prior to molding at a monomer to catalyst ratio of 60,000:1. Aluminum molds are spray coated with the paint formulation of Example 2. The molds are filled with the

catalyzed resin formulation and heated from room temperature to 75°C at a heating rate of 1°C/min, and then heated to 120°C and held at that temperature for two hours. After the resin cures, the syntactic foam is demolded and paint adhesion is determined by cross hatch testing as described above.

Example 10

Polymer Glass Fiber Composite

[000191] A DCPD resin formulation is prepared by blending the modified DCPD (containing 20-25% tricyclopentadiene) with Ultrene[®] 99 DCPD to achieve a tricyclopentadiene level of 8% and then adding 2 phr Ethanox[®] 702 antioxidant, 1.5 phr of HENB, and 0.6 phr TPP inhibitor. ROMP catalyst C827, as a suspension in Renoil 51-W (Whitaker Oil Company), is mixed into the resin formulation immediately prior to use at a monomer to catalyst ratio of 45,000:1. An aluminum mold is spray coated with the paint formulation of Example 2. A glass composite laminate is prepared using the VARTM process. The laminate is constructed by cutting and arranging plies of glass fabric on the spray coated aluminum mold to achieve approximately 50% fiber volume at 1/8" thickness. A rigid plate is placed on top of the ply stack to ensure that pressure is applied evenly across the surface. Using braided tubing, an infusion inlet and outlet vent are positioned appropriately near the glass fabric. A sheet of vacuum bagging film and tacky tape is used to create an air-tight cover on the glass and the tubing and the bagged laminate is evacuated to a vacuum level of between 25 inches-Hg to 28 inches-Hg. The catalyzed resin mixture is infused in to the glass fabric, driven by the pressure gradient between the ambient pressure and the evacuated glass fabric assembly. After the infusion is complete, the composite laminate is heated from room temperature to 75°C at a heating rate of 1°C/min, and then the composite laminate is heated to 120°C and held at that temperature for two hours. After the resin cures, the polymer composite is debagged and paint adhesion is determined by cross hatch testing as described above.

Example 11

Polymer Carbon Fiber Composite

[000192] A DCPD resin formulation is prepared by blending the modified DCPD (containing 20-25% tricyclopentadiene) with Ultrene[®] 99 DCPD to achieve a tricyclopentadiene level of 8% and then adding 2 phr Ethanox[®] 702 antioxidant, 1.5 phr of HENB, and 0.6 phr TPP inhibitor. ROMP catalyst C827, as a suspension in Renoil 51-W (Whitaker Oil Company), is mixed into the resin formulation immediately prior to use at a monomer to catalyst ratio of 45,000:1. An aluminum mold is spray coated with the paint formulation of Example 2. A carbon composite laminate is prepared using the VARTM process.

The laminate is constructed by cutting and arranging plies of carbon fabric on the spray coated aluminum mold to achieve approximately 50% fiber volume at 1/8" thickness. A rigid plate is placed on top of the ply stack to ensure that pressure is applied evenly across the surface. Using braided tubing, an infusion inlet and outlet vent are positioned appropriately near the carbon fabric. A sheet of vacuum bagging film and tacky tape is used to create an air-tight cover on the carbon fabric and the tubing and the bagged laminate is evacuated to a vacuum level of between 25 inches-Hg to 28 inches-Hg. The catalyzed resin mixture is infused in to the carbon fabric, driven by the pressure gradient between the ambient pressure and the evacuated carbon fabric assembly. After the infusion is complete, the composite laminate is heated from room temperature to 75°C at a heating rate of 1°C/min, and then the composite laminate is heated to 120°C and held at that temperature for two hours. After the resin cures, the polymer composite is debagged and paint adhesion is determined by cross hatch testing as described above.

Example 12

Polymer Glass Fiber Composite

[000193] A first DCPD resin formulation is prepared by blending the modified DCPD (containing 20-25% tricyclopentadiene) with Ultrene[®] 99 DCPD to achieve a tricyclopentadiene level of 8% and then adding 2 phr Ethanox[®] 702 antioxidant, 1.5 phr of HENB, and 0.6 phr TPP inhibitor. ROMP catalyst C827, as a suspension in Renoil 51-W (Whitaker Oil Company), is mixed into the first resin formulation immediately prior to use at a monomer to catalyst ratio of 30,000:1. An aluminum mold is spray coated with the paint formulation of Example 2. The catalyzed first resin formulation is applied to the spray coated aluminum mold, where the catalyzed first resin formulation forms a tie coat. A glass composite laminate is prepared using the VARTM process. The laminate is constructed by cutting and arranging plies of glass fabric on the tie coated surface of the aluminum mold to achieve approximately 50% fiber volume at 1/8" thickness. A rigid plate is placed on top of the ply stack to ensure that pressure is applied evenly across the surface. Using braided tubing, an infusion inlet and outlet vent are positioned appropriately near the glass fabric. A sheet of vacuum bagging film and tacky tape is used to create an air-tight cover on the glass and the tubing and the bagged laminate is evacuated to a vacuum level of between 25 inches-Hg to 28 inches-Hg. A second DCPD resin formulation is prepared by blending the modified DCPD (containing 20-25% tricyclopentadiene) with Ultrene[®] 99 DCPD to achieve a tricyclopentadiene level of 8% and then adding 2 phr Ethanox[®] 702 antioxidant, and 0.6 phr TPP inhibitor. This second resin formulation is optionally

further formulated with 1.5 phr of HENB. ROMP catalyst C827, as a suspension in Renoil 51-W (Whitaker Oil Company), is mixed into the second resin formulation immediately prior to use at a monomer to catalyst ratio of 30,000:1. The catalyzed second resin formulation is infused in to the glass fabric, driven by the pressure gradient between the ambient pressure and the evacuated glass fabric assembly. After the infusion is complete, the composite laminate is heated from room temperature to 75°C at a heating rate of 1°C/min, and then the composite laminate is heated to 120°C and held at that temperature for two hours. After the resin cures, the polymer composite is debagged and paint adhesion is determined by cross hatch testing as described above.

Example 13

Polymer Carbon Fiber Composite


A first DCPD resin formulation is prepared by blending the modified DCPD (containing 20-25% tricyclopentadiene) with Ultrene[®] 99 DCPD to achieve a tricyclopentadiene level of 8% and then adding 2 phr Ethanox[®] 702 antioxidant, 1.5 phr of HENB, and 0.6 phr TPP inhibitor. ROMP catalyst C827, as a suspension in Renoil 51-W (Whitaker Oil Company), is mixed into the first resin formulation immediately prior to use at a monomer to catalyst ratio of 30,000:1. An aluminum mold is spray coated with the paint formulation of Example 2. The catalyzed first resin formulation is applied to the spray coated aluminum mold, where the catalyzed first resin formulation forms a tie coat. A carbon composite laminate is prepared using the VARTM process. The laminate is constructed by cutting and arranging plies of carbon fabric on the tie coated surface of the aluminum mold to achieve approximately 50% fiber volume at 1/8" thickness. A rigid plate is placed on top of the ply stack to ensure that pressure is applied evenly across the surface. Using braided tubing, an infusion inlet and outlet vent are positioned appropriately near the carbon fabric. A sheet of vacuum bagging film and tacky tape is used to create an air-tight cover on the carbon fabric and the tubing and the bagged laminate is evacuated to a vacuum level of between 25 inches-Hg to 28 inches-Hg. A second DCPD resin formulation is prepared by blending the modified DCPD (containing 20-25% tricyclopentadiene) with Ultrene[®] 99 DCPD to achieve a tricyclopentadiene level of 8% and then adding 2 phr Ethanox[®] 702 antioxidant, and 0.6 phr TPP inhibitor. This second resin formulation is optionally further formulated with 1.5 phr of HENB. ROMP catalyst C827, as a suspension in Renoil 51-W (Whitaker Oil Company), is mixed into the second resin formulation immediately prior to use at a monomer to catalyst ratio of 30,000:1. The catalyzed second resin formulation is infused in to the

carbon fabric, driven by the pressure gradient between the ambient pressure and the evacuated carbon fabric assembly. After the infusion is complete, the composite laminate is heated from room temperature to 75°C at a heating rate of 1°C/min, and then the composite laminate is heated to 120°C and held at that temperature for two hours. After the resin cures, the polymer composite is debagged and paint adhesion is determined by cross hatch testing as described above.

What is claimed is:

1. A composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound,

wherein the at least one in-mold coating adhesion compound is a compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin having the structure:



wherein:

O^M is a metathesis active olefin fragment selected from cyclic olefins or acyclic olefins;

Q^* is a linker group selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, substituted heteroatom-containing hydrocarbylene, or $-(CO)-$;

n is zero or 1; and

X^* is selected from oxygen, sulfur, or a heteroatom-containing fragment, wherein the heteroatom-containing fragment is selected from $N(R^X)$, $P(R^X)$, $OP(R^X)$, $OP(R^X)O$, $OP(OR^X)O$, $P(=O)(R^X)$, $OP(=O)(R^X)$, $OP(=O)(R^X)O$, $OP(=O)(OR^X)O$, $Si(R^X)_2$, $Si(R^X)_2O$, $Si(OR^X)_2O$, or $Si(R^X)(OR^X)O$, wherein each R^X is independently selected from hydrogen, hydrocarbyl, or substituted hydrocarbyl.

2. The composition of claim 1, further comprising at least one paint.

3. The composition of claims 1 or 2, further comprising at least one primer.


4. The composition of any one of claims 1-3, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is selected from 5-norbornene-2-methanol, 2-hydroxyethyl bicyclo[2.2.1]hept-2-ene-carboxylate, 2-hydroxyethyl acrylate, allyl alcohol, oleyl alcohol, 9-decen-1-ol, vinyl alcohol, cis-13-dodecenol, trans-9-octadecenol, norbornyl alcohol, 2-cycloocten-1-ol, 2-cyclooctadiene-1-ol, p-vinyl phenol,

2-hydroxyethyl methacrylate, 2-hydroxy-3-acryloxypropyl methacrylate, ethoxylated hydroxyethyl acrylate, ethoxylated hydroxyethyl methacrylate, polypropyleneglycol monomethacrylate, polypropylene glycol monoacrylate, phenol acrylate, phenol methacrylate, bisphenol A type epoxy acrylate, novolac type epoxy acrylate, brominated bisphenol A type epoxy acrylate, allyl amine, diallyl amine, olelyl amine, bicyclo[2.2.1]hept-2-ene-5-methylamine, 5-norbornenyl-2-methylamine, 9-octadecene-1,18-diol, or combinations thereof.

5. The composition of any one of claims 1-4, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is selected from 5-norbornene-2-methanol, 2-hydroxyethyl bicyclo[2.2.1]hept-2-ene-carboxylate, 9-octadecene-1,18-diol, or combinations thereof.

6. The composition of any one of claims 1-5, wherein the at least one olefin metathesis catalyst is selected from osmium olefin metathesis catalysts or ruthenium olefin metathesis catalysts.

7. The composition of any one of claims 1-5, wherein the at least one olefin metathesis catalyst is selected from complexes having the structure of formula (I):



wherein:

M is a Group 8 transition metal;

L^1 , L^2 , and L^3 are independently selected from neutral electron donor ligands;

n is 0 or 1, such that L^3 may or may not be present;

m is 0, 1, or 2;


k is 0 or 1;

X^1 and X^2 are independently anionic ligands; and

R¹ and R² are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, substituted heteroatom-containing hydrocarbyl, and functional groups;

wherein any two or more of X¹, X², L¹, L², L³, R¹, and R² can be taken together to form one or more cyclic groups, and further wherein any one or more of X¹, X², L¹, L², L³, R¹, and R² may be attached to a support.

8. The composition of claim 7, wherein the at least one olefin metathesis catalyst is selected from complexes wherein L¹ is a carbene ligand having the structure of formula (II):



wherein:

X and Y are independently selected from C, N, O, S, and P;

p is zero when X is O or S, and p is 1 when X is N or P;

q is zero when Y is O or S, and q is 1 when Y is N or P;

Q¹, Q², Q³, and Q⁴ are independently selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, substituted heteroatom-containing hydrocarbylene, and -(CO)-, and further wherein two or more substituents on adjacent atoms within Q may be linked to form an additional cyclic group;

w, x, y, and z are independently zero or 1; and

R³, R^{3A}, R⁴, and R^{4A} are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, and substituted heteroatom-containing hydrocarbyl,

wherein any two or more of R³, R^{3A}, R⁴, R^{4A}, Q¹, Q², Q³, and Q⁴ can be taken together to form a cyclic group, and further wherein any one or more of Q¹, Q², Q³, Q⁴, R³, R^{3A}, R⁴, and R^{4A} may be attached to a support.

9. The composition of claim 7, wherein the at least one olefin metathesis catalyst is selected from complexes wherein at least one of L¹, L², and L³ is an N-heterocyclic carbene ligand.

10. The composition of any one of claims 1-9, wherein the at least one cyclic olefin is selected from strained cyclic olefins, unstrained cyclic olefins, or combinations thereof, wherein the cyclic olefin may contain a functional group, or be substituted with a group, selected from halogen, hydroxyl, hydrocarbyl, alkoxy, alkenyloxy, alkynyloxy, aryloxy, aralkyloxy, alkaryloxy, acyl, acyloxy, alkoxy-carbonyl, alkylcarbonato, arylcarbonato, carboxy, carboxylato, carbamoyl, alkyl-substituted carbamoyl, haloalkyl-substituted carbamoyl, aryl-substituted carbamoyl, thiocarbamoyl alkyl-substituted thiocarbamoyl, aryl-substituted thiocarbamoyl, carbamido, cyano, cyanato, thiocyanato, formyl, thioformyl, amino, alkyl-substituted amino, aryl-substituted amino, alkylamido, arylamido, imino, alkylimino, arylimino, nitro, nitroso, sulfo, sulfonato, alkylsulfanyl, arylsulfanyl, alkylsulfinyl, arylsulfinyl, alkylsulfonyl, alkylaminosulfonyl, arylsulfonyl, boryl, borono, boronato, phosphono, phosphonato, phosphinato, phospho, phosphino, or a combination thereof.

11. The composition of any one of claims 1-10, wherein the at least one cyclic olefin is selected from the group consisting of dicyclopentadiene; tricyclopentadiene; dicyclohexadiene; norbornene; 5-methyl-2-norbornene; 5-ethyl-2-norbornene; 5-isobutyl-2-norbornene; 5,6-dimethyl-2-norbornene; 5-phenylnorbornene; 5-benzylnorbornene; 5-acetylnorbornene; 5-methoxycarbonylnorbornene; 5-ethoxycarbonyl-1-norbornene; 5-methyl-5-methoxycarbonylnorbornene; 5-cyanonorbornene; 5,5,6-trimethyl-2-norbornene; cyclohexenylnorbornene; endo, exo-5,6-dimethoxynorbornene; endo, endo-5,6-dimethoxynorbornene; endo, exo-5,6-dimethoxycarbonylnorbornene; endo, endo-5,6-dimethoxycarbonylnorbornene; 2,3-dimethoxynorbornene; norbornadiene; tricycloundecene; tetracyclododecene; 8-methyltetracyclododecene; 8-ethyltetracyclododecene; 8-methoxycarbonyltetracyclododecene; 8-methyl-8-tetracyclododecene; 8-cyanotetracyclododecene; pentacyclopentadecene; pentacyclohexadecene; cyclopentadiene tetramer, cyclopentadiene pentamer; 5-butyl-2-norbornene; 5-hexyl-2-norbornene; 5-octyl-2-


norbornene; 5-decyl-2-norbornene; 5-dodecyl-2-norbornene; 5-vinyl-2-norbornene; 5-ethylidene-2-norbornene; 5-isopropenyl-2-norbornene; 5-propenyl-2-norbornene; 5-butenyl-2-norbornene, and mixtures thereof.

12. The composition of any one of claims 1-11, wherein the at least one cyclic olefin is selected from the group consisting of dicyclopentadiene, tricyclopentadiene, cyclopentadiene tetramer, cyclopentadiene pentamer, tetracyclododecene, norbornene, 5-butyl-2-norbornene, 5-hexyl-2-norbornene, 5-octyl-2-norbornene, 5-decyl-2-norbornene, 5-dodecyl-2-norbornene, 5-vinyl-2-norbornene, 5-ethylidene-2-norbornene, 5-isopropenyl-2-norbornene, 5-propenyl-2-norbornene, 5-butenyl-2-norbornene, and mixtures thereof.

13. A method of in-mold coating a ROMP polymer, comprising:
providing a paint;
applying the paint to a mold surface to form a painted mold surface;
providing primer;
applying the primer to the painted mold surface;
contacting the painted and primed mold surface with a resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound; and

subjecting the resin composition to conditions effective to polymerize the resin composition forming an in-mold coating ROMP polymer,

wherein the at least one in-mold coating adhesion compound is a compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin having the structure:



wherein:

O^M is a metathesis active olefin fragment selected from cyclic olefins or acyclic olefins;

Q* is a linker group selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, substituted heteroatom-containing hydrocarbylene, or $-(CO)-$;

n is zero or 1; and

X* is selected from oxygen, sulfur, or a heteroatom-containing fragment, wherein the heteroatom-containing fragment is selected from $N(R^X)$, $P(R^X)$, $OP(R^X)$, $OP(R^X)O$, $OP(OR^X)O$, $P(=O)(R^X)$, $OP(=O)(R^X)$, $OP(=O)(R^X)O$, $OP(=O)(OR^X)O$, $Si(R^X)_2$, $Si(R^X)_2O$, $Si(OR^X)_2O$, or $Si(R^X)(OR^X)O$, wherein each R^X is independently selected from hydrogen, hydrocarbyl, or substituted hydrocarbyl.

14. The method of claim 13, where the paint is a urethane-based paint.

15. The method of claims 13 or 14, where the primer is a urethane-based primer.


16. The method of any one of claims 13-15, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is selected from 5-norbornene-2-methanol, 2-hydroxyethyl bicyclo[2.2.1]hept-2-ene-carboxylate, 2-hydroxyethyl acrylate, allyl alcohol, oleyl alcohol, 9-decen-1-ol, vinyl alcohol, cis-13-dodecenol, trans-9-octadecenol, norbornyl alcohol, 2-cycloocten-1-ol, 2-cyclooctadiene-1-ol, p-vinyl phenol, 2-hydroxyethyl methacrylate, 2-hydroxy-3-acryloxypropyl methacrylate, ethoxylated hydroxyethyl acrylate, ethoxylated hydroxyethyl methacrylate, polypropyleneglycol monomethacrylate, polypropylene glycol monoacrylate, phenol acrylate, phenol methacrylate, bisphenol A type epoxy acrylate, novolac type epoxy acrylate, brominated bisphenol A type epoxy acrylate, allyl amine, diallyl amine, oleyl amine, bicyclo[2.2.1]hept-2-ene-5-methylamine, 5-norbornenyl-2-methylamine, 9-octadecene-1,18-diol, or combinations thereof.

17. The method of any one of claims 13-16, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is selected

from 5-norbornene-2-methanol, 2-hydroxyethyl bicyclo[2.2.1]hept-2-ene-carboxylate, 9-octadecene-1,18-diol, or combinations thereof.

18. The method of any one of claims 13-17, wherein the at least one olefin metathesis catalyst is selected from osmium olefin metathesis catalysts or ruthenium olefin metathesis catalysts.

19. The method of any one of claims 13-17, wherein the at least one olefin metathesis catalyst is selected from complexes having the structure of formula (I):



wherein:

M is a Group 8 transition metal;

L^1 , L^2 , and L^3 are independently selected from neutral electron donor ligands;

n is 0 or 1, such that L^3 may or may not be present;

m is 0, 1, or 2;


k is 0 or 1;

X^1 and X^2 are independently anionic ligands; and

R^1 and R^2 are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, substituted heteroatom-containing hydrocarbyl, and functional groups;

wherein any two or more of X^1 , X^2 , L^1 , L^2 , L^3 , R^1 , and R^2 can be taken together to form one or more cyclic groups, and further wherein any one or more of X^1 , X^2 , L^1 , L^2 , L^3 , R^1 , and R^2 may be attached to a support.

20. The method of claim 19, wherein the at least one olefin metathesis catalyst is selected from complexes wherein L^1 is a carbene ligand having the structure of formula (II):



wherein:

X and Y are independently selected from C, N, O, S, and P;

p is zero when X is O or S, and p is 1 when X is N or P;

q is zero when Y is O or S, and q is 1 when Y is N or P;

Q¹, Q², Q³, and Q⁴ are independently selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, substituted heteroatom-containing hydrocarbylene, and -(CO)-, and further wherein two or more substituents on adjacent atoms within Q may be linked to form an additional cyclic group;

w, x, y, and z are independently zero or 1; and

R³, R^{3A}, R⁴, and R^{4A} are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, and substituted heteroatom-containing hydrocarbyl,

wherein any two or more of R³, R^{3A}, R⁴, R^{4A}, Q¹, Q², Q³, and Q⁴ can be taken together to form a cyclic group, and further wherein any one or more of Q¹, Q², Q³, Q⁴, R³, R^{3A}, R⁴, and R^{4A} may be attached to a support.

21. The method of claim 19, wherein the at least one olefin metathesis catalyst is selected from complexes wherein at least one of L¹, L², and L³ is an N-heterocyclic carbene ligand.

22. The method of any one of claims 13-21, wherein the at least one cyclic olefin is selected from strained cyclic olefins, unstrained cyclic olefins, or combinations thereof, wherein the cyclic olefin may contain a functional group, or be substituted with a group, selected from halogen, hydroxyl, hydrocarbyl, alkoxy, alkenyloxy, alkynyloxy, aryloxy, aralkyloxy, alkaryloxy, acyl, acyloxy, alkoxycarbonyl, alkylcarbonato, arylcarbonato, carboxy, carboxylato, carbamoyl, alkyl-substituted carbamoyl, haloalkyl-substituted carbamoyl, aryl-substituted carbamoyl,


thiocarbamoyl alkyl-substituted thiocarbamoyl, aryl-substituted thiocarbamoyl, carbamido, cyano, cyanato, thiocyanato, formyl, thioformyl, amino, alkyl-substituted amino, aryl-substituted amino, alkylamido, arylamido, imino, alkylimino, arylimino, nitro, nitroso, sulfo, sulfonato, alkylsulfanyl, arylsulfanyl, alkylsulfinyl, arylsulfinyl, alkylsulfonyl, alkylaminosulfonyl, arylsulfonyl, boryl, borono, boronato, phosphono, phosphonato, phosphinato, phospho, phosphino, or a combination thereof.

23. The method of any one of claims 13-22, wherein the at least one cyclic olefin is selected from the group consisting of dicyclopentadiene; tricyclopentadiene; dicyclohexadiene; norbornene; 5-methyl-2-norbornene; 5-ethyl-2-norbornene; 5-isobutyl-2-norbornene; 5,6-dimethyl-2-norbornene; 5-phenylnorbornene; 5-benzylnorbornene; 5-acetylnorbornene; 5-methoxycarbonylnorbornene; 5-ethoxycarbonyl-1-norbornene; 5-methyl-5-methoxycarbonylnorbornene; 5-cyanonorbornene; 5,5,6-trimethyl-2-norbornene; cyclohexenylnorbornene; endo, exo-5,6-dimethoxynorbornene; endo, endo-5,6-dimethoxynorbornene; endo, exo-5,6-dimethoxycarbonylnorbornene; endo, endo-5,6-dimethoxycarbonylnorbornene; 2,3-dimethoxynorbornene; norbornadiene; tricycloundecene; tetracyclododecene; 8-methyltetracyclododecene; 8-ethyltetracyclododecene; 8-methoxycarbonyltetracyclododecene; 8-methyl-8-tetracyclododecene; 8-cyanotetracyclododecene; pentacyclopentadecene; pentacyclohexadecene; cyclopentadiene tetramer, cyclopentadiene pentamer; 5-butyl-2-norbornene; 5-hexyl-2-norbornene; 5-octyl-2-norbornene; 5-decyl-2-norbornene; 5-dodecyl-2-norbornene; 5-vinyl-2-norbornene; 5-ethylidene-2-norbornene; 5-isopropenyl-2-norbornene; 5-propenyl-2-norbornene; 5-butenyl-2-norbornene, and mixtures thereof.

24. The method of any one of claims 13-23, wherein the at least one cyclic olefin is selected from the group consisting of dicyclopentadiene, tricyclopentadiene, cyclopentadiene tetramer, cyclopentadiene pentamer, tetracyclododecene, norbornene, 5-butyl-2-norbornene, 5-hexyl-2-norbornene, 5-octyl-2-norbornene, 5-decyl-2-norbornene, 5-dodecyl-2-norbornene, 5-vinyl-2-

norbornene, 5-ethylidene-2-norbornene, 5-isopropenyl-2-norbornene, 5-propenyl-2-norbornene, 5-butenyl-2-norbornene, and mixtures thereof.

25. A method of in-mold coating a ROMP polymer, comprising:
- providing a primer;
 - applying the primer to a mold surface to form a primered mold surface;
 - contacting the primered mold surface with a resin composition comprising at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound; and
 - subjecting the resin composition to conditions effective to polymerize the resin composition forming an in-mold coating ROMP polymer,
- wherein the at least one in-mold coating adhesion compound is a compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin having the structure:



wherein:

- O^M is a metathesis active olefin fragment selected from cyclic olefins or acyclic olefins;
- Q^* is a linker group selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, substituted heteroatom-containing hydrocarbylene, or $-(CO)-$;
- n is zero or 1; and
- X^* is selected from oxygen, sulfur, or a heteroatom-containing fragment, wherein the heteroatom-containing fragment is selected from $N(R^X)$, $P(R^X)$, $OP(R^X)$, $OP(R^X)O$, $OP(OR^X)O$, $P(=O)(R^X)$, $OP(=O)(R^X)$, $OP(=O)(R^X)O$, $OP(=O)(OR^X)O$, $Si(R^X)_2$, $Si(R^X)_2O$, $Si(OR^X)_2O$, or $Si(R^X)(OR^X)O$, wherein each R^X is independently selected from hydrogen, hydrocarbyl, or substituted hydrocarbyl.


26. The method of claim 25, where the primer is a urethane-based primer.

27. The method of claims 25 or 26, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is selected from 5-norbornene-2-methanol, 2-hydroxyethyl bicyclo[2.2.1]hept-2-ene-carboxylate, 2-hydroxyethyl acrylate, allyl alcohol, oleyl alcohol, 9-decen-1-ol, vinyl alcohol, cis-13-dodecenol, trans-9-octadecenol, norbornyl alcohol, 2-cycloocten-1-ol, 2-cyclooctadiene-1-ol, p-vinyl phenol, 2-hydroxyethyl methacrylate, 2-hydroxy-3-acryloxypropyl methacrylate, ethoxylated hydroxyethyl acrylate, ethoxylated hydroxyethyl methacrylate, polypropyleneglycol monomethacrylate, polypropylene glycol monoacrylate, phenol acrylate, phenol methacrylate, bisphenol A type epoxy acrylate, novolac type epoxy acrylate, brominated bisphenol A type epoxy acrylate, allyl amine, diallyl amine, oleyl amine, bicyclo[2.2.1]hept-2-ene-5-methylamine, 5-norbornenyl-2-methylamine, 9-octadecene-1,18-diol, or combinations thereof.

28. The method of any one of claims 25-27, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is selected from 5-norbornene-2-methanol, 2-hydroxyethyl bicyclo[2.2.1]hept-2-ene-carboxylate, 9-octadecene-1,18-diol, or combinations thereof.

29. The method of any one of claims 25-28, wherein the at least one olefin metathesis catalyst is selected from osmium olefin metathesis catalysts or ruthenium olefin metathesis catalysts.

30. The method of any one of claims 25-28, wherein the at least one olefin metathesis catalyst is selected from complexes having the structure of formula (I):



wherein:

M is a Group 8 transition metal;

L^1 , L^2 , and L^3 are independently selected from neutral electron donor ligands;

n is 0 or 1, such that L³ may or may not be present;

m is 0, 1, or 2;


k is 0 or 1;

X¹ and X² are independently anionic ligands; and

R¹ and R² are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, substituted heteroatom-containing hydrocarbyl, and functional groups;

wherein any two or more of X¹, X², L¹, L², L³, R¹, and R² can be taken together to form one or more cyclic groups, and further wherein any one or more of X¹, X², L¹, L², L³, R¹, and R² may be attached to a support.

31. The method of claim 30, wherein the at least one olefin metathesis catalyst is selected from complexes wherein L¹ is a carbene ligand having the structure of formula (II):



wherein:

X and Y are independently selected from C, N, O, S, and P;

p is zero when X is O or S, and p is 1 when X is N or P;

q is zero when Y is O or S, and q is 1 when Y is N or P;

Q¹, Q², Q³, and Q⁴ are independently selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, substituted heteroatom-containing hydrocarbylene, and -(CO)-, and further wherein two or more substituents on adjacent atoms within Q may be linked to form an additional cyclic group;

w, x, y, and z are independently zero or 1; and

R³, R^{3A}, R⁴, and R^{4A} are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, and substituted heteroatom-containing hydrocarbyl,

wherein any two or more of R^3 , R^{3A} , R^4 , R^{4A} , Q^1 , Q^2 , Q^3 , and Q^4 can be taken together to form a cyclic group, and further wherein any one or more of Q^1 , Q^2 , Q^3 , Q^4 , R^3 , R^{3A} , R^4 , and R^{4A} may be attached to a support.

32. The method of claim 30, wherein the at least one olefin metathesis catalyst is selected from complexes wherein at least one of L^1 , L^2 , and L^3 is an N-heterocyclic carbene ligand.

33. The method of any one of claims 25-32, wherein the at least one cyclic olefin is selected from strained cyclic olefins, unstrained cyclic olefins, or combinations thereof, wherein the cyclic olefin may contain a functional group, or be substituted with a group, selected from halogen, hydroxyl, hydrocarbyl, alkoxy, alkenyloxy, alkynyloxy, aryloxy, aralkyloxy, alkaryloxy, acyl, acyloxy, alkoxy-carbonyl, alkylcarbonato, arylcarbonato, carboxy, carboxylato, carbamoyl, alkyl-substituted carbamoyl, haloalkyl-substituted carbamoyl, aryl-substituted carbamoyl, thiocarbamoyl, alkyl-substituted thiocarbamoyl, aryl-substituted thiocarbamoyl, carbamido, cyano, cyanato, thiocyanato, formyl, thioformyl, amino, alkyl-substituted amino, aryl-substituted amino, alkylamido, arylamido, imino, alkylimino, arylimino, nitro, nitroso, sulfo, sulfonato, alkylsulfanyl, arylsulfanyl, alkylsulfinyl, arylsulfinyl, alkylsulfonyl, alkylaminosulfonyl, arylsulfonyl, boryl, borono, boronato, phosphono, phosphonato, phosphinato, phospho, phosphino, or a combination thereof.


34. The method of any one of claims 25-33, wherein the at least one cyclic olefin is selected from the group consisting of dicyclopentadiene; tricyclopentadiene; dicyclohexadiene; norbornene; 5-methyl-2-norbornene; 5-ethyl-2-norbornene; 5-isobutyl-2-norbornene; 5,6-dimethyl-2-norbornene; 5-phenylnorbornene; 5-benzyl-norbornene; 5-acetylnorbornene; 5-methoxycarbonylnorbornene; 5-ethoxycarbonyl-1-norbornene; 5-methyl-5-methoxycarbonylnorbornene; 5-cyanonorbornene; 5,5,6-trimethyl-2-norbornene; cyclohexenylnorbornene; endo, exo-5,6-dimethoxynorbornene; endo, endo-5,6-dimethoxynorbornene; endo, exo-5,6-dimethoxycarbonylnorbornene; endo, endo-5,6-dimethoxycarbonylnorbornene; 2,3-dimethoxynorbornene; norbornadiene; tricycloundecene;

tetracyclododecene; 8-methyltetracyclododecene; 8-ethyltetracyclododecene; 8-methoxycarbonyltetracyclododecene; 8-methyl-8-tetracyclododecene; 8-cyanotetracyclododecene; pentacyclopentadecene; pentacyclohexadecene; cyclopentadiene tetramer, cyclopentadiene pentamer; 5-butyl-2-norbornene; 5-hexyl-2-norbornene; 5-octyl-2-norbornene; 5-decyl-2-norbornene; 5-dodecyl-2-norbornene; 5-vinyl-2-norbornene; 5-ethylidene-2-norbornene; 5-isopropenyl-2-norbornene; 5-propenyl-2-norbornene; 5-butenyl-2-norbornene, and mixtures thereof.

35. The method of any one of claims 25-34, wherein the at least one cyclic olefin is selected from the group consisting of dicyclopentadiene, tricyclopentadiene, cyclopentadiene tetramer, cyclopentadiene pentamer, tetracyclododecene, norbornene, 5-butyl-2-norbornene, 5-hexyl-2-norbornene, 5-octyl-2-norbornene, 5-decyl-2-norbornene, 5-dodecyl-2-norbornene, 5-vinyl-2-norbornene, 5-ethylidene-2-norbornene, 5-isopropenyl-2-norbornene, 5-propenyl-2-norbornene, 5-butenyl-2-norbornene, and mixtures thereof.

36. An article of manufacture comprising an in-mold coated ROMP polymer, where the in-mold coated ROMP polymer comprises a polymerized resin composition and an adherent coating thereon, where the polymerized resin composition comprises at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound; and the adherent coating comprises a paint, a primer, or combination thereof,

wherein the at least one in-mold coating adhesion compound is a compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin having the structure:



wherein:

O^M is a metathesis active olefin fragment selected from cyclic olefins or acyclic olefins;
 Q^* is a linker group selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, substituted heteroatom-containing hydrocarbylene, or $-(CO)-$;

n is zero or 1; and

X* is selected from oxygen, sulfur, or a heteroatom-containing fragment, wherein the heteroatom-containing fragment is selected from N(R^x), P(R^x), OP(R^x), OP(R^x)O, OP(OR^x)O, P(=O)(R^x), OP(=O)(R^x), OP(=O)(R^x)O, OP(=O)(OR^x)O, Si(R^x)₂, Si(R^x)₂O, Si(OR^x)₂O, or Si(R^x)(OR^x)O, wherein each R^x is independently selected from hydrogen, hydrocarbyl, or substituted hydrocarbyl.

37. The article of claim 36, wherein the paint is a urethane-based paint.


38. The article of claims 36 or 37, where the primer is a urethane-based primer.

39. The article of any one of claims 36-38, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is selected from 5-norbornene-2-methanol, 2-hydroxyethyl bicyclo[2.2.1]hept-2-ene-carboxylate, 2-hydroxyethyl acrylate, allyl alcohol, oleyl alcohol, 9-decen-1-ol, vinyl alcohol, cis-13-dodecenol, trans-9-octadecenol, norbornyl alcohol, 2-cycloocten-1-ol, 2-cyclooctadiene-1-ol, p-vinyl phenol, 2-hydroxyethyl methacrylate, 2-hydroxy-3-acryloxypropyl methacrylate, ethoxylated hydroxyethyl acrylate, ethoxylated hydroxyethyl methacrylate, polypropyleneglycol monomethacrylate, polypropylene glycol monoacrylate, phenol acrylate, phenol methacrylate, bisphenol A type epoxy acrylate, novolac type epoxy acrylate, brominated bisphenol A type epoxy acrylate, allyl amine, diallyl amine, oleyl amine, bicyclo[2.2.1]hept-2-ene-5-methylamine, 5-norbornenyl-2-methylamine, 9-octadecene-1,18-diol, or combinations thereof.

40. The article of any one of claims 36-39, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is selected from 5-norbornene-2-methanol, 2-hydroxyethyl bicyclo[2.2.1]hept-2-ene-carboxylate, 9-octadecene-1,18-diol, or combinations thereof.

41. The article of any one of claims 36-40, wherein the at least one olefin metathesis catalyst is selected from osmium olefin metathesis catalysts or ruthenium olefin metathesis catalysts.

42. The article of any one of claims 36-40, wherein the at least one olefin metathesis catalyst is selected from complexes having the structure of formula (I):



wherein:

M is a Group 8 transition metal;

L^1 , L^2 , and L^3 are independently selected from neutral electron donor ligands;

n is 0 or 1, such that L^3 may or may not be present;

m is 0, 1, or 2;


k is 0 or 1;

X^1 and X^2 are independently anionic ligands; and

R^1 and R^2 are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, substituted heteroatom-containing hydrocarbyl, and functional groups;

wherein any two or more of X^1 , X^2 , L^1 , L^2 , L^3 , R^1 , and R^2 can be taken together to form one or more cyclic groups, and further wherein any one or more of X^1 , X^2 , L^1 , L^2 , L^3 , R^1 , and R^2 may be attached to a support.

43. The article of claim 42, wherein the at least one olefin metathesis catalyst is selected from complexes wherein L^1 is a carbene ligand having the structure of formula (II):



wherein:

X and Y are independently selected from C, N, O, S, and P;

p is zero when X is O or S, and p is 1 when X is N or P;

q is zero when Y is O or S, and q is 1 when Y is N or P;

Q¹, Q², Q³, and Q⁴ are independently selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, substituted heteroatom-containing hydrocarbylene, and -(CO)-, and further wherein two or more substituents on adjacent atoms within Q may be linked to form an additional cyclic group;

w, x, y, and z are independently zero or 1; and

R³, R^{3A}, R⁴, and R^{4A} are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, and substituted heteroatom-containing hydrocarbyl,

wherein any two or more of R³, R^{3A}, R⁴, R^{4A}, Q¹, Q², Q³, and Q⁴ can be taken together to form a cyclic group, and further wherein any one or more of Q¹, Q², Q³, Q⁴, R³, R^{3A}, R⁴, and R^{4A} may be attached to a support.

44. The article of claim 42, wherein the at least one olefin metathesis catalyst is selected from complexes wherein at least one of L¹, L², and L³ is an N-heterocyclic carbene ligand.

45. The article of any one of claims 36-44, wherein the at least one cyclic olefin is selected from strained cyclic olefins, unstrained cyclic olefins, or combinations thereof, wherein the cyclic olefin may contain a functional group, or be substituted with a group, selected from halogen, hydroxyl, hydrocarbyl, alkoxy, alkenyloxy, alkynyloxy, aryloxy, aralkyloxy, alkaryloxy, acyl, acyloxy, alkoxycarbonyl, alkylcarbonato, arylcarbonato, carboxy, carboxylato, carbamoyl, alkyl-substituted carbamoyl, haloalkyl-substituted carbamoyl, aryl-substituted carbamoyl, thiocarbamoyl, alkyl-substituted thiocarbamoyl, aryl-substituted thiocarbamoyl, carbamido, cyano, cyanato, thiocyanato, formyl, thioformyl, amino, alkyl-substituted amino, aryl-substituted amino, alkylamido, arylamido, imino, alkylimino, arylimino, nitro, nitroso, sulfo, sulfonato, alkylsulfanyl, arylsulfanyl, alkylsulfinyl, arylsulfinyl, alkylsulfonyl, alkylaminosulfonyl, arylsulfonyl,

boryl, borono, boronato, phosphono, phosphonato, phosphinato, phospho, phosphino, or a combination thereof.


46. The article of any one of claims 36-45, wherein the at least one cyclic olefin is selected from the group consisting of dicyclopentadiene; tricyclopentadiene; dicyclohexadiene; norbornene; 5-methyl-2-norbornene; 5-ethyl-2-norbornene; 5-isobutyl-2-norbornene; 5,6-dimethyl-2-norbornene; 5-phenylnorbornene; 5-benzylnorbornene; 5-acetylnorbornene; 5-methoxycarbonylnorbornene; 5-ethoxycarbonyl-1-norbornene; 5-methyl-5-methoxycarbonylnorbornene; 5-cyanonorbornene; 5,5,6-trimethyl-2-norbornene; cyclohexenylnorbornene; endo, exo-5,6-dimethoxynorbornene; endo, endo-5,6-dimethoxynorbornene; endo, exo-5-6-dimethoxycarbonylnorbornene; endo, endo-5,6-dimethoxycarbonylnorbornene; 2,3-dimethoxynorbornene; norbornadiene; tricycloundecene; tetracyclododecene; 8-methyltetracyclododecene; 8-ethyltetracyclododecene; 8-methoxycarbonyltetracyclododecene; 8-methyl-8-tetracyclododecene; 8-cyanotetracyclododecene; pentacyclopentadecene; pentacyclohexadecene; cyclopentadiene tetramer, cyclopentadiene pentamer; 5-butyl-2-norbornene; 5-hexyl-2-norbornene; 5-octyl-2-norbornene; 5-decyl-2-norbornene; 5-dodecyl-2-norbornene; 5-vinyl-2-norbornene; 5-ethylidene-2-norbornene; 5-isopropenyl-2-norbornene; 5-propenyl-2-norbornene; 5-butenyl-2-norbornene, and mixtures thereof.

47. The article of any one of claims 36-46, wherein the at least one cyclic olefin is selected from the group consisting of dicyclopentadiene, tricyclopentadiene, cyclopentadiene tetramer, cyclopentadiene pentamer, tetracyclododecene, norbornene, 5-butyl-2-norbornene, 5-hexyl-2-norbornene, 5-octyl-2-norbornene, 5-decyl-2-norbornene, 5-dodecyl-2-norbornene, 5-vinyl-2-norbornene, 5-ethylidene-2-norbornene, 5-isopropenyl-2-norbornene, 5-propenyl-2-norbornene, 5-butenyl-2-norbornene, and mixtures thereof.

48. Use of at least one in-mold coating adhesion compound for adhering a metathesis-polymerized resin composition to a paint, a primer, or a combination thereof, where the

metathesis-polymerized resin composition comprises at least one cyclic olefin, at least one olefin metathesis catalyst, and at least one in-mold coating adhesion compound,

wherein the at least one in-mold coating adhesion compound is a compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin having the structure:



wherein:

O^M is a metathesis active olefin fragment selected from cyclic olefins or acyclic olefins;

Q^* is a linker group selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, substituted heteroatom-containing hydrocarbylene, or $-(CO)-$;

n is zero or 1; and

X^* is selected from oxygen, sulfur, or a heteroatom-containing fragment, wherein the heteroatom-containing fragment is selected from $N(R^X)$, $P(R^X)$, $OP(R^X)$, $OP(R^X)O$, $OP(OR^X)O$, $P(=O)(R^X)$, $OP(=O)(R^X)$, $OP(=O)(R^X)O$, $OP(=O)(OR^X)O$, $Si(R^X)_2$, $Si(R^X)_2O$, $Si(OR^X)_2O$, or $Si(R^X)(OR^X)O$, wherein each R^X is independently selected from hydrogen, hydrocarbyl, or substituted hydrocarbyl.

49. The use of claim 48, wherein the paint is a urethane-based paint.

50. The use of claims 48 or 49, where the primer is a urethane-based primer.


51. The use of any one of claims 48-50, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is selected from 5-norbornene-2-methanol, 2-hydroxyethyl bicyclo[2.2.1]hept-2-ene-carboxylate, 2-hydroxyethyl acrylate, allyl alcohol, oleyl alcohol, 9-decen-1-ol, vinyl alcohol, cis-13-dodecenol, trans-9-octadecenol, norbornyl alcohol, 2-cycloocten-1-ol, 2-cyclooctadiene-1-ol, p-vinyl phenol, 2-hydroxyethyl methacrylate, 2-hydroxy-3-acryloxypropyl methacrylate, ethoxylated hydroxyethyl acrylate, ethoxylated hydroxyethyl methacrylate, polypropyleneglycol

monomethacrylate, polypropylene glycol monoacrylate, phenol acrylate, phenol methacrylate, bisphenol A type epoxy acrylate, novolac type epoxy acrylate, brominated bisphenol A type epoxy acrylate, allyl amine, diallyl amine, olelyl amine, bicyclo[2.2.1]hept-2-ene-5-methylamine, 5-norbornenyl-2-methylamine, 9-octadecene-1,18-diol, or combinations thereof.

52. The use of any one of claims 48-51, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is selected from 5-norbornene-2-methanol, 2-hydroxyethyl bicyclo[2.2.1]hept-2-ene-carboxylate, 9-octadecene-1,18-diol, or combinations thereof.

53. The use of any one of claims 48-52, wherein the at least one olefin metathesis catalyst is selected from osmium olefin metathesis catalysts or ruthenium olefin metathesis catalysts.

54. The use of any one of claims 48-52, wherein the at least one olefin metathesis catalyst is selected from complexes having the structure of formula (I):



wherein:

M is a Group 8 transition metal;

L¹, L², and L³ are independently selected from neutral electron donor ligands;

n is 0 or 1, such that L³ may or may not be present;

m is 0, 1, or 2;


k is 0 or 1;

X¹ and X² are independently anionic ligands; and

R¹ and R² are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, substituted heteroatom-containing hydrocarbyl, and functional groups;

wherein any two or more of X^1 , X^2 , L^1 , L^2 , L^3 , R^1 , and R^2 can be taken together to form one or more cyclic groups, and further wherein any one or more of X^1 , X^2 , L^1 , L^2 , L^3 , R^1 , and R^2 may be attached to a support.

55. The use of claim 54, wherein the at least one olefin metathesis catalyst is selected from complexes wherein L^1 is a carbene ligand having the structure of formula (II):



wherein:

X and Y are independently selected from C, N, O, S, and P;

p is zero when X is O or S, and p is 1 when X is N or P;

q is zero when Y is O or S, and q is 1 when Y is N or P;

Q^1 , Q^2 , Q^3 , and Q^4 are independently selected from hydrocarbylene, substituted hydrocarbylene, heteroatom-containing hydrocarbylene, substituted heteroatom-containing hydrocarbylene, and $-(CO)-$, and further wherein two or more substituents on adjacent atoms within Q may be linked to form an additional cyclic group;

w , x , y , and z are independently zero or 1; and

R^3 , R^{3A} , R^4 , and R^{4A} are independently selected from hydrogen, hydrocarbyl, substituted hydrocarbyl, heteroatom-containing hydrocarbyl, and substituted heteroatom-containing hydrocarbyl,

wherein any two or more of R^3 , R^{3A} , R^4 , R^{4A} , Q^1 , Q^2 , Q^3 , and Q^4 can be taken together to form a cyclic group, and further wherein any one or more of Q^1 , Q^2 , Q^3 , Q^4 , R^3 , R^{3A} , R^4 , and R^{4A} may be attached to a support.

56. The use of claim 54, wherein the at least one olefin metathesis catalyst is selected from complexes wherein at least one of L^1 , L^2 , and L^3 is an N-heterocyclic carbene ligand.

57. The use of any one of claims 48-56, wherein the at least one cyclic olefin is selected from strained cyclic olefins, unstrained cyclic olefins, or combinations thereof, wherein the cyclic olefin may contain a functional group, or be substituted with a group, selected from halogen, hydroxyl, hydrocarbyl, alkoxy, alkenyloxy, alkynyloxy, aryloxy, aralkyloxy, alkaryloxy, acyl, acyloxy, alkoxycarbonyl, alkylcarbonato, arylcarbonato, carboxy, carboxylato, carbamoyl, alkyl-substituted carbamoyl, haloalkyl-substituted carbamoyl, aryl-substituted carbamoyl, thiocarbamoyl alkyl-substituted thiocarbamoyl, aryl-substituted thiocarbamoyl, carbamido, cyano, cyanato, thiocyanato, formyl, thioformyl, amino, alkyl-substituted amino, aryl-substituted amino, alkylamido, arylamido, imino, alkylimino, arylimino, nitro, nitroso, sulfo, sulfonato, alkylsulfanyl, arylsulfanyl, alkylsulfinyl, arylsulfinyl, alkylsulfonyl, alkylaminosulfonyl, arylsulfonyl, boryl, borono, boronato, phosphono, phosphonato, phosphinato, phospho, phosphino, or a combination thereof.

58. The use of any one of claims 48-57, wherein the at least one cyclic olefin is selected from the group consisting of dicyclopentadiene; tricyclopentadiene; dicyclohexadiene; norbornene; 5-methyl-2-norbornene; 5-ethyl-2-norbornene; 5-isobutyl-2-norbornene; 5,6-dimethyl-2-norbornene; 5-phenylnorbornene; 5-benzylnorbornene; 5-acetylnorbornene; 5-methoxycarbonylnorbornene; 5-ethoxycarbonyl-1-norbornene; 5-methyl-5-methoxycarbonylnorbornene; 5-cyanonorbornene; 5,5,6-trimethyl-2-norbornene; cyclohexenylnorbornene; endo, exo-5,6-dimethoxynorbornene; endo, endo-5,6-dimethoxynorbornene; endo, exo-5-6-dimethoxycarbonylnorbornene; endo, endo-5,6-dimethoxycarbonylnorbornene; 2,3-dimethoxynorbornene; norbornadiene; tricycloundecene; tetracyclododecene; 8-methyltetracyclododecene; 8-ethyltetracyclododecene; 8-methoxycarbonyltetracyclododecene; 8-methyl-8-tetracyclododecene; 8-cyanotetracyclododecene; pentacyclopentadecene; pentacyclohexadecene; cyclopentadiene tetramer, cyclopentadiene pentamer; 5-butyl-2-norbornene; 5-hexyl-2-norbornene; 5-octyl-2-norbornene; 5-decyl-2-norbornene; 5-dodecyl-2-norbornene; 5-vinyl-2-norbornene; 5-ethylidene-2-norbornene; 5-isopropenyl-2-norbornene; 5-propenyl-2-norbornene; 5-butenyl-2-norbornene, and mixtures thereof.

59. The use of any one of claims 48-58, wherein the at least one cyclic olefin is selected from the group consisting of dicyclopentadiene, tricyclopentadiene, cyclopentadiene tetramer, cyclopentadiene pentamer, tetracyclododecene, norbornene, 5-butyl-2-norbornene, 5-hexyl-2-norbornene, 5-octyl-2-norbornene, 5-decyl-2-norbornene, 5-dodecyl-2-norbornene, 5-vinyl-2-norbornene, 5-ethylidene-2-norbornene, 5-isopropenyl-2-norbornene, 5-propenyl-2-norbornene, 5-butenyl-2-norbornene, and mixtures thereof.

60. An article prepared by the method of claims 13-24.

61. An article prepared by the method of claims 25-35.

62. The composition of any one of claims 1-12, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.001-50 phr.

63. The composition of claim 62, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.05-10 phr.

64. The composition of claim 63, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.1-10 phr.

65. The composition of claim 64, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.5-4.0 phr.

66. The method of any one of claims 13-24, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.001-50 phr.

67. The method of claim 66, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.05-10 phr.

68. The method of claim 67, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.1-10 phr.

69. The method of claim 68, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.5-4.0 phr.

70. The method of any one of claims 25-35, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.001-50 phr.

71. The method of claim 70, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.05-10 phr.

72. The method of claim 71, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.1-10 phr.

73. The method of claim 72, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.5-4.0 phr.

74. The article of any one of claims 36-47, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.001-50 phr.

75. The article of claim 74, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.05-10 phr.

76. The article of claim 75, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.1-10 phr.

77. The article of claim 76, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.5-4.0 phr.

78. The use of any one of claims 48-59, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.001-50 phr.

79. The article of claim 78, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.05-10 phr.

80. The article of claim 79, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.1-10 phr.

81. The article of claim 80, wherein the compound comprising at least one hetero-atom containing functional group and at least one metathesis active olefin is present in the composition in an amount ranging from 0.5-4.0 phr.