

**(12) PATENT**  
**(19) AUSTRALIAN PATENT OFFICE**

**(11)** Application No. **AU 199746784 B2**  
**(10)** Patent No. **714551**

(54) Title

**Ink container**

(51)<sup>6</sup> International Patent Classification(s)

**B29C 049/22 B41J 002/175**

**B29C 049/00**

(21) Application No: **199746784**

(22) Application Date: **1997.12.01**

(30) Priority Data

(31) Number	(32) Date	(33) Country
7-90895	1995.04.17	JP
7-141947	1995.06.08	JP
8-12876	1996.01.29	JP
8-85251	1996.04.08	JP

(43) Publication Date : **1998.02.12**

(43) Publication Journal Date : **1998.02.12**

(44) Accepted Journal Date : **2000.01.06**

(62) Divisional of:

**199650706**

(71) Applicant(s)

**Canon Kabushiki Kaisha**

(72) Inventor(s)

**Toshiaki Sasaki; Sadayuki Sugama; Hideo Okada**

(74) Agent/Attorney

**SPRUSON and FERGUSON,GPO Box 3898,SYDNEY NSW 2001**

(56) Related Art

**AU 24153/92**


**WO 92/12926**

**WO 92/11187**

## Ink Container

### ABSTRACT

A liquid container (100) includes a substantially prism-like outer wall (101) provided with a substantial air vent portion (105) and having a corner formed by 3 surfaces: an inner wall (102) having outer surfaces equivalent or similar to inside surfaces of the outer wall (101) and a corner ( $\alpha 2$ ) corresponding a corner ( $\alpha 1$ ) of the outer wall, the inner wall (102) defining a liquid accommodating portion for containing liquid therein, the inner wall (102) further having a liquid supply portion (103) for supplying the liquid out of the liquid accommodating portion; wherein the inner wall (102) has a thickness which decreases from a central portion of the surfaces of the prism-like shape to the corner, and the outer wall (101) and the inner wall (102) are separable from each other.



**AUSTRALIA**  
**PATENTS ACT 1990**

**COMPLETE SPECIFICATION**

**FOR A STANDARD PATENT**

**ORIGINAL**

---

Name and Address  
of Applicant: Canon Kabushiki Kaisha  
30-2, Shimomaruko 3-chome  
Ohta-ku  
Tokyo 146  
JAPAN

Actual Inventor(s): Toshiaki Sasaki, Sadayuki Sugama and Hideo Okada

Address for Service: Spruson & Ferguson, Patent Attorneys  
Level 33 St Martins Tower, 31 Market Street  
Sydney, New South Wales, 2000, Australia

Invention Title: Ink Container

The following statement is a full description of this invention, including the best method of performing it known to me/us:-

Ink Container

5

FIELD OF THE INVENTION AND RELATED ART

The present invention relates to a liquid  
accommodating container for supplying liquid out with  
10 a negative pressure to a recording station such as a  
pen, ink ejection portion or the like, a manufacturing  
method for the container, an ink jet cartridge  
containing the container portion and an ink jet  
recording head portion, and an ink jet recording  
15 apparatus, and more particularly, to use of blow  
molding for formation of the ink container per se in  
the field of ink jet recording.

A container for accommodating liquid is known  
wherein the liquid is supplied out of the container  
20 while maintaining a negative pressure within the  
container. Such a container performs appropriate  
liquid supply for the liquid using portion such as a  
nib or tip of a pen or recording head connected to the  
container, by the negative pressure produced by the  
25 container per se.

Various liquid accommodating containers of  
this type are used, but the usable ranges thereof are

rather limited. One of the reasons for this is that there has not been an one easy to manufacture and having a simple structure.

For example, in the field of the ink jet  
5 recording requiring a proper negative pressure  
property, a container having a sponge therein as a  
generation source for the negative pressure or a  
bladder-like container having a spring providing force  
10 of the ink, as disclosed in Japanese Laid Open Patent  
Application No. SHO- 56-67269, Japanese Laid Open  
Patent Application No. HEI- 6-226993, for example.  
U.S. Patent No. 4, 509, 062 discloses an ink  
accommodation portion of rubber having a conical  
15 configuration with a rounded top having a smaller  
thickness than the other portion. The round thinner  
portion of the circular cone portion provides a  
portion which displaces and deforms earlier than the  
other portion. These examples have been put into  
20 practice, and are satisfactory at present.

However, the negative pressure generating  
mechanisms described above is relatively expensive,  
and therefore, does not suit for the writing devices  
such as markers, plotters having writing tips. The  
25 use of the complicated negative pressure generating  
mechanism is not desirable since it result in  
bulkiness of the writing device.

In writing devices, the use is made with a felt capable of generating a negative pressure and of introducing the air from the tip to permit supply of the ink thereto. The main problem of this type of the gas-liquid exchange structure for the ink supply is the ink leakage at the tip. In order to solve this problem, an ink retaining mechanism has been proposed wherein a great number of fins are formed at predetermined intervals between the tip and the liquid accommodating container extending in a direction perpendicular to the ink supply direction, for the purpose of preventing the ink leakage by retaining the ink which is going to leak upon the ambient condition change or the like. However, such a mechanism results in a relatively large amount of non-usable ink remaining in the container.

The ink supplying system of such writing devices, generally uses an open type, which leads to evaporation of the ink, with the result of reduction of the usable amount of the ink. Therefore, ink evaporation suppression by using substantial sealed type is desirable.

The description will be made briefly about the substantially sealed type in the ink jet recording. When a negative pressure generation source is not used in an ink supplying system, the ink is supplied using the level difference relative to the

ink using portion(ink ejection head), that is, the static head difference. This does not require any special condition in the ink accommodation portion, and therefore, a simple ink accommodation bladder is  
5 used in many cases.

However, in order to use a closed system, the ink supply path has to extend between the ink accommodation bladder to the ink using portion(ink ejection head) thereabove with the result that a long  
10 ink supply tube is required, so that the system is bulky. In order to reduce or eliminate the static head difference of the ink supply path, an ink container capable of providing the ink ejection head with a negative pressure, has been proposed and put  
15 into practice. Here, a term "head cartridge" is used to cover an unified head and ink container.

The head cartridge is further classified into a type wherein the recording head and the ink accommodating portion are always unified, and a type  
20 wherein the recording means and the ink accommodating portion are separable, and are separately mountable to the recording device, but are unified in use.

In either structure, the connecting portion of the ink accommodating portion relative to the  
25 recording means is provided at a position lower than the center of the ink accommodating portion in order to increase the usage efficiency of ink accommodated

in the ink accommodating portion. In order to stably maintain the ink and to prevent the ink leakage from the ejection portion such as a nozzle in the recording means, the ink accommodating portion in the head  
5 cartridge is given a function of generating a back pressure against the ink flow to the recording means. The back pressure is called " negative pressure ", since it provides negative pressure relative to the ambient pressure at the ejection outlet portion.

10 In order to produce the negative pressure, the use may be made with capillary force of a porous material or member. The ink container using the method, comprises a porous material such as a sponge contained and preferably compressed in the entirety of  
15 the ink container, and an air vent for introducing air thereinto to facilitate the ink supply during the printing.

However, when the porous material is used as an ink retaining member, the ink accommodation  
20 efficiency per unit volume is low. In order to provide a solution to this problem, the porous material is contained in only a part of the ink container rather than in the entirety of the ink container in a proposal. With such a structure, the  
25 ink accommodation efficiency and ink retaining performance per unit volume is larger than the structure having the porous material in the entirety



of the ink container.

From the standpoint of improving the ink accommodation efficiency, the bladder-like container using or not using the spring, or the ink accommodating container of rubber is usable.


5 Such an ink container is widely used now.

5  
6  
7  
8  
9  
10  
11  
12

However, further improvement is desired.

For example, further increase of the ink accommodation efficiency is desirable. More particularly, a larger amount of the ink is desired to be contained in the same volume of the container.

5 The smaller number of parts constituting the ink container and simpler container are desirable. An increase of the yield and reduction of the quality control items are desired.



### SUMMARY OF THE INVENTION

It is an object of the present invention to ameliorate one or more disadvantages  
5 of the prior art.

In accordance with one aspect of the present invention, there is provided a  
manufacturing method for a liquid accommodating container for an ink jet recording  
apparatus, said container being capable of producing a negative pressure, said method  
10 comprising:

5  
10  
15  
20



providing a liquid container, comprising:  
a substantially prism-like outer wall provided with a substantial air vent portion  
and having a corner formed by 3 surfaces:

5  
10  
15  
20  
25  
30



an inner wall having outer surfaces equivalent or similar to inside surfaces of said outer wall and a corner corresponding the corner of said outer wall, said inner wall defining a liquid accommodating portion for containing liquid therein, said inner wall further having a liquid supply portion for supplying the liquid out of said liquid  
5 accommodating portion;

5  
6  
7  
8  
9  
10



wherein said inner wall has a thickness which decreases from a central portion of the surfaces of the prism-like shape to the corner, and said outer wall and said inner wall are separable from each other;

SECRET



reducing pressure of the liquid accommodating portion to separate the inner wall and the outer wall from each other; and

5  
10  
15  
20  
25



supplying the liquid into the liquid accommodating portion.

SECRET





**BRIEF DESCRIPTION OF THE DRAWINGS**

Figure 1, (a) is a schematic sectional view of an ink container according to a first embodiment of the present invention.

Figure 1, (b) is a side view thereof.

5 Figure 1, (c) is a perspective view thereof.

Figure 2, (a) is a sectional view of a container illustrating deformation thereof with ink discharge, according to a first embodiment of the present invention.

Figure 2, (b) is a side view thereof.

Figure 3, (a) is a sectional view of another



example of the container of the first embodiment.

Figure 3, (b) is a side view thereof.

Figure 4, (a) is an is a schematic sectional  
view of another example of a structure of an ink  
5 container according to the first embodiment of the  
present invention.

Figure 4, (b) is a side view thereof.

Figure 5 is a schematic illustration of a  
negative pressure property of an ink container of the  
10 present invention.

Figure 6, (a)-(d) are an illustration of a  
manufacturing step for the ink container, according to  
a first embodiment of the present invention.

Figure 7 is a flow chart of manufacturing  
15 steps for an ink container according to a first  
embodiment of the present invention.

Figure 8 is a schematic illustration of an  
ink container during a manufacturing step of the ink  
container according to the first embodiment of the  
20 present invention.

Figure 9, (a) is a schematic sectional view  
of an ink container according to a second embodiment  
of the present invention.

Figure 9, (b) is a top plan view thereof.

Figure 9, (c) is a perspective view thereof  
25 when the bottom portion takes a top position.

Figure 10 is a schematic illustration of the

ink container according to the second embodiment of the present invention when it is deformed with the ink discharge.

Figure 11 is a schematic sectional view of an ink container according to the third embodiment of the present invention.

Figure 11, (b) is a side view thereof.

Figure 12, (a)-(d) are an illustration of manufacturing steps for the ink container according to a third embodiment of the present invention.

Figure 13 is an illustration of a nipping portion of a parison and metal mold having intermittent separation layer.

Figure 14 is a flow chart of manufacturing steps of the ink container according to the third embodiment of the present invention.

Figure 15, (a) is a schematic perspective view of an ink container and a recording head connectable to the ink container, according to an embodiment of the present invention.

Figure 15 (b) is a substantially sectional view of connection state between the recording head and ink container.

Figure 16 is a schematic view of an ink jet recording apparatus carrying the ink container according to an embodiment of the present invention.

Figure 17 is a schematic illustration of



dimensions of the ink container.

Figure 18, (a) is a schematic sectional view of another example of an ink container of the first embodiment of the present invention.

5 Figure 18, (b) is a side view thereof.

Figure 19, (a) is a schematic sectional view of a further example of an ink container according to the first embodiment of the present invention.

Figure 19, (b) is a side view thereof.

10 Figure 20 is an illustration of manufacturing step for the ink container according to the first embodiment.

Figure 21, (a) is a schematic sectional view of an ink container according to a fourth embodiment of the present invention.

Figure 21, (b) is a side view thereof.

Figure 21, (c) is a perspective view thereof.

#### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

20 Referring to the accompanying drawings, the embodiments of the present invention will be described.

Referring to Figures 1, 2 and Figure 5, the description will first be made as to the stabilized  
25 negative pressure generation and as to the mechanism for the ink retaining, before the description of the embodiments.

Figure 1, (a) -(c), are schematic views of a structure of an ink container according to an embodiment of the present invention, wherein (a) is a sectional view, (b) is a side view, and (c) is a perspective view. Figure 1, (a) is a sectional view taken along a plane parallel with a maximum area side of the container, as shown in Figure 1, (c). Figure 2 is an illustration of the ink container when the ink therein is consumed, wherein (a1)-(d1) are sectional views taken along a line B-B of Figure 1, (b), and (a2)-(d2) are sectional views taken along a line A-A of Figure 1, (a). The ink container of this embodiment has an inner wall (inner shell) and an outer wall (outer casing, housing or frame) and a separation layer, and the ink container has been manufactured through a single process using a direct blow molding as will be described hereinafter.

The ink container 100 of Figure 1 has the inner wall 102 separable from the outer wall 101 constituting an outer casing or housing, and the ink can be accommodated in the space defined by the inner wall 102 (ink accommodating portion). The thickness of the outer wall 101 is sufficiently larger than that of the inner wall 102 so that the outer wall 101 hardly deforms despite the deformation of the inner wall 102 due to the discharging of the ink to the outside. The outer wall is provided with an air vent

105 for permission of air introduction. The inner wall has a welded portion (pinch-off portion) 104 where the inner wall is supported by the outer wall.

The ink container 100 of Figure 1 is  
5 constituted by 8 flat surfaces, and by an additional cylindrical ink supplying portion 103. The maximum area surfaces of the inner and outer walls at the respective sides of the ink supplying portion 103 have 6 corners ( $\alpha_1, \beta_1, \beta_1, \beta_1, \beta_1$  and  $\alpha_1$ ), and ( $\alpha_2, \beta_2, \beta_2,$   
10  $\beta_2, \beta_2$  and  $\alpha_2$ ), respectively, as will be described in detail hereinafter.

The thickness of the inner wall is smaller in the corner portions than in the central portions of the surfaces or sides constituting the substantially  
15 prism-like (more particularly, rectangular parallelepiped) configuration, more particularly, the thickness gradually decreases from the central portions of each side surface to the associated corners, and therefore, the respective surfaces are  
20 convex toward the inside of the ink accommodating portion. The convex configuration is along the direction of deformation of the surface occurring with the consumption of the ink. The convex shape promotes the deformation of the ink accommodating portion.

25 The corner of the inner wall is provided by 3 surfaces, which will be described hereinafter, so that the strength of the corner as a whole is relatively

high as compared with the strength of the central portion of the surfaces. However, the surfaces at and adjacent each corner has a thickness smaller than the center portions of the surfaces providing the corner, thus permitting easy movement of the surfaces, as will be described hereinafter. It is desirable that the portions constituting the inner wall corner have substantially the same thicknesses.

The ink supplying portion 103 is connected with an ink discharge tube of an ink jet recording means through an ink discharge permission member 106 having an ink leakage preventing function for preventing the leakage of the ink upon small vibration or external pressure imparted thereto (initial state). The ink supplying portion 103, the inner wall and the outer wall are not easily separated from each other by the ink discharge permission member 106 and so on. Crossing portions  $\gamma_1$  and  $\gamma_2$  between the flat surface and a curved surface of the cylindrical configuration, do not easily collapse against the deformation of the inner wall resulting from the consumption of the ink by normal ejections of the ink through the ink jet recording means. The configuration of the ink supplying portion is not limited to the cylindrical shape. It may be a polygonal prism shape (polygonal column). Even in this case, the size of the ink supplying portion is

sufficiently smaller than the ink accommodating  
portion, and therefore, it does not easily collapse  
against the deformation of the inner wall resulting  
from the consumption of the ink. Therefore, even at  
5 the end of the consumption of the ink, the outer wall  
and the inner wall are not deformed but has the same  
configuration as the initial stage, at the ink  
supplying portion.

In Figures 1 and 2, the outer wall 101 and  
10 the inner wall 102 of the ink container are separated  
with a relatively large clearance therebetween, but it  
is not inevitable, and the clearance may be so small  
that they may be substantially contacted, or it will  
suffice if they are separable. Therefore, in the  
15 initial state, the corners  $\alpha_2$  and  $\beta_2$  of the inner wall  
102 are at the inner side of the corners  $\alpha_1$  and  
corners  $\alpha_2$  of the outer wall 101 (Figure 2, (a1) and  
(a2)).

Here, the corner means a crossing portion of  
20 at least 3 surfaces of polyhedron constituting the ink  
container, and a portion corresponding to a crossing  
portion of extended surfaces thereof. The reference  
characters designating the corners are such that  $\alpha$   
means corners formed by the surfaces having the ink  
25 supply port, and  $\beta$  means the other corners; and suffix  
1 is for the outer wall, and suffix 2 is for the inner  
wall. The crossing portions between the substantial





flat surface and the curved surface of the cylindrical ink supplying portion is designated by  $\gamma$ ; and the outer wall and inner wall are formed at the crossing portions, too, which are designated by  $\gamma_1$  and  $\gamma_2$ .

5 The corner may be rounded in a small range. In such a case, the round portions are deemed as corners, and the other surface portions are deemed as side surfaces.

The ink of the ink accommodating portion is supplied out in response to the ejections of the ink through the ink jet recording head of the ink jet recording means, in accordance with which the inner wall starts to deform in a direction of reducing the volume of the ink accommodating portion, first at the central portion of the maximum area surface. The outer wall functions to constrain the displacement of the corners of the inner wall. In this embodiment, the corner  $\alpha_2$  and the  $\beta_2$  are hardly moved, so that the corners are effective to be against the deformation caused by the ink consumption, and therefore, a stabilized negative pressure is produced.



The air is introduced through the air vent 105 into between the inner wall 102 and the outer wall 101, and the surfaces of the inner wall can be deformed smoothly, thus permitting the negative pressure to be stably maintained. The space between the inner wall and the outer wall is in fluid

communication with the ambience through the air vent.  
Then, the force provided by the inner wall and the  
meniscus force at the ejection outlet of the recording  
head balance so that the ink is retained (Figure 2,  
5 (b1) and (b2)).

When quite a large amount of the ink is  
discharged from the ink accommodating portion (Figure  
2, (c1) and (c2)), the ink accommodating portion is  
deformed, more particularly, the central portions of  
10 the ink accommodating portion smoothly deforms  
inwardly, as described hereinbefore. The welded  
portions 104 function to constrain the deformation of  
the inner wall. Therefore, as for the sides adjacent  
to the maximum area sides, the portions not having the  
15 pinch-off portion start to deform so as to become away  
from the outer wall earlier than the portions having  
the pinch-off portion 104.

However, only with these inner wall  
deformation constraining portions described above, the  
20 deformation of the inner wall adjacent to the ink  
supplying portion may close the ink supplying portion  
before the ink contained in the ink accommodating  
portion is used up to sufficient extent.

According to this embodiment, however, the  
25 corner a2 of the inner wall shown in Figure 1, (c), is  
adjacent along the corner a1 of the outer wall in the  
initial state, and therefore, when the inner wall is

deformed, the corner  $\alpha_2$  of the inner wall is less easily deformed than the other portion of the inner wall, so that the deformation of the inner wall is effectively constrained. In this embodiment, the  
5 angles of the corners are 90 degrees.

Here, the angle of the corner  $\alpha_2$  of the inner wall is defined as the corner  $\alpha_1$  between two substantially flat surfaces of the at least 3 surfaces of the outer wall, namely, as the portion of the  
10 crossing portion of the extensions of the 2 surfaces. The angle of the corner of the inner wall is defined as the angle of the corner of the outer wall, because in the manufacturing step which will be described hereinafter, the container is manufactured on the  
15 basis of the outer wall and because the inner wall and outer wall are similar in configuration in the initial state.

Thus, as will be understood from Figure 2, (c1) and (c2), the corner  $\alpha_2$  of the inner wall shown in  
20 Figure 1, (c) is provided separably from the corresponding corner  $\alpha_1$  of outer wall, and on the other hand, the corner  $\beta_2$  of the inner wall other than the corner formed by the surfaces having the ink supply port, is slightly separated from the corner  $\beta_1$   
25 of the corresponding outer wall as compared with the corner  $\alpha_2$ . However, in the embodiment of Figure 1 and 2, the angle  $\beta$  at the opposite position is

generally not more than 90 degrees. Therefore, the positional relation relative to the outer wall can be maintained close to the initial state as compared with the other parts of the inner wall constituting the ink  
5 accommodating portion, so as to provide an auxiliary support for the inner wall.

Furthermore, in Figure 2, (c1) and (c2), the opposite maximum surface area sides are substantially simultaneously deformed, and therefore, the center  
10 portions thereof are brought into contact with each other. The contact portion of the center portions (Figure 2, (c1) and (d1), hatched portion) expands with further ink discharge. In other words, in the ink container of this embodiment, the opposite maximum  
15 area sides of the container start to contact before the edge formed between the maximum area side and the side adjacent to thereto, collapses, with the consumption of the ink.

Figure 2, (d1) and (d2) show the state in  
20 which substantially the entirety of the ink is used up from the ink accommodating portion (final state).

In this state, the contact portion of the ink accommodating portion, expands substantially over the entirety of the ink accommodating portion, and one or  
25 some of the corners  $\beta 2$  of the inner wall are completely separated from the corresponding corners  $\beta 1$  of the outer wall. On the other hand, the corner  $a 2$

of the inner wall is still separably positioned closely to the corresponding corner a1 of the outer wall even in the final state, so that the corner a2 functions to constrain the deformation to the end.

5           Before this state is reached, the welded portion 104 may have been separated from the outer wall, depending on the thickness of the inner wall. Even in that case, the length of the welded portion 104 is maintained, and therefore, the direction of the  
10 deformation is limited. Therefore, even if the welded portion is separated from the outer wall, the deformation is not irregular but it occurs with the balance properly maintained.

          As described in the foregoing, the  
15 deformation starts at the maximum area sides, which then are brought into surface contact with each other before an edge of the maximum area sides are collapsed, and the contact area increases. The corners other than the corners constituted by the side  
20 having the ink supplying portion are permitted to move. Thus, the order of precedence of deforming portions of the ink accommodating portion is provided by the structure thereof.



          At least one of the maximum area sides of the  
25 substantially flat sides of the outer wall of the ink container having a substantially prism configuration, is not fixed to the inner wall. This will be

described in detail.

When the amount of the ink in the ink  
accommodating portion reduces by the ejection of the  
ink from the ink jet recording head, the inner wall of  
5 the ink container tends to deform at the portion which  
is easiest to deform under the constraint described  
above. Since at least one of the substantially flat  
maximum surface area sides of the polyhedron shape, is  
not fixed to the inner wall, the deformation starts at  
10 substantially the central portion of the internal wall  
surface corresponding to this side.

Since the side at which the deformation  
starts, is flat, it smoothly and continuously deforms  
toward the side opposite therefrom corresponding to  
15 the decrease amount of the ink in the ink  
accommodating portion. Therefore, during the  
repeated ejection and non- ejection, the ink  
accommodating portion does not deform substantially  
non-continuously, so that a further stabilized  
20 negative pressure can be maintained, which is  
desirable for the ink ejection of the ink jet  
recording apparatus.

In this embodiment, the maximum surface area  
sides are opposed to each other and are not fixed to  
25 the outer wall and therefore are easily separable from  
the outer wall thereat, and therefore, the two  
opposite sides deform substantially simultaneously

toward each other, so that the maintaining of the negative pressure and the stabilization of the negative pressure during the ink ejections can be further improved.

5           The volume of the ink container for the ink jet in this embodiment is usually approx.  $5-100\text{cm}^3$ , and is  $500\text{cm}^3$  at a typical maximum .

          A ratio of size of the maximum surface area side to the other sides of the ink container can be  
10 determined in the following manner. As shown in Figure 17, first, a rectangular parallelopiped of minimum size capable of containing therein the ink container is taken. The edges of the rectangular  
15 parallelopiped are designated by 11, 12 and 13 (length of edge 11 is not less than that of the edge 12, which is larger than that of the edge 13). It is desirable that the ratio of the lengths of the edges 11 and 13 is approx. 10: 1-approx. 2: 1. By this, when the ink  
20 container has a substantially rectangular parallelopiped configuration, the size of the maximum surface area side can be determined relative to the all surface area. In this embodiment, the area of the maximum area surface is larger than the total sum of the areas of the surfaces adjacent thereto.

25           The experiments have been carried out with a liquid container having a thickness of approx.  $100\mu\text{m}$  at the central portion of the inner wall, and having a

thickness of several  $\mu\text{m}$ - $10\mu\text{m}$  adjacent to the corner.  
In this case, the corner is provided by a crossing  
portion of the 3 surfaces, the strength of the corner  
substantially corresponds to that of the tripled  
5 thickness namely  $10 \times 3 = 30\mu\text{m}$  approx.

In the initial stage of the start of the  
liquid discharge, the desired negative pressure can be  
produced by the constraint of the collapse of the  
corners and the crossing portions between the surfaces  
10 or sides.

With the further discharge of the liquid, the  
deformation occurs and increases at the center  
portions of the maximum area sides of the container.  
Then, the corners of the sides of the inner wall begin  
15 to become away from the corresponding corners of the  
outer wall. Immediately after the separation of the  
corners, the original configuration of the corners  
tend to be maintained so that the deformation of the  
corners is constrained. However, with further liquid  
20 discharge, the configuration of the corners are  
gradually deformed since the thickness is as small as  
 $100\mu\text{m}$ .

However, all of the corner constituting the  
liquid container are not simultaneously separated and  
25 deformed, but they occur in the predetermined  
precedence order.

The precedence order is determined by the





configuration of the liquid container, corner conditions such as film thickness, the position of the pinch-off portion where the inner wall is welded and is sandwiched by the outer wall, or the like. By the provision of the pinch-off portion at the positions as in this embodiment, the deformation of the inner wall and the separation thereof from the outer wall can be regulated at the positions, so that irregular deformation of the inner wall can be prevented. Additionally, the provision of the pinch-off portions at opposite positions as in this embodiment, the negative pressure can be further stabilized.

By the subsequent separation of the corners constituting the liquid container, the predetermined negative pressure can be produced stably from the initial stage of the liquid discharge to the end thereof. With the thickness of the inner wall about 100 $\mu$ m as in this embodiment, the crossing portion between the adjacent surfaces and the corners are irregularly deformed namely toward the ink supplying portion, at the time when the ink is used up.

The similar experiments were carried out with a liquid container having a thickness of 100-400 $\mu$ m at the central portions of the inner wall and a thickness of 20-200 $\mu$ m adjacent to the corners, wherein the strength of the corners were quite higher than in the foregoing sample of the container.

With this container, the predetermined negative pressure were produced at the initial stage of the liquid discharge, similarly to the foregoing example. With the further consumption of the ink, the inner wall begin to gradually separate from the outer wall at the central portion of the sides. Corresponding to the deformation, the corners begin to separate from the corresponding corners of the outer wall. The deformation of the corners is small even after quite a large amount of the liquid is discharged. Since the corner is separated from the outer wall with the initial configuration is substantially maintained, the negative pressure is stabilized. At the end of the consumption of the ink, the configuration is stabilized, so that the negative pressure is provided stably to the end of use of the ink with the minimum remaining amount of the ink.

As a result of additional experiments, it has been found that the stabilized negative pressure can be generated when the thickness adjacent to the central portion of the inner wall is 100-250 $\mu$ m, and the thickness adjacent to the corner is 20-80 $\mu$ m.

Similar investigation were made as to a simply cylindrical container. Here, the cylindrical configuration means a cylindrical container having a height larger than the diameter thereof.

With such a cylindrical container, the strength of the side is so high because of the curved surface thereof, that the container does not collapse when it is used for the ink jet recording. The high strength structure provided by the curved surface withstand the inside pressure reduction. Therefore, the internal negative pressure tends to be too large.

When the inside liquid is forcedly sucked out, the curved side suddenly collapses, and simultaneously, a part of of the end surface is significantly buckled. It is very difficult to produce stabilized negative pressure with the use of the cylindrical configuration, and therefore, it does not suit for the ink jet recording.

Figure 5 shows a relation between the ink use amount of the ink accommodating portion and the negative pressure of the ink container in the ink container according to this embodiment. In Figure 5, the abscissa represents the ink discharge amount, and the ordinate represents the negative pressure. In this Figure, the negative static pressure is plotted with square marks. A total negative pressure which is a sum of the negative static pressure and the dynamic negative pressure produced when the ink flows, is plotted by "+" marks.

Here, the negative pressure in the ink accommodating portion is preferably as follows.

1. First, the negative static pressure at the time of shipment of the ink containers to the market is approx.+2 to 60mmAq. approx. relative to the ambient pressure, and desirably, -2 to 30mmAq. approx.

5 If the pressure is positive at the delivery, a proper negative pressure can be provided by an initial refreshing operation in the main assembly of the recording device, for example. Here, "the state at the time of delivery" is not limited to the initial

10 state shown in Figure 2, (a1) and (a2). If the negative pressure is maintained, the container may contain an amount of the ink which is slightly smaller than the maximum accommodatable amount of the ink accommodating portion.

15 Secondly, the pressure difference between when the recording is effected and when it is not effected, is small, namely, the difference between the negative static pressure and the total pressure is small. This is accomplished by reducing the dynamic

20 pressure. The dynamic pressure in the ink accommodating portion per se can be neglected as contrasted to the ink accommodating portion using a porous material, and therefore, the small dynamic pressure can be easily accomplished.

25 Thirdly, the change in the negative static pressure due to the change of the ink amount in the ink accommodating portion is small from the initial



state to the final state. In a simple structure of the ink accommodating portion, the negative static pressure changes linearly or non-linearly relative to the ink amount existing in the ink accommodating portion, and therefore, the change ratio of the static pressure is large. However, in the ink container of this embodiment, the change of the negative static pressure is small from the initial stage to immediately before final state, so that substantially stabilized negative static pressure is accomplished.

In the ink container of the first embodiment, the ink supply performance of the ink container was evaluated. The maximum thickness of the outer wall was 1mm; the maximum thickness of the inner wall was 100 $\mu$ m; and the surface area of the inner wall was 100cm<sup>2</sup>. The outer wall was of Noryl resin material, and the inner wall was of polypropylene resin material. The properties were similar to the container of Figure 5, and the total pressure was maintained at approx.-100mmAq. Therefore, the ink container of this embodiment is satisfactory in the field of the ink jet recording wherein the stabilized negative pressure production is necessary. Since the volume usage efficiency is high, it is particularly suitable for a small ink jet recording apparatus.

The description will be made as to 4 embodiments of the present invention including the

manufacturing method. However, the present invention is not limited to these embodiment.

Embodiment 1


5 Figure 1, (a) and (b) show schematic views of the ink container of first embodiment, wherein (a) is a sectional view, (b) is a side view, and (c) is a perspective view.

10 Figures 3 and 4 show a modified example of the ink container shown in Figure 1. Figures 3 and 4, (a) and (b) are sectional views and side views, respectively.

The structure of the ink container of the first embodiment will first be described.

15 In the ink container 100 shown in Figure 1, (a), designated by 101 is an outer wall of the ink container, and 102 is an inner wall of the ink container. The ink is accommodated in an ink accommodating portion which is defined by the inner  
20 wall 102. The outer wall is provided outside of the inner wall to protect the ink accommodating portion so as to avoid leakage of the ink due to the unintended deformation of the inner wall.


25 Designated by 103 is an ink supplying portion for the ink supply from the inside to the outside of the container, and functions as a connecting portion with an ink receiving portion of the ink jet head side



unshown.

In the ink container of this embodiment, the corners of the inner wall are close to the corners of the outer wall, so that the ink container inner wall 5 102 is similar in configuration to the ink container outer wall 101, and therefore, the ink container inner wall 102 can be matched with the configuration of the ink container outer wall 101 (outer housing) with a predetermined gap therebetween. Thus, the dead space 10 remaining in a conventional container having a casing and a bladder-like container therein, can be removed, so that the ink accommodation capacity per unit volume of the outer wall can be increased (ink accommodation efficiency can be increased).

15 Designated by 104 is a welded portion for forming a sealing space by the inner wall 102. The welded portion is formed in the following manner. During the blow molding of the container as will be described in detail hereinafter, a parison for forming 20 the wall of the ink container is sandwiched by metal molds, so that the welded portion is formed. The inner wall portions are welded, and the outer wall are closely contacted thereto, so that the outer wall functions to support the inner wall 102, as will be 25 described in detail hereinafter. In this embodiment, as shown Figure 1, (b), the configuration of the welded portion 104 is rectilinear as seen from the



lateral side. But, the rectilinear shape is not inevitable if in the manufacturing step which will be described hereinafter, the ink container is easily taken out from the mold. The length thereof is not  
5 limited to the length used in this embodiment, if it does not project beyond the side.

In Figure 1, (a), only the ink supplying portion is indicated with deviation for better illustration purpose of the ink supplying portion 103.  
10 If the ink supplying portion is at the position opposed to the welded portion 104 of the lateral side of the ink container, the welded portion is also provided at the ink supplying portion. In such a case, the section is as shown in Figure 3, (a).

15 Designated by 105 is an air vent for introducing the air into between the inner wall 102 and outer wall 101 when the volume of the ink accommodating portion defined by the inner wall 102 is reduced with the consumption of the ink. It may be a  
20 simple opening or a combination of an opening and an air entering valve. In the embodiment of Figure 1, it is a simple opening.

Figures 3 and 4 show a modified examples of the air vent.

25 In the modified example of Figure 3, a small gap 107 of approx. several 10  $\mu\text{m}$  between the outer wall and the inner wall occurring in the neighborhood



of the welded portion 104, is utilized as the air vent. The gap is easily formed by using a material of the inner wall having a low adhesiveness relative to the outer wall and by separating the inner wall 102  
5 from the outer wall 101 by imparting external force to the welded portion 104.

In the modified example of Figure 4, the outer wall 101 and the inner wall 102 are made of different materials, and the inner wall is separated  
10 from the outer wall using residual stress or the like, similarly to the modified example of Figure 3. The maintaining of pressure balance of the inner wall of the ink container is assisted by provision of the valve 108 open to the outside in the outer wall. In a  
15 usual ink supply, the sufficient pressure adjustment is possible by introducing and discharging the air to and from the space between the outer wall 101 and the inner wall 102 through the gap. But the valve 108 is provided to accommodate quick and abrupt pressure  
20 change due to the falling of the ink container or the like.

Designated by 106 is an ink discharge  
permission member having an ink leakage preventing  
function for preventing the leakage of the ink from  
25 the ink supplying portion in the case that slight vibration or external pressure is imparted to the container. In this embodiment, it is in the form of

one directional fibrous member of ink absorbing material having meniscus retentivity. The ink accommodating portion is substantially hermetically sealed by the ink discharge permission member 106, and  
5 in the case that the ink introduction portion of the ink jet head side is inserted therewith, the ink is discharged while the sealed state is maintained.

In place of the press-contact member, a rubber plug, a porous material, a valve, a filter or a  
10 resin material are usable at the ink discharge permission member 106, depending on the coupling structure between the ink container 100 and the ink jet head.

The description will be made as to the  
15 manufacturing method according to this embodiment.

The ink container of an embodiment of the present invention has a double wall structure of molding resin material, wherein the outer wall has a thickness to provide high strength, and the inner wall  
20 is of soft material with small thickness, thus permitting it to follow the volume variation of the ink. It is preferable that the inner wall has an anti-ink property, and the outer wall has a shock resistant property or the like.

In this embodiment, the manufacturing method  
25 for the ink container uses a blow molding method with the use of blowing air. This is for the purpose of


forming the wall constituting the ink container from a resin material not expanded substantially. By doing so, the inner wall of the ink container constituting the ink accommodating portion can resist the load  
5 substantially uniformly in any direction. Therefore, despite the swinging motion, in any direction, of the ink in the inner wall of the ink container after some amount of the ink is consumed, the inner wall can assuredly maintain the ink, thus improving the total  
10 durability of the ink container.

As for the blow molding method, there are a method using injection blow, a method using direct blow, and a method using double wall blow.

The description will be made as to the method  
15 using the direct blow molding used in this embodiment.

Figure 6, (a) -(d) show the manufacturing steps for the ink container, according to this embodiment, and Figure 7 is a flow chart showing the manufacturing steps for the ink container. Figure 8  
20 shows the ink container during the manufacturing step, and the suffix 1 indicates the maximum surface area portion of the ink container, and suffix 2 indicates a section parallel to the end surface of the ink container at the central portion of the ink container.

In Figure 6, designated by 201 is a main  
25 accumulator for supplying the resin material constituting the inner wall; 202 is a main extruder



for extruding the inner wall resin material; 203 is a sub-accumulator for supplying the resin material constituting the outer wall; and 204 is a sub-extruder for extruding the outer wall resin material. The injection nozzle is in the form of a multi-layer nozzle, and it injects the inside resin material and the outside resin material simultaneously into the mold to produce an integral first and second parison. In this case, the inside resin material and the outside resin material may be contacted to each other when resin material is supplied, or they may be only partly contacted. The materials of the inside resin material and the outside resin material are so selected as to avoid the welding of the resin materials at the contact portion therebetween, or a chemical compound may be added to one of the resin materials when it is supplied into the mold to make them separable. When similar materials are to be used from the standpoint of the liquid contact property relative to the ink, the inside material or the outside material may be of multi-layer structure so that the resin materials are supplied in such a manner that different kind materials are present in the contact portion. The supply of the inside resin material is uniform along the circumference ideally, but it may be locally thin to provide a structure easily followable to the variation of the inside



pressure. The locally thin part will extend in the direction of supply of the resin material.

Thus, the outer wall resin material and the inner wall resin material are supplied to the dies 206 through a ring 205, (step S301 S302), a parison 207 constituted by the first and second parisons, is formed (step S303). Metal molds 208 are disposed so as to be able to sandwich the integral parison 207, as shown in Figure 6 (b), and they are moved to the positions shown in Figure 6, (c) to sandwich the parison 207 (step S304).

Then, as shown Figure 6, (c), the air is injected through the air nozzle 209 to effect the blow molding into the inside shape of the metal mold 208 (step S305). The ink container at this time is shown in Figure 8, (a1), (a2).

At this time, the inner wall and the outer wall are closely close contacted without gap therebetween. The temperature of the mold during the molding operation is desirably controlled within the range of approx.  $\pm 30^{\circ}\text{C}$  relative to a reference temperature, since then the variation of the thickness of the walls of individual containers can be reduced.

Then, the inner and outer walls are separated at other than the ink supplying portion (step S306). Figure 8 (b1) and (b2) shows the ink container at step S306 in the case that they are separated by vacuum.

As for another separation method, the molding resin materials of the inner wall and the outer wall have different thermal expansion coefficients (shrinkage rates). In this case, the separation is effected  
5 automatically by decrease of the temperature of the molded product after the blow molding, so that the number of manufacturing steps can be decreased. The portion having been sandwiched by the molds during the blow molding may be imparted by external force after  
10 the molding to separate the outer wall from the inner wall, and the gap therebetween may be brought into communication with the air, so that the gap can be used as an air vent. This is preferable in the case of the container for ink jet recording since then the  
15 number of manufacturing steps can be reduced. .

After the separation between the inner wall and the outer wall, the ink is injected (step S307). Before the injection of the ink, the ink accommodating portion may be shaped into the initial state by  
20 compressed air (Figure 8, (c1), (c2)), and then the ink injection may be carried out. When the initial state shaping operation is effected, the ink may be injected by pressure.

The amount of the injected ink may preferably  
25 be approx. 90% of the volume of the ink accommodating portion, since then the leakage of the ink can be avoided even upon the external force exerted thereto,

the temperature change or the pressure change.

Figure 8, (d1) and (d2) show the state of the schematic view after the ink injection. At this time, the inner wall and the outer wall of the ink container  
5 are separable when the ink is consumed from the container. After the injection of the ink, the ink discharge permission member is mounted (step S308).

In the above-described blow molding, the processing of the parison 207 is carried out when it  
10 has a certain viscosity, so that the inner wall resin material and the outer wall resin material do not have an orientation property.

The thicknesses  $t_1$  and  $T_1$  of the inner wall resin material and the outer wall resin material after  
15 the blow molding are smaller than the thicknesses  $t$ ,  $T$  before the blow molding. The relation between the thicknesses of the outer wall resin material and the inner wall resin material is  $T > t$  and  $T_1 > t_1$ , for the reason described hereinbefore.


20 More particularly, the thickness of the outer wall is 1mm, and the thickness of the inner wall is 0.1mm, and the surface area of the inner wall is 100cm<sup>2</sup>. The material of the outer wall is Noryl (available from General Electric, U.S.A.), and  
25 the resin material of the inner wall is polypropylene resin material having a low elastic modulus than the Noryl. The thickness of the inner wall is uniform,

and it is contracted as a whole by the internal pressure. By the use of the blow molding, the number of the processes and the number of the parts could be reduced during the manufacturing. Therefore, the yield has been improved, and the inner wall 102 can be easily given the configuration such that the corners of the inner wall 102 are positioned at the corners of the outer wall 101 along the inside of the outer wall 101 of the ink container, as shown in Figure 1.

More particularly, at the initial state with full ink, the ink container inner wall 102 is similar in configuration to the ink container outer wall 101, and the ink container inner wall 102 can be extended along the inside of the ink container outer wall 101 with a gap in a predetermined range, so that the dead space necessitated in the conventional container having a casing and a bladder-like container therein, can be avoided. By this, the ink accommodation capacity per unit volume of the space defined by the outer wall can be increased (ink accommodation efficiency is increased).

Since the inner wall to which the ink is deposited, is separated from the outer wall, and is in the form of a thin layer, it may be easily taken out of the outer wall, so that it can be disposed of or it can be separately recycled.

Figure 20 is a view of the mold of Figure 6,





(b) -(d), and Figure 20, (a1), (b1) and (c1) are views as seen in dividing direction and (a2), (b2) and (c2) are views seen in a direction perpendicular to the dividing plane.

5 In Figure 20, (a1) and (a2) are views before sandwiching the parison by the molds, and (b1) (b2) are views after the parison is sandwiched between the molds. In the portion sandwiched by the molds, the circular parison is collapsed into a flat shape and  
10 therefore is widened. The nipped portions by the sandwiching remain as the pinch-off portions. In Figure 10, (c1) and (c2), the configuration is after the parison is molded by the blowing air.

The description will be made as to the  
15 molding resin material constituting the ink container.

The ink container has the 2 heavy structure including the inner wall for accommodating the ink and the outer wall covering the inner wall. Therefore, the material of the inner wall preferably has a  
20 flexibility with small thickness, a high liquid contact property and low permeability for gases; and the material of the outer wall has a high strength to protect the inner wall.

Ink containers having the configuration  
25 similar to the first embodiment were manufactured using polypropylene resin material, polyethylene resin material and Noryl as the molding resin material.

The Noryl is non-crystalline property hardly having a crystalline structure, although the polypropylene resin material and polyethylene resin material have crystal property.

5           A non-crystalline resin material generally has small heat contraction rate, and crystal resin material generally has a large heat contraction rate, and examples of the non-crystalline plastic resin material include a polystyrene resin, polycarbonate  
10 resin, polyvinyl chloride and the like. Polyacetal and polyamide resin partly constitute crystalline portion at a certain ratio under a predetermined condition.

          The crystalline plastic resin material has a  
15 glass transition temperature ( $T_g$ ; a temperature at which the molecules begin the micro-Brownian motion and the property changes from glass-like to rubber-like) and a relatively clear melting point. On the other hand, a non-crystalline plastic resin material  
20 has a glass transition temperature but does not have clear melting point.

          The plastic resin material exhibits steeply changing mechanical strength, specific volume, specific heat, thermal expansion coefficient at the  
25 glass transition temperature and the melting point, and therefore, by selecting the combination of the materials using the properties, the release or

separation property between the inside and the outside  
can be improved. For example, the outer wall is made  
of non-crystalline resin such as Noryl, and the inner  
wall is made of crystalline plastic resin material  
5 such as polypropylene resin material, as in the first  
embodiment, so that the outer wall is given the high  
mechanical strength while the inner wall is given the  
large heat contraction rate and softness.

The resin having the hydro carbon structure  
10 wherein the polymer molecules have only the C-C  
bond and C-H bond, is called a non-polar  
polymer. A polymer containing a large part of polar  
atom such as O, S, N, halogen is called a polar  
polymer. The polar polymer has a large cohesive  
15 power in the molecules thus providing a large binding  
power.

The release property of the resin material  
can be increased by using proper combination of the  
non-polar resin materials and combination of non-polar  
20 resin material and polar resin material.

Embodiment 2

Figure 9 shows an ink container according to  
a second embodiment of the present invention. The ink  
25 container is usable with a BJ-30v ink jet printer  
available from Canon KABUSHIKI KAISHA, Japan. The  
configuration of the container and the positional

relation between the ink supplying portion and the supporting portion of the inner wall is different from those of the first embodiment.

Similarly to the first embodiment, the wall  
5 of the ink container has a double wall structure for the purpose of the evaporation prevention of the ink, uniform pressure of the container and ink leakage prevention. The container can follow the inside pressure variation due to the ink decrease. At least  
10 one of the corners  $\alpha$  of the surface having the ink supplying portion has substantially 90 degrees in three orthogonal planes, by which the inner wall is properly constrained.

In this embodiment, the configuration is  
15 slightly close to a cubic member as compared with the first embodiment, and the ink supplying portion 113 is formed in the bottom surface. The side having the ink supplying portion 113 and the side having the welded portion 114 are not opposed to each other. The gap  
20 117 formed adjacent the welded portion is utilized as an air vent.

At least one of the outer maximum surface area sides among the substantially flat outer wall sides, does not have a connection with the inner wall  
25 112, so that the inner wall is easily separable from the outer wall similarly to the first embodiment. In this embodiment, however, the opposed surface has an

ink supplying portion 113, rather than it has the same structure.


When inner wall 112 of the ink container of this embodiment deforms with the consumption of the ink in the ink accommodating portion, the deformation begins at the top of the ink container, rather than the opposed two surfaces are deformed. The direction of the deformation is vertically downward, and is the same as the ink supply direction from the ink supplying portion to the recording head. Therefore, in this embodiment, the stabilized ink ejection and the maintaining of the negative pressure as good as in the first embodiment can be accomplished, although the structure is different. Figure 10, (a) -(d) show the changes when the ink is discharged from the ink supplying portion of ink container of this embodiment having been filled with the ink. Here, the suffix 1 in (a) -(d) indicates sections vertical to the top ceiling surface at the central portion of the ink container, and the suffix 2 indicates the top ceiling surface of the ink container.

Figure 10, (a1) and (a2) show the initial state, and corners of the outer wall are disposed at the corners of the inner wall of the ink container, and the inner wall and the outer wall are separable. The container has a pair of maximum surface area sides, and one of them is provided with an ink supply

portion and takes a bottom position, the other maximum surface area side takes a top position.

When the discharge of the ink starts from the ink supplying portion, as shown Figure 10, (b1) and (b2), the deformation starts at the central portion of the internal wall surface corresponding to the ceiling side of the outer wall of the ink container. At this time, the position of such a corner as is formed by the internal wall surfaces corresponding to the ceiling surface, among the corners  $\beta 2$  of the inner wall, begins to separate from the corresponding corner of the outer wall, and moves down along the outer wall. The corner  $\beta 2$  having started the motion constrain the deformation of the inner wall to a certain extent, and therefore, it cooperates with the intersection  $\alpha 2$  to produce the force to restore the initial state of the side of the inner wall corresponding to the ceiling surface, with the result of negative pressure produced in the ink accommodating portion. Similarly to the first embodiment, the air is introduced into between the inner wall 112 and the outer wall 111, so that the deformation of the inner wall is not obstructed. Thus, the negative pressure is stably maintained during the ink discharge.

When the ink is further discharged, the inner wall portion corresponding to the ceiling is further deformed, as shown in Figure 10, (c1) and (c2), and



the corner formed by the inner wall portion is separated from the corner of the outer wall. On the other hand, the internal wall surface having the ink supplying portion 113 is hardly deformed. This is because, similarly to first embodiment, at least one of the angles of the opposed corners  $\alpha 2$  of the inner wall of the ink container is not more than 90 degrees, and therefore, the corners  $\alpha 2$  of the inner wall are positioned in a separable state at the corners  $\alpha 1$  of the outer wall.

When the ink is further discharged, the final state is reached as shown in Figure 10, (d1) and (d2), wherein the internal wall surface corresponding to the ceiling surface and the surface having the ink supplying portion are contacted. The corners  $\beta 2$  formed by the internal wall surface corresponding to the ceiling surface, is further deformed, so that it is completely separated from the outer wall.

There is a possibility that the ink supplying portion is closed by the inside surface of the inner wall. To avoid this, the ink supplying portion is provided with a porous material or fibrous member partly extended into the ink accommodating portion, so that the inside ink can be assuredly discharged out by the meniscus force of the porous material or the fibrous member through the gap formed between the internal wall surface corresponding to the surface of



the ceiling and the projected portion.

In this final state, too, the corner  $\alpha 2$  constituted by the internal wall surface is separable from the corner  $\alpha 1$  of the corresponding outer wall so  
5 that the internal wall surface having the ink supplying portion is hardly deformed.

By thus providing the ink supplying portion in the surface opposing to the outer wall surface having the maximum surface area, the negative pressure  
10 can be stably maintained from the initial state to the final state, and in addition, the usage efficiency is improved.

The manufacturing method of the present ink container is similar to that for the first embodiment,  
15 namely, the blow molding is used. However, in the first embodiment, the ink supplying portion is provided along the parison supply direction, and the air blowing opening is provided by the ink supplying portion. In this embodiment, the ink supplying portion  
20 113 is different from the parison supply direction, and therefore, a process of welding the air blowing opening and a step of providing the ink supplying portion, are additionally required. The air blowing opening may be the welded portion 114a or 114b. In  
25 this embodiment, the welded portion 114b is used therefor, and after the molding, the inner wall is welded by the welded portion 114b.



The ink container of embodiment 2 can be more easily produced when the step of welding the air blow port member and the step of welding the ink supply portion are added, than when the maximum surface area side is provided in a direction of welded portion, that is, the direction perpendicular to the direction relative to parison supply direction, in the case that the ink supplying portion is along the parison supply direction similarly to the first embodiment.

10

#### Embodiment 3

Figure 11 shows an ink container according to a third embodiment of the present invention. In Figure 11, (a) is a sectional view, and (b) is a bottom view. In the third embodiment, a separation layer is provided between the inner wall and the outer wall.

Similarly to the first and second embodiment, in order to accomplish the evaporation prevention of the ink, uniformity of the pressure in the container and the leakage prevention of the ink, a plurality of walls are provided such that the ink container follows the inside due to the decrease of the ink in the ink container. Similarly to the first and second embodiment, at least one of the angles of the corners  $\alpha_2$  of at a plurality of opposing inner walls as regards the corners  $\alpha$  formed by the surfaces including



the ink supplying portion, is not more than 90 degrees, so that the deformation confinement portion function is provided.

In the ink container 120 shown in Figure 11, 1(a), designated by 121 is an outer wall of the ink container, and 122 is an inner wall of the ink container.

A part of the outer wall 121 and a part of the inner wall 122 are separated by a separation layer 129, but they are integral at the rest, and the same materials are used although the thicknesses are different. The separation layer 129 is of a material not adhesive to the outer wall 121 or to the inner wall 122 to facilitate the separation therebetween.

What is necessary is that the separation layer 129 is separable from the outer wall 121 and from the inner wall 122, the separation layer may be contacted with or spaced from the outer wall or the inner wall. In any case, only the space between the separation layer 129 and the outer wall 121 is in fluid communication with the outside through an air vent formed in the outer wall 121. The inner wall 122 and the separation layer 129 may be integral.

When the ink is consumed from the inside of the ink container, the inner wall 122 is deformed, and the volume of the space defined by the inner wall reduces with the result of force produced in the

direction of elastically returning to the initial state. Since the separation layer has thickness smaller than the inner wall, it is deformed simultaneously with the deformation of the inner wall  
5 so as to follow the inner wall. The ambience is introduced into between the separation layer 127 and the outer wall through the air vent 125. The introduction of the ambience assists the deformation of the inner wall and functions to maintain the  
10 stabilized negative pressure.

Designated by 123 is an ink supplying portion for supplying the ink out of the container, and is connectable with an ink receiving portion unshown of the ink jet head. Designated by 126 is a ink  
15 discharge permission member functioning as a connecting portion with the ink jet head, and is in the form of a press-contact member, rubber plug or valve, similarly to the first embodiment.

In the neighborhood of the ink supplying  
20 portion 123, the outer wall 121 and the inner wall 122 are integral, so that the moldability of the ink supplying portion 123 can be increased in the manufacturing step using the blow molding, which will be described hereinafter.

25 To the ink supplying portion 123, an unshown ink introduction portion of the head side is connected through the ink discharge permission member 126, by

which the ink jet recording head can be supplied with the ink. Usually, the ink receiving portion of the recording head is in the form of an ink supply tube as shown in Figure 5, (a) to accomplish the stabilized  
5 ink supply, in many cases. If the moldability of the ink supplying portion 123 is good, the connection with the ink jet recording head is assured, so that the ink leakage through the connecting portion does not occur, and the mounting-and-demounting of the ink container  
10 relative to the ink jet recording head can be repeated, and therefore, it is desirable. Further, since the outer wall and the inner wall are integral adjacent the ink supplying portion 123, the strength adjacent the ink supplying portion 123 can be  
15 enhanced. Designated by 124 is a welded portion of the inner wall sandwiched by the outer wall 121 together with the separation layer 129. By the welded portion the inner wall 122 is supported by the outer wall.

20 In this embodiment, the outer wall has a thickness of 1mm, and the inner wall has a thickness of 100 $\mu$ m, and the separation layer has a thickness of 50 $\mu$ m. The surface area of the inner walls approx. 100cm<sup>2</sup>. The outer wall and the inner wall are of  
25 polypropylene resin material, and the separation layer is of ethylene vinyl alcoholic (EVA).

The polypropylene resin material has a high

strength and low permeability of gasses. The EVA resin material has lower permeability of gasses than the polypropylene resin material, and low liquid contact property. In the case of the ink container shown in Figure 11, (a) and (b), the inner wall is not directly contacted to the ambience by the provision of the separation layer. The thickness of the outer wall is sufficiently larger than the inner wall or the separation layer. The gas permeability is substantially proportional to the average thickness of the wall, and therefore, the gas permeability is not considered for the outer wall and the inner wall. Thus, the inner wall desirably exhibits the high liquid contact property relative to the ink, and the separation layer desirably has the low gas permeability, and the outer wall desirably has a high strength. In the ink container of this embodiment, the desired materials may be used for the outer wall, the inner wall and the separation layer, respectively (function separation).

The description will be made as to the manufacturing method of the ink container of the third embodiment. The manufacturing method of this embodiment uses the blow molding method as in the first and second embodiment. The blow molding method includes an one using injection blow, an one using direct blow, an one using double wall blow. Here, the

direct blow molding method will be described,  
particularly as to the portion different from the  
first and second embodiments.

Figure 12, (a) -(d) show the manufacturing  
5 step of the ink container of this embodiment, and  
Figure 13 shows a sandwiching portion of the metal  
mold and a parison intermittently including the  
separation layer.

In Figure 12, designated by 211 is a main  
10 accumulator for supplying the resin material for the  
inner wall; 212 is a main extruder for extruding the  
inner wall resin material; 213a is a sub-accumulator  
for supplying the separation layer resin material;  
214a is a sub-extruder for extruding the separation  
15 layer resin material; 213b is a sub-accumulator for  
supplying the outer wall resin material; and 214b is a  
sub-extruder for extruding the outer wall resin  
material. The inner wall resin material, the  
separation layer resin material and the outer wall  
20 resin material thus supplied, are supplied to the dies  
216 through the ring 215 so that a parison 217  
integrally comprising them is formed. The parison  
217, as shown in Figure 12, (b) - Figure 2, (d), is  
molded by the metal mold 218 for sandwiching the  
25 parison 217 and by the air nozzle 219 for injecting  
the air at the top.

Referring to Figure 13 and 14, the

description will be made as to the manufacturing process for the ink container.

The inside material 217c, the separation resin material 217b and the outside resin material 5 217a are supplied (step S311, S312, S313), so that the parison 217 is extruded (step S314). The supply of the resin material, as shown in Figure 13, is such that the inner wall resin material 217c and the outer wall resin material 217a are continuously supplied, 10 but the separation resin material 217b is intermittently supplied.

The metal mold 218 capable of sandwiching the parison 217 is moved from the state shown in Figure 2, (b) to the state shown in Figure 2, (c) to sandwich 15 the parison 217 (step S315). Then, as shown in Figure 2, (c), the air is injected by the air nozzle 219 to effect the blow molding into the shape of the metal mold 218 (step S316).

Then, the container is separated from the 20 metal mold (step S317), and the ink is injected (step S318). Thereafter, the cap including the ink discharge permission member 126 is mounted (step S319).

In this blow molding, the parison 217 is 25 processed while it has a certain viscosity, and therefore, the inner wall resin material, the outer wall resin material and the separation layer resin

material do not have an orientation property.

The thicknesses  $t_1$ ,  $T_1$  and  $b$  of the inner wall resin material, the outer wall resin material and the separation resin material after the blow molding  
5 are smaller than the thicknesses  $t$ ,  $T$  and  $b$  thereof before the blow molding. In this embodiment, the outer wall resin material and the inner wall resin material satisfy  $T > t$  and  $T_1 > t_1$ . Since the separation layer is used only to separate the inner wall from the  
10 outer wall, the thickness thereof is not limited, but is desirably thinner than the inner wall in consideration of the liability that the separation layer does not sufficiently separate them. Therefore, the thickness  $b_1$  of the separation layer satisfies  
15  $b_1 = t_1 \times (1/2)$  in this embodiment.

Embodiment 4

Figure 18 shows an ink container according to a fourth embodiment of the present invention. In  
20 Figure 18, (a) is a sectional view, and (b) is a side view. In embodiment, the diameter of the parison is made larger to be substantially equal to the entire width of the container, as is different from the foregoing embodiment.

25 The different point will be described.

In Figure 16, (a), designated by 104 is a portion where the inner wall is welded, and the inner



wall is nipped by the outer wall. This portion is called " pinch-off portion ". The pinch-off portion 107, as shown in the Figure, is formed substantially along the entire width in the height direction of the 5 ink container 100.

The manufacturing method will be described. By thus reducing the expansion of the parison, the distance to the corner of the ink container from the parison can be reduced in effect, so that the 10 thicknesses of the corners can be made close to equal to each other, thus the variations of the strengths of the corners can be reduced.

By the provision of the pinch-off portion substantially over the entire width of the lateral 15 side of the container, as in this embodiment, the supporting portion of the inner wall is stabilized, and therefore, the negative pressure can be produced stably. By forming the wide pinch-off portion at each of the opposing positions, the strength of the 20 ink container per se can be increased, so that the reliability against the shock or the like is increased.

According to this embodiment, the similar effect can be provided irrespective of the 25 configuration of the ink container. However, it is particularly desirable that the configuration of the container is symmetrical, and the pinch-off portion is

faced to a side adjacent to the side having the maximum area, since then the negative pressure can be produced. More particularly, by resisting the deformation of the inner wall at the position opposed  
5 through the maximum area side, the deformation of the maximum side due to the ink consumption can be made regular. This further stabilizes the negative pressure together with the above-described corner deformation confinement.

10

#### Embodiment 5

Figure 19 is a schematic view of an ink container according to embodiment 5. In Figure 19, (a) is a sectional view, and (b) is a side view.


15

In embodiment, as compared with the above-described ink container, the corners and crossing portions between surfaces are slightly rounded.

By doing so, the corners and the crossing portions are stably formed, when the parison is  
20 expanded to the inside of the metal mold.

Additionally, the occurrence of a pin hole can be significantly prevented.

Furthermore, the film thicknesses of the outer wall and inner wall are made substantially  
25 uniformly by the rounded shape, so that stabilized surface movement is permitted. By the uniformity of the film thicknesses at the corners and intersections,



the strength can also be stabilized.

Furthermore, the corners are locally spherical, and the intersecting portions are locally cylindrical, so that the strength thereof is enhanced, and the collapsing thereof is effectively prevented. Thus, the collapse of the surface can be stably prevented.

In the case of this embodiment, the following relations apply:

(anti-collapse force of the surface per se) < (anti-collapse force of the crossing portion between adjacent sides) < (anti-collapse force of the corner).

therefore, the precedence order of collapses can be regulated, thus accomplishing the stabilized negative pressure generation.

The manufacturing method in the foregoing embodiments are usable for manufacturing the container of this embodiment, if the portions of the metal mold 208(Figure 12) corresponding to the corners and crossing portions between sides are rounded.

The manufacturing of the metal mold is easier, so that the productivity is improved, and therefore, the cost is reduced.

This embodiment is applicable to any shape of the container, and therefore, usable with any of the foregoing embodiment, and is usable with an embodiment which will be described below wherein only one wall is

used.

Embodiment 6

Figure 21 is a schematic view of an ink  
5 container according to embodiment 6.

In Figure 21, (a) is a sectional view, (b) is  
a side view, and (c) is a perspective view.

In this embodiment, one of the inner and  
outer walls is removed, or only one is used as the  
10 container structure.

Similarly to the first to fifth embodiments,  
the used manufacturing method is blow molding using  
blowing air. In the first and second embodiments, the  
parison is made of different resin materials using a  
15 main extruder 202 and sub-extruder 204, and the  
parison is fed into the mold, where the blowing air is  
supplied. In this embodiment, only the main extruder  
202 is used with a single resin material. The resin  
material may be an integral different resin materials  
20 having different liquid contact property and  
evaporation property.


In this type, the air vent is not  
necessitated, and the outer wall is not used.

The pinch-off portion is not provided at the  
25 maximum area portion, so that the thickness of the  
maximum area side continuously decreases from the  
center portion of the maximum area side to the

corners. When the container is produced in the same manner as in the foregoing embodiments with the outer wall, and then, the outer wall is removed, the distribution of the thickness of the outer wall is such that the central portion of the maximum area side of the inner wall is inwardly convex, as in the foregoing embodiments. The convex configuration and the distribution of the thickness are effective to permit smooth deformation of the maximum convex configuration side from the central portion thereof in response to the change in the negative pressure in the ink container, while increasing the convexity.

The corners move toward the center portion of the maximum area side in accordance with the decrease of the ink in the ink container, but the configuration of the corner is maintained. In this embodiment, the inside surfaces of the maximum area surfaces are brought into contact to each other with the reduction of the ink in the ink container, before the intersection or edge line formed between the maximum area side and a side adjacent thereto, collapses. Then, the contact area between the maximum area surfaces increases with the reduction of the ink. Therefore, the smooth deformation of the maximum area side is assured.

Because of the regularity of the deformation, the property thereof is suitable for an ink container.



The description will be made as to the use of the ink container according to an embodiment with a recording head. Figure 5, (a) is a schematic view of a recording head as a recording means connectable with the ink container of the present invention, and (b) shows the recording head and the ink container connected with each other.

In Figure 15, (a), designated by 401 is a recording head unit as the recording means, and includes as an unit black, yellow, cyan, magenta recording heads to permit full-color printing. Each of the recording heads includes liquid flow paths each having ejection outlets for ejecting the ink, and heat generating resistors for ejecting the ink through the ink ejection outlets.

Designated by 402 is an ink supply tube for introducing the ink into the recording head portion, and it has at one end a filter 403 for trapping the foreign matter or the bubble.

When the above-described ink container 100 is to be mounted to the recording head unit 401, the ink supply tube 402 is connected to a press-contact member 106 provided in the ink container 100, as shown in Figure 5, (b).

After the ink container mounting, the ink in the ink container is fed into the recording head side by unshown recovering means or the like provided in

the recording device, so that ink communication state is established. Thereafter, during the printing operation, the ink is ejected from the ink ejection portion 404 in the recording head so that the ink is  
5 consumed from the inside of the ink container inner wall 102.

In this embodiment, the ink supplying portion of the ink container is disposed at a lower position than the center thereof. Thus, there is no need of  
10 adjusting the ejection power of the recording head side despite the change of the ink remaining amount in the ink container, and in addition, the usage efficiency of the ink can be increased (the amount of the ink actually usable is increased).

15 Further, since the ink container of each of the embodiments, is capable of providing the negative pressure by itself, the press-contact member, valve, rubber plug or another ink discharge permission member provided at the ink supplying portion will suffice if  
20 it can retain the ink when the ink container is removed from the recording head.

The description will be made as to an ink jet recording apparatus for effecting the recording using the ink container of Figure 1 embodiment. Figure 16  
25 is a schematic view of an ink jet recording apparatus using the ink container of this embodiment.

In Figure 16, the head unit 401 and the ink

container 100 are fixing-and-supported on a carriage of the ink jet recording apparatus by unshown positioning means, wherein the recording head and the ink container are respectively detachable.

5           The forward and rearward rotation of the driving motor 513 is transmitted to a lead screw 504 through drive transmission gears 511 and 509 to rotate it, and the carriage has a pin(unshown) engageable with a spiral groove 505 of the lead screw 504. By  
10 this, the carriage is reciprocated in a longitudinal direction of the recording apparatus.

          Designated by 502 is a cap for capping a front side of each recording head in the recording head unit, and is used to effect the sucking recovery of  
15 the recording head through the opening in the cap by unshown sucking means. The cap 502 is moved by the driving force transmitted through the gear 508 or the like to cap the ejection side surface of the recording head. Adjacent the cap 502, an unshown cleaning blade  
20 is provided, and is supported for vertical movement. The blade is not in the disclosed form, but a known cleaning blade is usable.

          The capping cleaning sucking recovery are carried out when the carriage is at the home position  
25 by the operation of the lead screw 505. Any other known mechanism is usable for this purpose.

          Electrical connection pads 452 of the



recording head unit mounted to the carriage, are brought into contact to the connection pad 531 by the rotation of the connecting plate 530 provided on the carriage about a predetermined axis, thus establishing the electrical connection. Since a connector is not used, no excessive force is applied to the recording head.

In the foregoing description, the outer wall or the inner wall is of single layer structure, but it may of multi-layer structure for the purpose of increasing the anti-impact property, for example. Particularly, a multi-layer structure outer wall is effective to damage to the ink container during transportation or upon mounting thereof. An ink container may be the one integral with the ink jet recording head, may be the one detachably mountable relative to an ink jet recording head, or the like. The present invention is applicable to any type.

In the foregoing description, the ink container is used in the field of the ink jet recording, but is usable to a liquid accommodating container for supplying liquid with negative pressure to an outside member or element such as a pen.

A manufacturing method for the container of Figure 21 embodiment, will be described. Also, an additional description will be made as to the outer wall structure, and the effect of the outer wall to

the inner wall in each of the foregoing embodiments.

It is considered that the mold is shape  
beforehand to provide the desired curvature. The  
container of Figure 21 embodiment can be manufactured  
5 by producing only the outer wall or inner wall in the  
direct blow manufacturing method.

In the direct blow manufacturing method, the  
separable outer wall and inner wall are produced from  
a cylindrical parison by uniformly expanding it to the  
10 inside surfaces of the substantially prism shaped mold  
by air blow.

Therefore, the thickness of the inner wall is  
thinner in the corners than in the center portion  
region of the side surfaces. The same applies to the  
15 outer wall, that is, the thickness is thinner in the  
corners than in the center portion region of the side  
surfaces.

Therefore, the inner wall is formed as if it  
is laminated on the inside of the outer wall which has  
20 a thickness distribution gradually decreasing from the  
central portion of each of the sides to the corners.  
As a result, the inner wall is given an outer surface  
matched with the inner surface of the outer wall.  
Since the outer surface of the inner wall follows the  
25 thickness distribution of the outer wall, the inner  
wall becomes convex inwardly. These structures are  
desirable particularly in the maximum area side since

they assist the smooth deformation of the inner wall. The degree of convex shape of the inner wall may be not more than 2mm, and more particularly, the degree of the convex shape of the outer surface of the inner wall is not more than 1mm. The convex configuration may be within the measurement error range in a small area side, but it a desirable nature since it assists to provide regularity of precedence of deformations of the prism ink container.

10 Additional description will be made as to the outer wall. As described hereinbefore, one of the functions of the outer wall is to constrain the deformation of the corners of the inner wall. To accomplish this function, it desirably covers the corners of the inner wall and desirably maintain the shape of the inner wall against the deformation. Therefore, the outer wall or inner wall may be covered with a plastic resin material, metal or thick paper such as. The outer wall may cover the entirety of the inner wall, or it may be in the form of corner covers which may be connected with metal rods or the like. The outer wall may be of mesh structure structure.

25 The material for the liquid accommodating container may be polyethylene resin material, polypropylene resin material, and the material of the inner wall desirably has a stretching elastic modulus

of 15-3000 (kg/cm<sup>3</sup>).

Within this range, the proper material can be selected in consideration of the configuration, thickness and desired negative pressure such as of the  
5 container.

While the invention has been described with reference to the structures disclosed herein, it is not confined to the details set forth and this application is intended to cover such modifications or changes as  
10 may come within the purposes of the improvements or the scope of the following claims.

15

20

25



**The claims defining the invention are as follows:**

1. A manufacturing method for a liquid accommodating container for an ink jet recording apparatus, said container being capable of producing a negative pressure, said method comprising:

providing a liquid container, comprising:

a substantially prism-like outer wall provided with a substantial air vent portion and having a corner formed by 3 surfaces:

an inner wall having outer surfaces equivalent or similar to inside surfaces of said outer wall and a corner corresponding the corner of said outer wall, said inner wall defining a liquid accommodating portion for containing liquid therein, said inner wall further having a liquid supply portion for supplying the liquid out of said liquid accommodating portion;

wherein said inner wall has a thickness which decreases from a central portion of the surfaces of the prism-like shape to the corner, and said outer wall and said inner wall are separable from each other;

reducing pressure of the liquid accommodating portion to separate the inner wall and the outer wall from each other; and

supplying the liquid into the liquid accommodating portion.

2. A method according to claim 1, further comprising pressuring the accommodating portion.

DATED this Twenty-eighth Day of October, 1999

**Canon Kabushiki Kaisha**  
Patent Attorneys for the Applicant  
SPRUSON & FERGUSON







FIG. 1







FIG. 2



(a)



(b)





FIG. 3





(a)



(b)





FIG. 4



7 19 07 65104

5/21






FIG. 5


(a)



(b)



(c)



(d)





FIG. 6






FIG. 7







FIG. 8

9/21







FIG. 9








FIG. 10

(a)



(b)





FIG. II









FIG. 12

1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65  
66  
67  
68  
69  
70  
71  
72  
73  
74  
75  
76  
77  
78  
79  
80  
81  
82  
83  
84  
85  
86  
87  
88  
89  
90  
91  
92  
93  
94  
95  
96  
97  
98  
99  
100

13/21




FIG. 13

13/21






FIG. 14



15/21

(a)



(b)





FIG. 15



1 1 2 9 7 4 6 7 0 4




FIG. 16





FIG. 17

17  
21  
17  
21  
17  
21  
17  
21

(a)



(b)






FIG. 18



(a)



(b)





FIG. 19









FIG. 20



(a)



(b)



(c)




FIG. 21

