

208.4 - Glass Liquidus Temperature (solid form)

This SRM is intended for checking test methods and for calibrating equipment used to determine the liquidus temperature of glass by the gradient furnace methods per ASTM C 829.

PLEASE NOTE: The tables are presented to facilitate comparisons among a family of materials to help customers select the best SRM for their needs. For specific values and uncertainties, the certificate is the only official source.

[1416](#)
**Description >> Aluminosilicate Glass for Liquidus
 Temperature**
Unit Size >> 250 g

Method	
Temperature (°C)	1147

-
- Certified values are normal font
 - Non-certified or reference values are italicized
 - Non-certified values in parentheses are for information only